

Style 8764

Premium Grade Virgin PTFE Sheet & Film

Physical Properties

Property	Units	ASTM Method	Typical Values ¹
Specific Gravity	g/cc	D-792	2.14 - 2.20
Hardness	Shore D	D-2240	52-65
Tensile Strength	PSI	D-638 D-1708	4000 min
Elongation	%	D-638 D-1709	300 min
Deformation Under Load (73°F, 2000 psi, 24 hrs)	%	D-621	15 - 16
Coefficient Of Linear Thermal Expansion (78°F - 400°F)	in/in/°F	D-696	4 - 9 x 10 ⁻⁵
Thermal Conductivity	BTU/hr./ft ² /F in	C-177	1.7
Volume Resistivity	ohm - cm	D-257	>10 ¹⁵
Dielectric Strength	Volts / mil	D-149a	600 min

¹ The measured values expressed in ranges reflect measurements made both with and across the molding direction of the product.

Warning: Properties shown on this document are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations, consult Plastomer Technologies. While the utmost care has been used in compiling this document, we assume no responsibility for errors. This edition cancels all previous issues. Subject to change without notice.



Plastomer Technologies

an EnPro Industries company

10633 W Little York, Bldg 3, Suite 300

Houston, TX 77041

Phone: 713.983.4200 • 800.345.4901

Fax: 713.466.3721

E-mail: info@plastomertech.com

www.plastomertech.com

