

Garlock 19



MATERIAL PROPERTIES*

Color:	Black
Composition:	SBR rubber reinforced with 10.8oz cotton sheeting (5.0oz in 1/32" material).
Durometer, Shore A, +/- 5:	80
Temperature², Maximum, °F (°C):	+200 (+93)
Pressure², Maximum, psig (bar):	250 (17)
Finish Available	
Thru 1/8":	Cloth
Over 1/8":	Smooth
Number of Plies	
1/32", 1/16", 3/32":	1
1/8":	2
3/16":	3
1/4":	4

PHYSICAL PROPERTIES*

ASTM D751	Burst test across 2" (50mm) dia. opening	Not recommended for use as a diaphragm material.
	psi (bar):	
ASTM D149	Dielectric Properties, range, volts/mil.	
	Sample conditioning	<u>1/8"</u>
	None	31
ASTM F586	Design Factors	
	"m" factor:	1.25
	"y" factor, psi (N/mm ²):	400 (2.8)
ASTM D2000	Line Call Out:	2AA810A13 ⁽³⁾

Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material.

* Values do not constitute specification Limits

² When approaching the maximum or minimum ratings consult Garlock Applications Engineering

³ For rubber compound only, not fabric