

Garlock 22



MATERIAL PROPERTIES*

Color:	Red
Composition:	SBR Rubber
Durometer, Shore A, +/- 5:	75
Temperature², °F (°C)	
Minimum:	-10 (-23)
Maximum:	+200 (+93)
Pressure², Maximum, psig (bar):	250 (17)
P x T (max.)², psig x °F (bar x °C):	20,000 (600)
Finish Available	
Thru 1/8":	Cloth
Over 1/8":	Smooth
Meets Specification:	HHG-156 Type III and ASTM-D-1330 Grade I and II

PHYSICAL PROPERTIES*

ASTM D412	Tensile Strength , psi (N/mm ²):	700 (5)
ASTM D412	Elongation , %:	150
ASTM D395 B	Compression Set , 25% Deflection, Max. %	
	22 hours at 158°F (70°C):	40
ASTM D149	Dielectric Properties , range, volts/mil.	
	Sample conditioning	<u>1/8"</u>
	None	280 ⁽³⁾
ASTM F586	Design Factors	
	"m" factor:	1
	"y" factor, psi (N/mm ²):	200 (1.4)
ASTM D2000	Line Call Out:	2AA810A13F16EA14

Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material.

* Values do not constitute specification Limits

² When approaching the maximum or minimum ratings consult Garlock Applications Engineering

³ Indicates current arced around and not through gasket. Dielectric higher than indicated.