

Garlock 9064

MATERIAL PROPERTIES*

Color:	Off-White
Composition:	Neoprene rubber
Durometer , Shore A, +/- 5:	60
Temperature ² , °F (°C)	
Minimum:	-20 (-29)
Maximum:	+250 (+121)
Pressure ² , Maximum, psig (bar):	250 (17)
P x T (max.) ² , psig x °F (bar x °C):	20,000 (600)
Finish Available	
Thru 1/8":	Cloth
Over 1/8":	Smooth
Meets Specification:	FDA (Food and Drug Administration)

PHYSICAL PROPERTIES*

ASTM D412	Tensile Strength , psi (N/mm ²):	2400 (17)
ASTM D412	Elongation , %:	790
ASTM F586	Design Factors	
	"m" factor:	0.50
	"y" factor, psi (N/mm ²):	0 ⁽³⁾
ASTM D2000	Line Call Out:	2BE620A14E014E034F17

Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material.

* Values do not constitute specification Limits

² When approaching the maximum or minimum ratings consult Garlock Applications Engineering

³ Garlock Applications Engineering has historically recommended a suggested "Y" value of 100psi (0.7N/mm²) for these elastomers.