

# TEST REPORT

NO.HY20230331

**Supplier: YIWU HARLEY LEATHER PRODUCT CO.,LTD**

**Add: ROOM NO. 40440, LANE 10, 4TH FLOOR, INTERNATIONAL PRODUCTION  
MATERIAL MARKET, YIWU, ZHEJIANG, CHINA**

**CUSTOMER: VIET KAI ECOTECH COMPANY LIMITED**

**Add: 24/9/9/18 BEN LOI, BINH TRI DONG A WARD, BINH TAN DISTRICT, HO CHI MINH CITY**

**DESCRIPTION: MICROFIBER LEATHER**

THICKNESS	WIDTH	BACKING	EMBOSSING	COLOR
1.2mm	54inch	Microfiber base	Release paper	All series

TEST ITEM		STANDARD VALUE	TEST RESULT	RESULT
TENSILE STRENGTH(N/2.5cm)	L	≥360	591.1	Pass
	W	≥320	342.9	Pass
BLONGATION (%)	L	≥60	115.88	Pass
	W	≥80	201.38	Pass
TEARING STRENGTH (N)	L	≥60	74.3	Pass
	W	≥55	71.7	Pass
PEELING STRENGTH(N/2.5cm)	L	≥50	Unable to peel	Pass
	W	≥50	Unable to peel	Pass
BENDING RESISTANCE AT ROOM TEMPERATURE	>50000 Times	Pass		
COLD MODULUS OF RUPTURE (-10℃)	>15000 Times	Pass		
ABRASION (Martindale)	>30000 Times	Pass		
ABRASION (TAMBER)	1000 Revolutions	No obvious damage		
Remark	义乌市涵盈皮革制品有限公司 YIWU HARLEY LEATHER PRODUCT CO.,LTD			

Director: Ai su

QC: Lu peng

