



ELSEVIER

Contents lists available at ScienceDirect

## Applied Catalysis B: Environmental

journal homepage: [www.elsevier.com/locate/apcatb](http://www.elsevier.com/locate/apcatb)Effects of initial crystal structure of  $\text{Fe}_2\text{O}_3$  and Mn promoter on effective active phase for syngas to light olefinsYi Liu<sup>a</sup>, Fangxu Lu<sup>a</sup>, Yu Tang<sup>b</sup>, Minyang Liu<sup>a</sup>, Franklin Feng Tao<sup>b,\*</sup>, Yi Zhang<sup>a,\*</sup><sup>a</sup> State Key Laboratory of Organic-Inorganic Composites, Beijing University of Chemical Technology, 15 Beisanhuan East Road, Beijing 100029, PR China<sup>b</sup> Department of Chemical and Petroleum Engineering, University of Kansas, Lawrence, KS 66045, USA

## ARTICLE INFO

## Keywords:

Fischer-Tropsch synthesis  
Heterogeneous catalysis  
Light olefins  
Crystal phase effect  
Fe-Mn interaction

## ABSTRACT

Although it is generally acknowledged that iron carbides are the active phase in Fischer-Tropsch synthesis (FTS), adjusting the formation of active phase and catalytic performance via the initial crystal structure of iron oxides has never been studied. Herein, we take one-dimensional pure phase  $\alpha\text{-Fe}_2\text{O}_3$  and  $\gamma\text{-Fe}_2\text{O}_3$  nonporous nanorods to explore the effects of initial crystal phase of  $\text{Fe}_2\text{O}_3$  on both formation of active phase and corresponding catalytic performance, in which the influence of diffusion limitation on selectivity can be ignored. *In situ* characterizations uncovered that the formation of iron carbides with high selectivity of light olefins strongly depends on the initial crystal phase of iron oxide and its induced metal-promoter interaction. Responding to the morphology effect and crystallographic phase effect, Mn located on surface of  $\gamma\text{-Fe}_2\text{O}_3$  nanorods exhibit a low oxidation state due to a strong Fe-Mn interaction. This interaction was beneficial to the formation of C-poor iron carbide species at the metal-promoter interface during carburization. Hence, outstanding selectivity for light olefins (61.2%) was achieved on 0.5 Mn/ $\gamma\text{-Fe}_2\text{O}_3$  nanorods catalyst at a CO conversion of 55.1% under industrially relevant conditions (320 °C, 1 MPa,  $\text{H}_2/\text{CO}$  ratio of 1, and  $\text{W/F} = 5 \text{ g}_{\text{cat}} \text{ h mol}^{-1}$ ). This finding enriches the fundamental understanding of active phase evolution and promoter effect in STO process and may guide the design of a catalyst with high selectivity.

## 1. Introduction

Fischer-Tropsch synthesis (FTS) has long been known as an alternative process to produce synthetic liquid fuels and valuable chemicals from coal, natural/shale gas and lignocelluloses biomass [1]. Recently, direct synthesis of light olefins ( $\text{C}_2\text{-C}_4$ ) from syngas (STO) using Fe-based catalysts has become an increasingly important research topic in the conventional FTS process [2–4]. Generally, the most common initial phase of fresh Fe catalyst is present as iron oxides, which is hematite ( $\alpha\text{-Fe}_2\text{O}_3$ ) and occasionally maghemite ( $\gamma\text{-Fe}_2\text{O}_3$ ) [5–8]. And  $\gamma\text{-Fe}_2\text{O}_3$  has the same XRD patterns with that of  $\text{Fe}_3\text{O}_4$  [7], which might be ignored by previous researchers in FTS. The initial iron oxides are transformed to various types of iron carbides (such as  $\chi\text{-Fe}_5\text{C}_2$ ,  $\epsilon\text{-Fe}_2\text{C}$ , and  $\theta\text{-Fe}_3\text{C}$ ) [9–13] during reduction and carburization processes. The formation of different types of iron carbides was typically attributed to experimental kinetic factors (lattice deformation, carbon diffusion) and different carbon potential ( $\mu_c$ ) surroundings [10,14]. Although it is generally acknowledged that iron carbides are the active phase in FTS [15–17]. The correlation between initial phase of iron oxides and formation of iron carbide has never been studied and remained unknown. In fact,

maghemite ( $\gamma\text{-Fe}_2\text{O}_3$ ) can be more easily reduced in contrast to  $\alpha\text{-Fe}_2\text{O}_3$  phase [18,19]. As the formation of active phase of Fe-based catalyst of FT synthesis involves reduction of oxide to iron and carbonization of metal to carbide, we hypothesized that the initial surface chemistry and structure of the two different oxides ( $\alpha\text{-Fe}_2\text{O}_3$  versus  $\gamma\text{-Fe}_2\text{O}_3$ ) could significantly influence the formation of iron carbide phase. Thus, here we explored the potential correlation between properties of  $\alpha\text{-Fe}_2\text{O}_3$  and  $\gamma\text{-Fe}_2\text{O}_3$  and its phase transition to iron carbides in syngas and their corresponding catalytic performance. To clearly present the difference, we performed two sets of parallel studies by using pure  $\alpha\text{-Fe}_2\text{O}_3$  and  $\gamma\text{-Fe}_2\text{O}_3$  nonporous nanorods under same catalytic conditions, which can avoid the influence of diffusion limitation on the selectivity during the FTS reaction due to its nonporous structure and low surface area [11].

Manganese has been widely described as an effective promoter to increase olefins selectivity and suppress the formation of methane [20,21]; however, the promotion function is poorly understood since in most studies there was no control of other factors which may vary catalytic selectivity. In addition, iron oxide has been found to be a good candidate as cheap and efficient active metal and/or support, and it can form interaction with other active metal or promoter and enhance

\* Corresponding authors.

E-mail addresses: [franklin.feng.tao@ku.edu](mailto:franklin.feng.tao@ku.edu) (F.F. Tao), [yizhang@mail.buct.edu.cn](mailto:yizhang@mail.buct.edu.cn) (Y. Zhang).<https://doi.org/10.1016/j.apcatb.2019.118219>

Received 4 July 2019; Received in revised form 15 August 2019; Accepted 18 September 2019

Available online 19 September 2019

0926-3373/ © 2019 Elsevier B.V. All rights reserved.

catalytic performance [22–24]. To clearly understand how the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> could be responsible for the promotion effect of Mn differently, we use pure phase  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> nanorods which have the same morphology and very similar sizes as support to anchor Mn. Different from the conventional supported or bulk Fe nanoparticles catalysts with complicated composition and many mesopores or micropores, here pure phase  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> nonporous nanorods were synthesized through an aqueous precipitation method to avoid the influence of other factors such as diffusion limitation [11,25], metal/promoter-inert support interaction [26], farraginous crystal facets [5], and ambiguous spatial collocation between Fe and Mn [27]. Based on various characterization results, we found that phase transitions of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> to iron carbides are distinctly different; the active phases from  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> exhibit quite different selectivity of light olefins in FTS. On the other hand, due to the different properties of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>, the more reduced MnO<sub>1-x</sub> edge sites with strong Fe-Mn interaction was preferentially formed on the surface of  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> nanorods, which was beneficial to the formation of C-poor iron carbides phase ( $\theta$ -Fe<sub>3</sub>C), resulting in forming more light olefins.

## 2. Experimental methods

### 2.1. Catalysts synthesis

The  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> nanorods were prepared by an aqueous precipitation method as reported [28]. Briefly, a mixture containing FeCl<sub>3</sub>·6H<sub>2</sub>O (5.38 g), NaCl (11.60 g), and PEG (10 mL) was premixed and dissolved in water (190 mL) at 120 °C. A Na<sub>2</sub>CO<sub>3</sub> aqueous solution (200 mL, 0.2 M) was then added under stirring at a rate of 5.5 mL min<sup>-1</sup>. After that, the mixture was aged at 120 °C for 1 h. The precipitate was then washed with deionized water and ethanol, and finally dried at 50 °C for 6 h under vacuum to obtain the  $\beta$ -FeOOH precursor. The  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> nanorods were prepared by heating the  $\beta$ -FeOOH precursor in PEG at 200 °C to reflux for 24 h under a stream of nitrogen. The resulting solid was washed with water and ethanol, followed by drying at 50 °C for 12 h under vacuum. The  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> nanorods were prepared by calcining the  $\beta$ -FeOOH precursor at 500 °C for 5 h. For preparation of Mn promoted Fe<sub>2</sub>O<sub>3</sub> nanorods catalysts, in order to improving the dispersion of supported Mn [11], an ethylene glycol solution of Mn(NO<sub>3</sub>)<sub>2</sub>·4H<sub>2</sub>O was impregnated onto the Fe<sub>2</sub>O<sub>3</sub> nanorods, followed by drying at 200 °C under vacuum. All samples were pressed into pellets (10 MPa), crushed and sieved to retain 20–40 mesh particles for reaction tests.

### 2.2. Synthesis of iron carbide reference samples

The  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> precursors were firstly prepared by precipitation method. 15 g Fe(NO<sub>3</sub>)<sub>3</sub>·9H<sub>2</sub>O (99.9%, Tianjing Chemical Co., China) were dissolved in 300 ml deionized water, and continuously stirred for 1 h at room temperature. Aqueous Na<sub>2</sub>CO<sub>3</sub> (99.9%, Beijing Chemical Co., China) was used as a precipitating agent. Both solutions were simultaneously added to a precipitating batch containing 300 ml of distilled water at the start, and its rate was controlled in order to keep the pH of the slurry at 8.0 ± 0.2 during precipitation. The resulting precipitate was first filtered and then washed with deionized water. The precursor was dried in air at 120 °C for 12 h, and then calcined at 500 °C for 2 h. After that,  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> reference materials was synthesized by exposing the precipitated  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> to a flow of 15 mL min<sup>-1</sup> CO (99.0%) and heating it up to 350 °C at 2 °C min<sup>-1</sup> [14].

$\theta$ -Fe<sub>3</sub>C reference materials was synthesized by wet-chemical route [29]. The iron precursor solution was prepared by dissolving iron(II) acetate (1.5 g, Aldrich) in 20 mL deionized water. Gelatin (2 g, Type A from porcine skin, Sigma #G2500) was dissolved in deionized water (100 mL) at 90 °C to form a clear biopolymer solution. To synthesize iron carbide, the iron acetate solution (10 mL) was added dropwise to the biopolymer solution (6 mL) with fast stirring. The products were

dried at 80 °C in air for 5 h, and then calcined at 650 °C under a flow of N<sub>2</sub> for 2 h.

### 2.3. Catalysts characterization

For characterization of carburized catalysts, the catalysts were pre-carburized at 340 °C for 10 h using syngas (H<sub>2</sub>/CO = 1) and then passivated by 1% O<sub>2</sub> in N<sub>2</sub> at room temperature to form a metal oxide layer on the surface of metal particle, in order to preventing oxidation of iron metal when the catalysts were exposed to air. Before the *in situ* XPS/XAFS characterization, the passivated samples were carburized again *in situ* at 340 °C for 1–2 h using syngas (H<sub>2</sub>/CO = 1).

The size and morphology of the products were characterized by scanning electron microscope (SEM, JEOL, JSM-7600 F) and high-resolution transmission electron microscope (HRTEM, JEOL, JEM-2100). The specimen was prepared by ultrasonically suspending the sample in ethanol. A drop of the suspension was deposited on a coverslip or carbon-coated copper grids and dried in air. XRD measurements were determined on an X-ray diffractometer (SHIMADZU XRD-6000) with Cu K $\alpha$  radiation ( $\lambda$  = 0.154 nm), operated at 40 kV and 30 mA. Nitrogen adsorption isotherms measurement was carried out at -196 °C with a Micrometrics ASAP 2020 equipment. The sample was degassed at 180 °C for 6 h prior to the measurement. Raman spectroscopy (Renishaw UV-vis Raman 1000) with laser excitation at a visible 514 nm (Ar<sup>+</sup> laser) was conducted at room temperature to evaluate the structure of samples.

*In-situ* XPS experiments were performed at the photoemission end-station at beamline BL10B in the National Synchrotron Radiation Laboratory (NSRL) in Hefei, China. The beamline is connected to a bending magnet and covers photon energies from 60 to 1000 eV with a resolving power (E/ $\Delta$ E) better than 1000. The end-station is composed of four chambers, *i.e.*, analysis chamber, preparation chamber, quick sample load-lock chamber and high pressure reactor. The analysis chamber, with a base pressure of < 2 × 10<sup>-10</sup> torr, is connected to the beamline and equipped with a VG Scienta R3000 electron energy analyzer and a twin anode X-ray source. The high pressure reactor houses a reaction cell where the samples can be treated with different gases up to 20 bar and simultaneously heated up to 650 °C. After the sample treatment, the reactor can be pumped down to high vacuum (< 10<sup>-8</sup> torr) for sample transfer. In the current work, the pre-carburized samples were pressed into thin pellets and then placed into the reaction cell and carburized in a flowing syngas (H<sub>2</sub>/CO = 1) under atmospheric pressure at 340 °C for 2 h. Then the samples were cooled down to room temperature and transferred to the analysis chamber under vacuum conditions for measurements.

H<sub>2</sub> temperature programmed reduction (H<sub>2</sub>-TPR) experiments were carried out in a quartz tube reactor using 0.05 g as-prepared catalysts. The reducing gas, a mixture of 10% H<sub>2</sub> diluted by Ar, was fed via a mass flow controller at 30 mL min<sup>-1</sup> and the temperature was increased from 30 °C until 800 °C at a rate of 8 °C min<sup>-1</sup>. The effluent of reactor passed through a 5 Å molecular sieve trap to remove produced water, before reaching TCD. CO-TPD experiments were performed on Micrometrics 2020 chemisorption instrument equipped with a thermal conductivity detector (TCD), using Helium as the carrier gas. The sample loading was 0.1 g. The pretreatment conditions were the same as the reduction conditions before FTS reaction. After pretreatment, the sample was cooled to 50 °C and exposed to 5% CO/95% He (30 mL min<sup>-1</sup>) for 30 min, purged in He for 1 h at 50 °C and then heated linearly at 10 °C min<sup>-1</sup> to 800 °C.

*In situ* X-ray absorption spectra at Fe K-edge and Mn K-edge for the catalysts and the reference compounds were measured on the beamline 1W1B of Beijing Synchrotron Radiation Facility (BSRF). The storage ring of BSRF was operated at 2.5 GeV with a maximum current of 120 mA. The X-ray absorption spectra at K-edge of the metals were collected in transmission mode. Fe foil (99.99%),  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> (99.9%, Aldrich-sigma) and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> (99.9%, Aldrich-sigma) were used as

references. The XAS data was processed and analyzed by Demeter software package including Athena and Artemis [30]. The  $k^2$ -weighted  $r$ -space spectrum was obtained from Fourier transformation and then fitted. The fitting range of  $k$  is 3–10 Å<sup>-1</sup>, while the range of  $r$ -space is 1–4 Å. Coordination number, distance and Debye-Waller factor ( $ss$ ) were fitted as variables. The iron phase compositions were fitted from XANES by using principle combination analysis (PCA) and the linear combination fitting (LCF) method.

Transmission <sup>57</sup>Fe Mössbauer spectra were collected at room temperature on an MR-351 constant-acceleration Mössbauer spectrometer (FAST, Germany), using a 25 mCi <sup>57</sup>Co in Pd matrix. The spectrometer was operated in the symmetric constant acceleration mode. Data analysis was performed using a nonlinear least-squares fitting routine that models the spectra as a combination of singlets, quadruple doublets, and magnetic sextuplets based on a Lorentzian line shape profile.

## 2.4. Fischer-Tropsch synthesis reaction

The FTS reaction was carried out in a continuous-flow-type fixed-bed reactor (stainless steel 316, 8 mm i.d.) under the temperature of 320 °C and a pressure of 1.0 MPa. The feed gas consisted of Ar (4.9%), CO (47.5%) and H<sub>2</sub> (47.6%), where Ar was used as inner reference gas. The 0.5 g catalyst mixed with 1.0 g quartz sand was placed in the reactor tube. The temperature was then increased from room temperature to 340 °C at a rate of 2 °C·min<sup>-1</sup>. The catalyst was carburized *in situ* at 340 °C for 10 h in the flow of feed gas (W/F(CO + H<sub>2</sub> + Ar) = 2.5 g<sub>cat</sub>·h·mol<sup>-1</sup>) at 0.1 MPa, followed by cooling down to 80 °C in N<sub>2</sub>. After that, the reaction temperature was increased to 320 °C at a rate of 10 °C·min<sup>-1</sup>, with a flow of pressurized syngas (W/F(CO + H<sub>2</sub> + Ar) = 5 g<sub>cat</sub>·h·mol<sup>-1</sup>). The reaction was continuously carried out for 20–50 h.

The effluent gas from the reactor was analyzed by on-line gas chromatography (GC-2014C, Shimadzu). A thermal conductivity detector (TCD) was used to analyze gaseous products (CO, CO<sub>2</sub> and CH<sub>4</sub>). Light hydrocarbons (C<sub>1</sub>–C<sub>5</sub>) were on-line analyzed by another GC with flame ionization detector (FID) using a Porapak-Q column. The analyses of hydrocarbons dissolved in the solvent (10 ml *n*-decane) and cooled in the trap were carried out with GC-FID using silicone SE-30 column. The mass balance of various reactions were calculated, which were almost 95% based on carbon mole for all reactions.

## 3. Results and discussion

### 3.1. Relationship between initial crystal phases and catalytic performances

Fig. 1a is a typical X-ray powder diffraction (XRD) patterns of the as-prepared α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> nanorods, suggesting that the as-synthesized sample is well crystallized α-Fe<sub>2</sub>O<sub>3</sub> (JCPDS 33-0664) and γ-Fe<sub>2</sub>O<sub>3</sub> (JCPDS 39-1346) phase, respectively. As γ-Fe<sub>2</sub>O<sub>3</sub> has the same XRD patterns with that of Fe<sub>3</sub>O<sub>4</sub>, the formation of γ-Fe<sub>2</sub>O<sub>3</sub> phase was

further confirmed by the appearance of broad Raman characteristic features around 353, 491, 665, and 720 cm<sup>-1</sup> (Fig. 1b) [18,31] and XANES spectra (Fig. S1). Scanning electron microscopy (SEM) and transmission electron microscopy (TEM) observations (Fig. 2) revealed that the as-prepared α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> samples have the same morphology, which are nanorods with an average diameter of 40 nm and length of 500 nm. However, they have distinctly different crystal phases. The measured interplanar distances of 0.250 nm and 0.295 nm in HRTEM (Fig. 2c and f) corresponds to the (110) plane of α-Fe<sub>2</sub>O<sub>3</sub> and (220) plane of γ-Fe<sub>2</sub>O<sub>3</sub>, respectively. Moreover, both α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> display type-II N<sub>2</sub> sorption isotherm (Fig. S2) typically associated with nonporosity, yielding the low surface area of 11.7 m<sup>2</sup> g<sup>-1</sup> and 12.5 m<sup>2</sup> g<sup>-1</sup>, respectively, those could guarantee to avoid the influence of diffusion limitation on selectivity during FTS reaction. Thus, the successful preparation of α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> with highly similar size and surface area allow exploring crystal phase-dependent formation of iron carbide and correlating this phase formation and catalytic selectivity.

The as-prepared pure α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> nanorods were carburized at 340 °C for 10 h and then tested in the FTS at 320 °C, 1 MPa, H<sub>2</sub>/CO ratio of 1, and W/F = 5 g<sub>cat</sub>·h·mol<sup>-1</sup>. As shown in Fig. 3a, b, The CO conversion and light olefins selectivity of both catalysts increased during the first 5 h of reaction, suggesting an incubation of FTS. It is reasonable since this is the period for the formation of stable active phase. The α-Fe<sub>2</sub>O<sub>3</sub> nanorods catalyst shows a lower maximum CO conversion (56.1%) than γ-Fe<sub>2</sub>O<sub>3</sub> nanorods catalyst (82.5%), likely due to the lower reducibility of α-Fe<sub>2</sub>O<sub>3</sub>, as confirmed by H<sub>2</sub>-TPR result (Fig. S3). Mössbauer spectra results of the reduced samples (Table 2) also show that the concentration of Fe<sub>x</sub>C in γ-Fe<sub>2</sub>O<sub>3</sub> catalyst is higher than that in α-Fe<sub>2</sub>O<sub>3</sub> catalyst, which contributed to the higher catalytic activity. After FTS of 20 h on stream, the catalytic performances reached a steady state (Fig. 3a, b) and the CO conversion of α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> catalysts were change to 52.7% and 57.1%, respectively. Meanwhile, it was found that α-Fe<sub>2</sub>O<sub>3</sub> catalyst exhibited much higher light olefins selectivity (44.5%) and olefin/paraffin ratio in C<sub>2</sub>–C<sub>4</sub> (4.01) compared with γ-Fe<sub>2</sub>O<sub>3</sub> nanorods catalyst. The γ-Fe<sub>2</sub>O<sub>3</sub> catalyst exhibits a light olefins selectivity of only 25.4% with olefin/paraffin ratio of 1.09 (Fig. 3c and Table 1). Thus, the observed distinct difference in selectivity must result from the potentially different phase transitions, which resulted in the formation of different active phases.

To reveal the correlation between initial phase and the formation of active phase, multiple characterization techniques were used to track surface and bulk structures of Fe catalyst. Based on the XRD studies of carburized (Figs. S4–S5) and spent catalysts (Fig. S6), Hägg carbide (χ-Fe<sub>5</sub>C<sub>2</sub>, JCPDS 36-1248) was the only carbide species detected from carburized/spent γ-Fe<sub>2</sub>O<sub>3</sub> catalyst. In contrast, for α-Fe<sub>2</sub>O<sub>3</sub> catalyst, a broad diffraction peak centered at ~45° indexed to cementite (θ-Fe<sub>3</sub>C, JCPDS 76-1877) was observed after carburization and 20 h reaction. The identification of iron carbide phases with XRD was further




Fig. 1. a) XRD patterns for the as-prepared α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> nanorods. b) Raman spectra of the as-prepared α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> nanorods.






Fig. 2. a) SEM image of the  $\alpha$ - $\text{Fe}_2\text{O}_3$  nanorods. b–c) HRTEM images of the  $\alpha$ - $\text{Fe}_2\text{O}_3$  nanorods. d) SEM image of the  $\gamma$ - $\text{Fe}_2\text{O}_3$  nanorods. e–f) HRTEM images of the  $\gamma$ - $\text{Fe}_2\text{O}_3$  nanorods.




Fig. 3. a) CO conversion and stability of various iron-based catalysts; b) Light olefins selectivity as a function of time on-stream for various iron-based catalysts; c) Catalytic performance of all  $\text{Fe}_2\text{O}_3$  nanorods catalysts with and without Mn promoter. Reaction conditions:  $\text{H}_2/\text{CO} = 1$ ,  $T = 320^\circ\text{C}$ ,  $P = 1.0\text{ MPa}$  and  $W/F(\text{CO} + \text{H}_2 + \text{Ar}) = 5\text{ g}_{\text{cat}}\cdot\text{h mol}^{-1}$ .

**Table 1**  
Catalytic activity and product selectivity of various iron-based catalysts.<sup>a</sup>

| Entry | Catalysts                               | CO conv. (%) <sup>b</sup> | CO conv. (%) <sup>c</sup> | CO <sub>2</sub><br>(%CO conv.) <sup>c</sup> | Hydrocarbon selectivity<br>(c-mol %, CO <sub>2</sub> -free) <sup>c</sup> |                  |                  |                 | O/P <sup>d</sup> |
|-------|-----------------------------------------|---------------------------|---------------------------|---------------------------------------------|--------------------------------------------------------------------------|------------------|------------------|-----------------|------------------|
|       |                                         |                           |                           |                                             | CH <sub>4</sub>                                                          | C <sub>2-4</sub> | C <sub>2-4</sub> | C <sub>5+</sub> |                  |
| 1     | γ-Fe <sub>2</sub> O <sub>3</sub>        | 82.5                      | 57.1                      | 34.1                                        | 23.5                                                                     | 25.4             | 23.4             | 27.7            | 1.09             |
| 2     | 0.3 Mn/γ-Fe <sub>2</sub> O <sub>3</sub> | 64.0                      | 59.3                      | 30.4                                        | 15.2                                                                     | 50.1             | 10.2             | 24.5            | 4.91             |
| 3     | 0.5 Mn/γ-Fe <sub>2</sub> O <sub>3</sub> | 57.1                      | 55.1                      | 31.7                                        | 11.7                                                                     | 61.2             | 8.9              | 18.2            | 6.88             |
| 4     | 1Mn/γ-Fe <sub>2</sub> O <sub>3</sub>    | 52.4                      | 48.2                      | 33.9                                        | 14                                                                       | 56.4             | 10.1             | 19.5            | 5.58             |
| 5     | α-Fe <sub>2</sub> O <sub>3</sub>        | 56.1                      | 52.7                      | 28.0                                        | 19.2                                                                     | 44.5             | 11.1             | 25.2            | 4.01             |
| 6     | 0.3 Mn/α-Fe <sub>2</sub> O <sub>3</sub> | 38.7                      | 35.2                      | 22.5                                        | 17.1                                                                     | 50.7             | 10.5             | 21.7            | 4.83             |
| 7     | 0.5 Mn/α-Fe <sub>2</sub> O <sub>3</sub> | 30.8                      | 29.4                      | 19.1                                        | 18.3                                                                     | 51.6             | 10.2             | 19.9            | 5.06             |
| 8     | 1Mn/α-Fe <sub>2</sub> O <sub>3</sub>    | 24.9                      | 23.6                      | 20.2                                        | 17.5                                                                     | 48.2             | 10.9             | 23.4            | 4.42             |

<sup>a</sup> Reaction condition: 320 °C, 1.0 MPa, H<sub>2</sub>/CO = 1, W/F(CO + H<sub>2</sub> + Ar) = 5 g<sub>cat</sub> h mol<sup>-1</sup>, time on stream 20 or 50 h.

<sup>b</sup> The highest conversion with time on stream.

<sup>c</sup> The data were taken after 20 h of time on stream.

<sup>d</sup> The molar ratio of olefin to paraffin in the fraction C<sub>2</sub>-C<sub>4</sub>.

**Table 2**  
Mössbauer parameters of the carburized catalysts after 10 h of carburization at T = 340 °C, P = 0.1 MPa and H<sub>2</sub>/CO ratio of 1.

| Catalysts                                        | Phases                                           | Mössbauer parameters <sup>a</sup> |           |           |                       |      |
|--------------------------------------------------|--------------------------------------------------|-----------------------------------|-----------|-----------|-----------------------|------|
|                                                  |                                                  | IS (mm/s)                         | QS (mm/s) | Hhf (kOe) | Area <sup>b</sup> (%) |      |
| $\alpha$ -Fe <sub>2</sub> O <sub>3</sub>         | Fe <sub>5</sub> C <sub>2</sub>                   | 0.40                              | 0.80      | 225       | 5.0                   |      |
|                                                  |                                                  | 0.01                              | −0.61     | 185       | 5.0                   |      |
|                                                  |                                                  | 0.06                              | 0.13      | 118       | 2.5                   |      |
|                                                  | Fe <sub>3</sub> C                                | 0.22                              | −0.17     | 208       | 8.4                   |      |
|                                                  |                                                  | 0.31                              | 0.53      | 204       | 4.2                   |      |
|                                                  | Fe <sub>3</sub> O <sub>4</sub>                   | 0.53                              | −0.005    | 486       | 34.9                  |      |
|                                                  |                                                  | 0.59                              | 0.26      | 446       | 33.7                  |      |
|                                                  | Fe <sup>3+</sup> (spm)                           | 0.40                              | −1.45     |           | 0.9                   |      |
|                                                  | Fe <sup>2+</sup> (spm)                           | 0.70                              | −1.43     |           | 5.4                   |      |
|                                                  | $\gamma$ -Fe <sub>2</sub> O <sub>3</sub>         | Fe <sub>5</sub> C <sub>2</sub>    | 0.40      | 0.80      | 212                   | 12.0 |
| 0.10                                             |                                                  |                                   | −0.55     | 192       | 12.0                  |      |
| 0.04                                             |                                                  |                                   | 0.80      | 117       | 5.8                   |      |
| Fe <sub>3</sub> O <sub>4</sub>                   |                                                  | 0.37                              | −0.04     | 508       | 24.2                  |      |
|                                                  |                                                  | 0.37                              | −0.02     | 459       | 30.6                  |      |
| Fe <sup>3+</sup> (spm)                           |                                                  | 0                                 | −0.98     |           | 4.8                   |      |
| Fe <sup>2+</sup> (spm)                           |                                                  | 0.70                              | −0.95     |           | 10.6                  |      |
| 0.5 Mn/ $\alpha$ -Fe <sub>2</sub> O <sub>3</sub> |                                                  | Fe <sub>5</sub> C <sub>2</sub>    | 0.03      | 0.56      | 224                   | 6.3  |
|                                                  |                                                  |                                   | 0.14      | 0.27      | 192                   | 6.3  |
|                                                  |                                                  |                                   | 0.26      | −0.15     | 113                   | 3.2  |
|                                                  | Fe <sub>3</sub> C                                | 0                                 | −0.80     | 210       | 2.4                   |      |
|                                                  |                                                  | 0.19                              | −0.80     | 204       | 1.2                   |      |
|                                                  | Fe <sub>3</sub> O <sub>4</sub>                   | 0.30                              | −0.01     | 493       | 32.8                  |      |
|                                                  |                                                  | 0.60                              | 0.05      | 454       | 31.6                  |      |
|                                                  | Fe <sup>3+</sup> (spm)                           | 0.16                              | −0.85     |           | 8.0                   |      |
|                                                  | Fe <sup>2+</sup> (spm)                           | 1.16                              | −0.51     |           | 8.2                   |      |
|                                                  | 0.5 Mn/ $\gamma$ -Fe <sub>2</sub> O <sub>3</sub> | Fe <sub>5</sub> C <sub>2</sub>    | 0.12      | −0.80     | 198                   | 4.3  |
| 0.23                                             |                                                  |                                   | −0.50     | 180       | 4.3                   |      |
| 0.21                                             |                                                  |                                   | −0.05     | 110       | 2.1                   |      |
| Fe <sub>3</sub> C                                |                                                  | 0.18                              | −0.04     | 208       | 14.0                  |      |
|                                                  |                                                  | 0.34                              | 0.80      | 207       | 7.0                   |      |
| Fe <sub>3</sub> O <sub>4</sub>                   |                                                  | 0.49                              | 0.64      | 475       | 20.5                  |      |
|                                                  |                                                  | 0.41                              | −0.34     | 484       | 36.4                  |      |
| Fe <sup>3+</sup> (spm)                           |                                                  | 0.02                              | 0.50      |           | 6.8                   |      |
| Fe <sup>2+</sup> (spm)                           |                                                  | 1.20                              | −0.75     |           | 4.6                   |      |

<sup>a</sup> Measured at room temperature.

<sup>b</sup> Max error = ± 1%.

supported by HRTEM images and Mössbauer spectra. HRTEM images (Fig. 4c-f) showed that the Fe<sub>2</sub>O<sub>3</sub> species were converted to Fe<sub>3</sub>O<sub>4</sub> and Fe<sub>5</sub>C<sub>2</sub> phase as a result of carburized treatment for both samples. In the case of the α-Fe<sub>2</sub>O<sub>3</sub> sample, Fe<sub>3</sub>C nanoparticles with exposed facets of (121) were observed as shown in Fig. 4c. In addition, it was found that the nanorod structure of α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> both maintained very well after carburization (Fig. 4a, b) and 20 h reaction (Fig. 4g, h).


Mössbauer spectroscopy is most powerful tool for identifying and quantifying iron phases in iron-based catalysts [12,13]. In the

Mössbauer spectrum of carburized α-Fe<sub>2</sub>O<sub>3</sub> catalyst (Fig. S7 and Table 2), three sextets (225, 185, and 118 kOe) for γ-Fe<sub>5</sub>C<sub>2</sub> and two sextets (208 and 204 kOe) for θ-Fe<sub>3</sub>C were observed [32], showing coexistence of both γ-Fe<sub>5</sub>C<sub>2</sub> and θ-Fe<sub>3</sub>C on FTS catalyst formed from α-Fe<sub>2</sub>O<sub>3</sub>; the total concentration of Fe<sub>x</sub>C (γ-Fe<sub>5</sub>C<sub>2</sub> + θ-Fe<sub>3</sub>C) formed from α-Fe<sub>2</sub>O<sub>3</sub> is 25.1%. In contrast, only γ-Fe<sub>5</sub>C<sub>2</sub> was formed from γ-Fe<sub>2</sub>O<sub>3</sub> and its fraction is 29.8%. We further explored Mössbauer spectra of α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> catalysts after 20 h on stream in FTS (Fig. 5 and Table 3). After reaction, the content of iron oxide in α-Fe<sub>2</sub>O<sub>3</sub> catalyst decreases from 74.9% in carburized catalyst to 66.9%, indicating that further carburization takes place during the reaction. The content of γ-Fe<sub>5</sub>C<sub>2</sub> increases to 22.3%, while the content of Fe<sub>3</sub>C slightly decreases to 10.8%. The further carburization during the reaction is probably due to the higher gas pressure (1 MPa) and longer reaction time compared with the carburization step. In contrast, the content of γ-Fe<sub>5</sub>C<sub>2</sub> in the spent γ-Fe<sub>2</sub>O<sub>3</sub> catalyst also increased to 34.0%, which is higher than the value of 29.8% in the carburized γ-Fe<sub>2</sub>O<sub>3</sub> catalyst. However, the θ-Fe<sub>3</sub>C phase is still absent in spent γ-Fe<sub>2</sub>O<sub>3</sub> catalyst. In addition, for both carburized and spent α-Fe<sub>2</sub>O<sub>3</sub> or γ-Fe<sub>2</sub>O<sub>3</sub> samples, the Mössbauer spectra include two doublets, which is assigned to the superparamagnetic (spm) Fe<sup>3+</sup>/Fe<sup>2+</sup> ions with the crystallite diameters smaller than 13.5 nm [2,6]. This is due to the limitation of room temperature Mössbauer spectra. At lower measurement temperatures (< 25 K), the coupling forces prevail over the thermal energy, causing the magnetic moments of neighbouring atoms to align and the Mössbauer spectra becomes magnetically split (hyperfine sextuplets are observed) [2].

Fig. S8 shows the adsorption behavior of CO on carburized α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> catalysts determined by CO-TPD. The Mössbauer spectra results (Table 2) mentioned above indicate that carburization in syngas leads mainly to the formation of Fe<sub>3</sub>O<sub>4</sub> and Fe<sub>x</sub>C species. Therefore, the peaks of CO desorption at 380 and 440 °C can be attributed to the desorption of surface and/or near-surface C and O species on Fe<sub>3</sub>O<sub>4</sub> and Fe<sub>x</sub>C, respectively [6,33]. Furthermore, there was another CO desorption peak on Fe<sub>x</sub>C at 490 °C for α-Fe<sub>2</sub>O<sub>3</sub> sample, demonstrating multiple CO adsorption sites. Such a result possibly originated from the Fe<sub>5</sub>C<sub>2</sub> and Fe<sub>3</sub>C mixing phase in carburized α-Fe<sub>2</sub>O<sub>3</sub> catalyst [34], as confirmed by Mössbauer spectra, XRD, and HRTEM results. Meanwhile, the amount of adsorbed CO on γ-Fe<sub>2</sub>O<sub>3</sub> sample was much larger than that on α-Fe<sub>2</sub>O<sub>3</sub>, showing the higher CO adsorption capacity on γ-Fe<sub>2</sub>O<sub>3</sub> catalyst.

The different phase transitions from iron oxides suggest that C-poor θ-Fe<sub>3</sub>C can preferentially form from α-Fe<sub>2</sub>O<sub>3</sub> phase. We speculate that the formation of C-rich iron carbides (γ-Fe<sub>5</sub>C<sub>2</sub>) on γ-Fe<sub>2</sub>O<sub>3</sub> instead of C-poor θ-Fe<sub>3</sub>C is due to the higher carburization ability of γ-Fe<sub>2</sub>O<sub>3</sub>. The ease of being carburization on γ-Fe<sub>2</sub>O<sub>3</sub> is due to a ready cleavage of Fe-O bond of an inverse spinel structure [35]. In contrast to γ-Fe<sub>2</sub>O<sub>3</sub>, FTS





**Fig. 4.** HRTEM of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> (a, c, e, g) and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> (b, d, f, h) nanorods after carburized (a–f) and after FTS reaction (g, h). Carburized conditions: 340 °C, 0.1 MPa, H<sub>2</sub>/CO = 1, W/F(CO + H<sub>2</sub> + Ar) = 2.5 g<sub>cat</sub>·h·mol<sup>-1</sup>. Reaction conditions: 320 °C, 1.0 MPa, H<sub>2</sub>/CO = 1, W/F(CO + H<sub>2</sub> + Ar) = 5 g<sub>cat</sub>·h·mol<sup>-1</sup>.

over  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> catalyst exhibited higher light olefins selectivity with much higher O/P ratio in products (Fig. 3c). This is consistent with earlier studies which revealing that  $\theta$ -Fe<sub>3</sub>C is responsible for the formation of light olefins [11,36], as it has relatively weak hydrogenation activity for unsaturated hydrocarbon [37].

Chemical and coordination environments of Fe in precursors and carburized/spent state were studied with *in situ* manner as reported [14,38]. The nonphase corrected,  $k^2$  or  $k^3$  weighted Fourier transformed Fe K-edge EXAFS spectra for the fresh, carburized, and spent catalysts are shown in Figs. 6 and 7a. As shown in Fig. 6, the fresh  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> catalyst shows three distinct scattering peaks (1.45, 2.55, and 3.16 Å), characteristics of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> or  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> [12]. After carburized/reaction, a new peak at  $\sim 2.00$  Å (value before phase correction, the same in the following) appeared, which is contributed from the first shell of Fe-(C)-Fe structure of iron carbides [8,12]. In addition, the different shape and broadening of the shell at 1.45 Å for carburized

catalysts indicate that iron oxide and iron carbide species coexist, as both Fe-C and Fe-O bonds affect this peak. As reported in literature [9–13],  $\theta$ -Fe<sub>3</sub>C and  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> can be distinguished with the fact that the first distance of Fe and C in Fe-(C)-Fe structure of  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> is longer than that of  $\theta$ -Fe<sub>3</sub>C, since the Fe lattice of  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> has to expand to accommodate more C atoms than carbon-poor  $\theta$ -Fe<sub>3</sub>C. Reference samples  $\theta$ -Fe<sub>3</sub>C and  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> was synthesized by wet-chemical route and *in situ* carbonization of hematite, respectively (Figs. S9–10); the r-space spectrum of  $\theta$ -Fe<sub>3</sub>C and  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> were presented in Fig. S11. The peak center of the Fe-Fe shell of  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> is 2.16 Å, while it is 1.97 Å for  $\theta$ -Fe<sub>3</sub>C. For the carburized/spent  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> catalyst, it is proposed that the shorter Fe-Fe shell of iron carbides (Figs. 6 and 7a and Table 4) is contributed by the coexistence of  $\theta$ -Fe<sub>3</sub>C and  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> carbide phase, as also confirmed by XRD, HRTEM, and Mössbauer spectra.




Fig. 5. Mössbauer spectra of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> based nanorods catalysts after 20 h reaction.

### 3.2. Correlation between original iron oxide structure and Mn promotion effect

Mn is one of the main elements, which promote catalytic selectivity of olefins in FTS. Hence, we further explored Mn-modulated iron oxide nanorods catalysts by impregnation method (Fig. S12) to improve FTS catalytic performance. Our catalysis studies of Mn/ $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> and Mn/ $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> showed that  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> and  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> responded to the promotion of Mn to light olefins selectivity distinctly differently (Fig. 3 and Table 1). In the case of 0.5 Mn/ $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>, addition of Mn to  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> results the increase of light olefins selectivity from 25.4% to 61.2%, while the conversion of CO slightly decreased. Olefin/paraffin ratio for C<sub>2</sub>-C<sub>4</sub> (O/P) is another important parameter for evaluate the extent of olefin secondary reaction to paraffins. In terms of 0.5 Mn/ $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>, it also exhibits much higher O/P ratio (O/P = 6.88) than nonpromoted  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> catalyst (O/P = 1.09). Different from the significant promotion of Mn on  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> catalysts, the improvement of light olefins selectivity is not significant for Mn-modulated  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> catalysts. Upon loading 0.5 wt. % Mn to  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub>, the selectivity for light olefins only increased from 44.5% to 51.6%, while CO conversion decreased from 56.1% to 30.8%. The Mössbauer spectra results (Tables 2 and 3) show that the Mn-promoted  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> samples exhibit much lower total carbides contents after reduction/reaction compared to non-promoted catalyst, and lower degree of carburization for Mn-promoted  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> catalysts could directly result in relatively lower catalytic activities. Table S1 shows LCF results of spent catalysts from XANES spectra. The contents of iron carbides fitted from XANES are consistent with the Mössbauer spectra results.

The CO<sub>2</sub> selectivity was defined as the percentage of CO that is converted to CO<sub>2</sub> in the total consumed CO. As seen in Table 1, the CO<sub>2</sub> selectivity of all catalysts was proportional to the FTS reaction activity. All  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> based catalysts exhibited higher CO<sub>2</sub> selectivity than  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> based catalysts. This can be ascribed to the increased concentration of H<sub>2</sub>O at higher CO conversion, which was believed to bring

Table 3

Mössbauer parameters of the spent catalysts after 20 h on stream at T = 320 °C, P = 1 MPa and H<sub>2</sub>/CO ratio of 1.

| Catalysts                                        | Phases                         | Mössbauer parameters <sup>a</sup> |           |           |                       |
|--------------------------------------------------|--------------------------------|-----------------------------------|-----------|-----------|-----------------------|
|                                                  |                                | IS (mm/s)                         | QS (mm/s) | Hhf (kOe) | Area <sup>b</sup> (%) |
| $\alpha$ -Fe <sub>2</sub> O <sub>3</sub>         | Fe <sub>3</sub> C <sub>2</sub> | 0.24                              | 0.63      | 218       | 8.9                   |
|                                                  |                                | 0.30                              | 0.36      | 191       | 8.9                   |
|                                                  |                                | 0.29                              | 0.73      | 123       | 4.5                   |
|                                                  | Fe <sub>3</sub> C              | 0                                 | -0.64     | 207       | 7.2                   |
|                                                  |                                | 0.17                              | -0.29     | 208       | 3.6                   |
| $\gamma$ -Fe <sub>2</sub> O <sub>3</sub>         | Fe <sub>3</sub> O <sub>4</sub> | 0.35                              | -0.04     | 487       | 27.8                  |
|                                                  |                                | 0.70                              | -0.11     | 441       | 20.5                  |
|                                                  | Fe <sup>3+</sup> (spm)         | 0.19                              | -1.45     |           | 8.1                   |
|                                                  |                                | 0.84                              | 1.23      |           | 10.5                  |
|                                                  | Fe <sup>2+</sup> (spm)         | 0.28                              | 0.65      | 225       | 14.1                  |
|                                                  |                                | 0.11                              | 0.65      | 189       | 14.1                  |
|                                                  | Fe <sub>3</sub> O <sub>4</sub> | 0.19                              | 0.62      | 114       | 5.8                   |
|                                                  |                                | 0.34                              | -0.12     | 519       | 27.5                  |
|                                                  | Fe <sup>3+</sup> (spm)         | 0.33                              | -0.13     | 450       | 26.5                  |
|                                                  |                                | 0.20                              | -0.67     |           | 6.4                   |
| 0.5 Mn/ $\alpha$ -Fe <sub>2</sub> O <sub>3</sub> | Fe <sup>2+</sup> (spm)         | 0.81                              | -1.10     |           | 5.6                   |
|                                                  |                                | 0.12                              | 0.69      | 224       | 8.9                   |
|                                                  | Fe <sub>3</sub> C <sub>2</sub> | 0.40                              | -0.18     | 191       | 8.9                   |
|                                                  |                                | 0.26                              | -0.54     | 111       | 4.4                   |
|                                                  | Fe <sub>3</sub> C              | 0                                 | -0.80     | 206       | 2.7                   |
|                                                  |                                | 0                                 | -0.80     | 204       | 1.3                   |
|                                                  | Fe <sub>3</sub> O <sub>4</sub> | 0.40                              | 0.01      | 485       | 26.3                  |
|                                                  |                                | 0.57                              | 0.15      | 443       | 16.6                  |
|                                                  | Fe <sup>3+</sup> (spm)         | 0.40                              | 1.13      |           | 11.4                  |
|                                                  |                                | 0.84                              | 0.87      |           | 19.5                  |
| 0.5 Mn/ $\gamma$ -Fe <sub>2</sub> O <sub>3</sub> | Fe <sub>3</sub> C <sub>2</sub> | 0.22                              | -0.70     | 214       | 12.6                  |
|                                                  |                                | 0.21                              | -0.61     | 180       | 12.6                  |
|                                                  | Fe <sub>3</sub> C              | 0.09                              | 0.37      | 124       | 6.3                   |
|                                                  |                                | 0.39                              | 0.80      | 206       | 16.5                  |
|                                                  | Fe <sub>3</sub> O <sub>4</sub> | 0                                 | 0.33      | 208       | 8.3                   |
|                                                  |                                | 0.25                              | -0.72     | 487       | 4.6                   |
|                                                  | Fe <sup>2+</sup> (spm)         | 0.43                              | 0.37      | 474       | 20.2                  |
|                                                  |                                | 0                                 | -1.29     |           | 8.7                   |
|                                                  | Fe <sup>3+</sup> (spm)         | 0.82                              | 1.27      |           | 10.2                  |
|                                                  |                                |                                   |           |           |                       |


<sup>a</sup> Measured at room temperature.

<sup>b</sup> Max error =  $\pm$  1%.

about the intensification of WGS (water-gas shift) reaction [12]. It has been reported that the WGS reaction activity could affect the hydrocarbon selectivity because the increased H<sub>2</sub>/CO ratio, leading to an increase in CH<sub>4</sub> selectivity and a decrease in longer hydrocarbon selectivity [39]. However, our present results suggested that there is no direct correlation between the CO<sub>2</sub> selectivity and the hydrocarbon selectivity, especially light olefins selectivity. This conclusion was also reported by other researchers [12,33].

In addition, further increase in the Mn concentration in the Mn/ $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> or Mn/ $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> catalyst both led to an increase in methane selectivity and decrease in light olefins selectivity (Fig. 3c). We proposed that the surface Fe<sub>x</sub>C sites of Mn/ $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> and Mn/ $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> can be partitioned into two types of ensembles: region of unpromoted sites that are not close to MnO<sub>x</sub> and region of promoted sites that are adjacent to MnO<sub>x</sub>. The volcano-like evolution of selectivity as a function of Mn loading suggests that the regions of promoted sites are the interfacial area of Fe<sub>x</sub>C<sub>y</sub> patch with MnO<sub>x</sub> clusters. This assignment is similar to the attribution of active site of WGS catalysis on Cu/CeO<sub>2</sub> to the interfacial area of Cu nanoparticles and CeO<sub>2</sub> [40–42]. At a relatively low loading (< 0.5 wt. %), the product selectivity increases along the fraction of the areas of ideal sites (Fe<sub>x</sub>C<sub>y</sub> patch with MnO<sub>x</sub> clusters); Further addition of promoter would begin to cover up the iron surface such that reaction performance would decrease simply by there being fewer active sites.

The observed distinct discrepancy in the promotion effect of Mn is expected from a different phase transition of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> to active phase in contrast to  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>. For the catalysts of Mn/ $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and Mn/ $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>



**Fig. 6.** The nonphase corrected,  $k^2$  weighted Fourier-transformed *in situ* EXAFS spectra at the Fe K-edge of the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> based catalysts after carburized. Dash lines denote reference samples of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>, solid lines denote experiment spectra of iron based catalysts, and dotted lines denote fitting curves. The carburized samples were *in situ* treated in syngas ( $H_2/CO = 1$ , 15 ml/min) at 340 °C for 2 h at 1 bar.


after carburized/reaction, both  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> and  $\theta$ -Fe<sub>3</sub>C were formed as shown in XRD (Figs. S4–S6) and HRTEM results (Fig. S13). More importantly, the fraction of  $\theta$ -Fe<sub>3</sub>C phase on carburized/spent catalysts of 0.5 Mn/ $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> is much higher than on 0.5 Mn/ $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> (Tables 2 and 3). Compared to the absence of  $\theta$ -Fe<sub>3</sub>C on pure  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> catalyst and its very low selectivity of olefins, addition of 0.5 wt. % Mn to  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> largely increased selectivity of light olefins, which clearly demonstrated the promotion effect of Mn on  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>. It should be noted that this positive promotion effect on the formation of  $\theta$ -Fe<sub>3</sub>C phase was only observed obviously in  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> based samples. In contrast, the addition of Mn on  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> suppresses the carburization ability and leads to a lower total Fe<sub>x</sub>C content (19.4% for carburized catalyst and 26.2% for spent catalyst) both in  $\chi$ -Fe<sub>5</sub>C<sub>2</sub> and  $\theta$ -Fe<sub>3</sub>C phase (Tables 2 and 3). The results of Fe K-edge XANES (Fig. S14) underline this negative effect by Mn on  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> based samples, as the limited Fe<sub>x</sub>C formation was observed in Mn/ $\alpha$ -Fe<sub>2</sub>O<sub>3</sub>. Similar results have also been reported in the literature which used  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> or Fe<sub>3</sub>O<sub>4</sub> [26,43]. Hence, we proposed

**Table 4**

Fe K-edge EXAFS fit results for the  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> nanorods materials after carburized.<sup>a</sup>

| Entry | Catalysts                                        | Shell     | CN              | R(Å)            | $\delta^2(\text{\AA}^{-2})$ |
|-------|--------------------------------------------------|-----------|-----------------|-----------------|-----------------------------|
| 1     | $\gamma$ -Fe <sub>2</sub> O <sub>3</sub>         | Fe-O(C)   | $5.03 \pm 0.93$ | $1.98 \pm 0.02$ | 0.0172                      |
|       |                                                  | Fe-(C)-Fe | $4.89 \pm 1.81$ | $2.77 \pm 0.02$ | 0.0149                      |
|       |                                                  | Fe-(O)-Fe | $6.64 \pm 2.26$ | $3.25 \pm 0.03$ | 0.0255                      |
| 2     | 0.5 Mn/ $\gamma$ -Fe <sub>2</sub> O <sub>3</sub> | Fe-O(C)   | $3.10 \pm 0.76$ | $1.98 \pm 0.03$ | 0.0118                      |
|       |                                                  | Fe-(C)-Fe | $1.32 \pm 0.98$ | $2.57 \pm 0.05$ | 0.0096                      |
|       |                                                  | Fe-(O)-Fe | $4.22 \pm 1.82$ | $3.11 \pm 0.03$ | 0.0144                      |
| 3     | $\alpha$ -Fe <sub>2</sub> O <sub>3</sub>         | Fe-O(C)   | $3.54 \pm 0.99$ | $2.01 \pm 0.04$ | 0.0122                      |
|       |                                                  | Fe-(C)-Fe | $0.44 \pm 0.65$ | $2.68 \pm 0.02$ | 0.0122                      |
|       |                                                  | Fe-(O)-Fe | $4.48 \pm 2.05$ | $3.20 \pm 0.01$ | 0.0122                      |
| 4     | 0.5 Mn/ $\alpha$ -Fe <sub>2</sub> O <sub>3</sub> | Fe-O(C)   | $3.58 \pm 0.99$ | $2.01 \pm 0.03$ | 0.0034                      |
|       |                                                  | Fe-(C)-Fe | $1.01 \pm 0.66$ | $2.71 \pm 0.05$ | 0.0034                      |
|       |                                                  | Fe-(O)-Fe | $1.60 \pm 1.00$ | $3.21 \pm 0.05$ | 0.0034                      |

<sup>a</sup> The catalysts were pre-carburized at 340 °C, 0.1 MPa for 10 h using syngas ( $H_2/CO = 1$ ).



**Fig. 7.** a) The nonphase corrected,  $k^3$  weighted Fourier-transformed *in situ* EXAFS spectra at the Mn K-edge of the 0.5 Mn/ $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and 0.5 Mn/ $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> based catalysts after reaction. Dash lines denote reference samples of  $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>, and solid lines denote experiment spectra of iron based catalysts. b) The nonphase corrected,  $k^3$  weighted Fourier-transformed *in situ* EXAFS spectra at the Mn K-edge of the 0.5 Mn/ $\alpha$ -Fe<sub>2</sub>O<sub>3</sub> and 0.5 Mn/ $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> nanorods catalysts after carburized. The carburized and spent samples were *in situ* treated in syngas ( $H_2/CO = 1$ , 15 ml/min) at 340 °C for 2 h at 1 bar.



**Table 5**  
Catalytic activity and product selectivity of various iron-based catalysts at similar CO conversion.<sup>a</sup>


| Entry | Catalysts                               | W/F(CO + H <sub>2</sub> + Ar) (g <sub>cat</sub> h mol <sup>-1</sup> ) | FTY (10 <sup>-5</sup> mol CO g <sub>Fe</sub> <sup>-1</sup> s <sup>-1</sup> ) | CO <sub>2</sub> (%CO conv.) | Hydrocarbon selectivity (c-mol %, CO <sub>2</sub> -free) |                  |                  |                 | O/P  | Exit H <sub>2</sub> /CO molar ratio |
|-------|-----------------------------------------|-----------------------------------------------------------------------|------------------------------------------------------------------------------|-----------------------------|----------------------------------------------------------|------------------|------------------|-----------------|------|-------------------------------------|
|       |                                         |                                                                       |                                                                              |                             | CH <sub>4</sub>                                          | C <sub>2-4</sub> | C <sub>2-4</sub> | C <sub>5+</sub> |      |                                     |
| 1     | γ-Fe <sub>2</sub> O <sub>3</sub>        | 4.34                                                                  | 2.98                                                                         | 38.2                        | 21.4                                                     | 24.8             | 25.2             | 28.6            | 0.98 | 1.47                                |
| 2     | 0.5 Mn/γ-Fe <sub>2</sub> O <sub>3</sub> | 5.83                                                                  | 2.31                                                                         | 36.8                        | 10.9                                                     | 58.4             | 9.5              | 21.2            | 6.15 | 1.28                                |
| 3     | α-Fe <sub>2</sub> O <sub>3</sub>        | 6.02                                                                  | 2.22                                                                         | 35.9                        | 14.9                                                     | 41.6             | 10.7             | 32.8            | 3.89 | 1.33                                |
| 4     | 0.5 Mn/α-Fe <sub>2</sub> O <sub>3</sub> | 10.9                                                                  | 1.25                                                                         | 37.1                        | 13.7                                                     | 36.7             | 14.6             | 35              | 2.51 | 1.45                                |

<sup>a</sup> Reaction condition: 0.2 g catalyst, 320 °C, 1.0 MPa, H<sub>2</sub>/CO = 1, time on stream 20 h. Data were reported at CO conversion levels between 63% and 68%, and were taken at 20 h of time on stream.

that the slightly higher light olefins selectivity of 0.5 Mn/α-Fe<sub>2</sub>O<sub>3</sub> catalyst was caused by the much lower hydrogenation capacity (CO Conv. 29.4%) than nonpromoted α-Fe<sub>2</sub>O<sub>3</sub> catalyst (CO Conv. 52.7%). To confirm this speculation, additional tests were carried out at 1 MPa, 320 °C, and an H<sub>2</sub>/CO ratio of 1 to compare the products selectivity of catalysts at similar CO conversion levels (63–68 %, Table 5). As expected, the 0.5 Mn/α-Fe<sub>2</sub>O<sub>3</sub> catalyst only achieved a light olefins selectivity of 36.7%, which is lower than nonpromoted α-Fe<sub>2</sub>O<sub>3</sub> catalyst (41.6%). Meanwhile, the CO<sub>2</sub> selectivity for all the samples was approximately 35–39 % on the basis of CO converted. Since the CO conversion and CO<sub>2</sub> selectivity of four catalysts is at a comparative level, this leads to the little difference in exit molar H<sub>2</sub>/CO ratio at a range from 1.28 to 1.47.


When Mn modified, Fig. 6b shows that the first Fe-(C)-Fe shell distance of 0.5 Mn/γ-Fe<sub>2</sub>O<sub>3</sub> after carburized is much shorter (1.98 Å, uncorrected) than γ-Fe<sub>2</sub>O<sub>3</sub>, due to the contributions from θ-Fe<sub>3</sub>C (21.0% in Mössbauer spectroscopy). The CNs of Fe-C(O) and Fe-Fe in the iron carbide are 3.10 and 1.32, respectively (Table 4). In contrast, for the carburized 0.5 Mn/α-Fe<sub>2</sub>O<sub>3</sub> catalyst, the first Fe-(C)-Fe shell distance in iron carbides is similar to the unpromoted α-Fe<sub>2</sub>O<sub>3</sub> catalyst, verifying that Mn had no promotion effect toward formation of θ-Fe<sub>3</sub>C from α-Fe<sub>2</sub>O<sub>3</sub>. More importantly, the fitting results (Table 4) show that the Fe-Fe bond length in 0.5 Mn/γ-Fe<sub>2</sub>O<sub>3</sub> is even shorter (2.57 Å) than in 0.5 Mn/α-Fe<sub>2</sub>O<sub>3</sub> (2.71 Å), due to the higher proportion of θ-Fe<sub>3</sub>C. Since *k*<sup>3</sup>-weighted *r*-space spectrum is more sensitive in the high *Z* element signal contribution at high *k* value [44], here the *k*<sup>3</sup>-weighted spectra are also summarized in Fig. S15 for a better comparison. And the differences between *r*-space spectra in *k*<sup>2</sup>-weighted spectra remain in the *k*<sup>3</sup>-weighted spectra.

Based on the above results, we proposed that the formation of surface iron species was influenced by Mn at different degrees on α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> nanorods, which leads to the different product selectivity especially for light olefins. To probe the surface electronic character evolution of Fe catalysts during FTS reaction, the *in situ* synchrotron radiation XPS features in Fe 2p and Mn 2p region were monitored for all catalysts (Fig. 8). The catalysts were treated in syngas (H<sub>2</sub>/CO = 1) at 340 °C for 2 h at 1 bar, after treatment the samples were transferred to the measurement chamber without exposure to air. For the fresh sample, all catalysts show a characteristic Fe<sup>3+</sup> and Mn<sup>3+</sup> 2p<sub>3/2</sub> peak at ~711.0 eV and ~641.6 eV, respectively [45,46]. Meanwhile, Mn promoted γ-Fe<sub>2</sub>O<sub>3</sub> samples (Fig. 8a) possess a lower binding energy of Fe than the corresponding nonpromoted samples (γ-Fe<sub>2</sub>O<sub>3</sub>) and Mn/α-Fe<sub>2</sub>O<sub>3</sub> (Fig. 8a), demonstrating the presence of significant Fe-Mn interaction in this unique catalyst structure [47,48], i.e., MnO<sub>x</sub> supported on nonporous γ-Fe<sub>2</sub>O<sub>3</sub> nanorods without any other inert supports. Moreover, it has been reported that γ-Fe<sub>2</sub>O<sub>3</sub> has an inverse spinel structure with cation vacancies, which may adsorb metal to form some special/stronger interaction [18]. Hence, we proposed that MnO<sub>x</sub> species locate on the surface of γ-Fe<sub>2</sub>O<sub>3</sub> nanorods and form strong interaction with clear metal-promoter interfaces and close proximity to Fe. The extended X-ray absorption fine structure (EXAFS) studies clarified that the MnO<sub>x</sub> on γ-Fe<sub>2</sub>O<sub>3</sub> nanorods possessed less Mn-Mn



**Fig. 8.** The *in situ* synchrotron radiation XPS spectra of Fe 2p (a) and Mn 2p (b) for fresh and spent catalysts. All spent samples were *in situ* treated in syngas (H<sub>2</sub>/CO = 1, 15 ml/min) at 340 °C for 2 h at 1 bar.

coordination than on the corresponding α-Fe<sub>2</sub>O<sub>3</sub> nanorods as prepared and after carburized (Fig. 7b), suggesting the Mn/γ-Fe<sub>2</sub>O<sub>3</sub> nanorods catalyst had more Mn edge sites [49] due to the strong Fe-Mn




**Fig. 9.** a) *in situ* X-ray absorption near edge spectra (XANES) at Mn K-edge of 0.5 Mn/γ-Fe<sub>2</sub>O<sub>3</sub> nanorods catalysts as-prepared, after carburized, and after reaction, in comparison with references for MnO<sub>2</sub>, MnO, and Mn<sub>3</sub>O<sub>4</sub>. All the pre-carburized catalysts were carburized again *in situ* in syngas (CO/H<sub>2</sub> = 1) at 340 °C for 1 h; b) Correlation between XANES absorption edge position of Mn K-edge and oxidation state of Mn in 0.5 Mn/γ-Fe<sub>2</sub>O<sub>3</sub> samples as prepared, after carburized and after reaction.

interaction.

After reduction, the peaks in Fe 2p and Mn 2p regions both shifted toward lower binding energies that correspond to the formation of Fe<sup>2+</sup> and Mn<sup>2+</sup> species [50,51]. Furthermore, the Mn 2p peaks of Mn/γ-Fe<sub>2</sub>O<sub>3</sub> possess a more reduced state of Mn compared with Mn/α-Fe<sub>2</sub>O<sub>3</sub> sample (Fig. 8b). Among them 0.5 Mn/γ-Fe<sub>2</sub>O<sub>3</sub> exhibited lowest binding energy, which is more than 0.5 eV lower (640.4 vs. 640.9 eV). This result suggests that more reduced MnO<sub>1-x</sub> species was formed on γ-Fe<sub>2</sub>O<sub>3</sub> supported samples. It is proposed that the interfacial MnO<sub>x</sub> with more low-coordinated edge sites might be more easily reduced by syngas, due to the higher intrinsic reactivity on edge sites [52–54] and interfacial spillover effect [8].

The normalized Mn K-edge X-ray absorption near-edge structure (XANES) for 0.5 Mn/γ-Fe<sub>2</sub>O<sub>3</sub> and 0.5 Mn/α-Fe<sub>2</sub>O<sub>3</sub> samples as prepared, after carburized and after reaction was further performed Figs. 9 and 10). It can be seen that the Mn oxidation state of fresh samples was both Mn<sup>3+</sup>, which is evidenced by the absorption edge position of Mn K-edge (Fig. 9b). The shift of the absorption edge toward energies closer to Mn<sup>2+</sup> (MnO reference) edge (6549 eV) after reduction show that Mn is further reduced during carbonization process, and the same absorption edge after reaction suggests that it maintained stable valence under catalytic conditions. Furthermore, Mn absorption edge in 0.5 Mn/γ-Fe<sub>2</sub>O<sub>3</sub> after carburized at 340 °C is at lower energy than that of pure MnO reference, which further confirmed that Mn species is presents as a more reduced chemical state than a pure MnO [8].

Iron carbides are classified as interstitial carbides [55], in which carbon atoms are placed in available interstitial sites of Fe<sup>0</sup> atoms. The



**Fig. 10.** *In situ* XANES at Mn K-edge of 0.5 Mn/α-Fe<sub>2</sub>O<sub>3</sub> nanorods catalysts as-prepared, after carburized, and after reaction, in comparison with references for MnO<sub>2</sub>, MnO, and Mn<sub>3</sub>O<sub>4</sub>. All the pre-carburized catalysts were carburized again *in situ* in syngas (CO/H<sub>2</sub> = 1) at 340 °C for 1 h.

present studies indicate that the presence of strong Fe-Mn interaction suppress diffusion of C atoms into the lattice of Fe oxide such that C-poor phases (cementite) emerge for Mn/γ-Fe<sub>2</sub>O<sub>3</sub> catalysts. The *r*-space structural parameters (Table 4) show that the Fe-(O)-Fe bond length shrinks in 0.5 Mn/γ-Fe<sub>2</sub>O<sub>3</sub> (3.11 Å) compared to that of γ-Fe<sub>2</sub>O<sub>3</sub> (3.25 Å). We believe that it originates from the lattice distortion in the surface Fe layers [56] at interfacial boundary of Fe<sub>x</sub>O<sub>y</sub>-MnO<sub>x</sub>, which strong interact with MnO<sub>1-x</sub>. Hence, the incorporation of carbon to iron lattices will be suppressed, due to the kinetic factors limitation [10,14]. As a result, the formation of θ-Fe<sub>3</sub>C phase which have weak hydrogenation activity for unsaturated hydrocarbon was promoted. Meanwhile, the special morphology structure of catalyst (promoter locate on nonporous iron oxide nanorods) would reduce the diffusion resistance of products, especially for light olefins. Hence, the selectivity of light olefins on Mn/γ-Fe<sub>2</sub>O<sub>3</sub> catalysts was improved dramatically. For Mn/α-Fe<sub>2</sub>O<sub>3</sub> catalysts, selectivity of light olefins increased only slightly. This little improvement can be ascribed to the lower hydrogenation capacity (*i.e.* FTS activity) on Mn-modulated α-Fe<sub>2</sub>O<sub>3</sub> catalyst, as the total Fe<sub>x</sub>C content was decreased (from 25.1% to 19.4%, Table 2).

#### 4. Conclusion

Correlation among the original phase of iron oxide and the corresponding catalytic performance is crucial for designing a catalyst with high selectivity in STO reaction. Pure α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> form quite different iron carbides and thus exhibit different catalytic selectivity for light olefins. By loading Mn on the surface of Fe<sub>2</sub>O<sub>3</sub>, light olefins selectivity was largely promoted on γ-Fe<sub>2</sub>O<sub>3</sub> but not on α-Fe<sub>2</sub>O<sub>3</sub>. This difference in promoting catalytic selectivity is closely related to structure of original iron oxide crystal structure and formation of iron carbides. Fundamental understanding of the intrinsic correlation between original oxide structure and the formation of iron carbide and promotion effect of Mn was achieved through *in situ* and *ex situ* characterizations.

In summary, with the goal of understanding the effects of initial iron oxide crystal phase on the active phase and controlling FTS performance, we prepared α-Fe<sub>2</sub>O<sub>3</sub> and γ-Fe<sub>2</sub>O<sub>3</sub> nonporous nanorods to explore the iron phase evolution during FTS, which can avoid the influence of diffusion limitation on the selectivity during the FTS reaction. Our studies reveal that the formation of high selective iron carbides (θ-Fe<sub>3</sub>C) to light olefins was affected by initial iron oxide crystal phase. The more reduced MnO<sub>1-x</sub> edge sites with strong Fe-Mn interaction was preferentially formed on the surface of γ-Fe<sub>2</sub>O<sub>3</sub> nanorods, which was beneficial to the formation of C-poor iron carbides phase (θ-Fe<sub>3</sub>C). Consequently, due to the morphology effect (promoter locate on

nonporous nanorods) and crystal phase effect ( $\gamma$ -Fe<sub>2</sub>O<sub>3</sub>), Mn-modulated  $\gamma$ -Fe<sub>2</sub>O<sub>3</sub> nanorods catalysts can achieve light olefins selectivity of up to 50.1–61.2 % with more than 50% of CO single-pass conversion under industrially relevant conditions. This catalyst exhibits high stability for at least 50 h on stream.

## Declaration of Competing Interest

The authors declare no competing financial interest.

## Acknowledgments

This work was supported by National Natural Science Foundation of P. R. China (91334206, 21606011), and China Postdoctoral Science Foundation (2016M591051 and 2017T100029). This work was also supported by the Beijing Synchrotron Radiation Facility (BSRF), National Synchrotron Radiation Laboratory (NSRL) of China, and Synfuels China Technology Co., Ltd.

## Appendix A. Supplementary data

Supplementary material related to this article can be found, in the online version, at doi:<https://doi.org/10.1016/j.apcatb.2019.118219>.

## References

- [1] L.S. Zhong, F. Yu, Y.L. An, Y.H. Zhao, Y.H. Sun, Z.J. Li, T.J. Lin, Y.J. Lin, X.Z. Qi, Y.Y. Dai, L. Gu, J.S. Hu, S.F. Jin, Q. Shen, H. Wang, *Nature* 538 (2016) 84–87.
- [2] H.M.T. Galvis, J.H. Bitter, C.B. Khare, M. Ruitenbeek, A.I. Dugulan, K.P. de Jong, *Science* 335 (2012) 835–838.
- [3] P. Zhai, C. Xu, R. Gao, X. Liu, M. Li, W. Li, X. Fu, C. Jia, J. Xie, M. Zhao, X. Wang, Y.W. Li, Q.W. Zhang, X.D. Wen, D. Ma, *Angew. Chem. Int. Ed.* 55 (2016) 9902–9907.
- [4] Y. Cheng, J. Lin, K. Xu, H. Wang, X. Yao, Y. Pei, S. Yan, M.H. Qiao, B.N. Zong, *ACS Catal.* 6 (2016) 389–399.
- [5] S. Zhao, X.W. Liu, C.F. Huo, Y.W. Li, J. Wang, H. Jiao, *Catal. Struct. React.* 1 (2015) 44–59.
- [6] M. Ding, Y. Yang, B. Wu, Y. Li, T. Wang, L. Ma, *Appl. Energy* 160 (2015) 982–989.
- [7] Y. Wei, C. Zhang, X. Liu, Y. Wang, Q. Chang, M. Qing, X. Wen, Y. Yang, Y.W. Li, *Catal. Sci. Technol.* 8 (2018) 1113–1125.
- [8] M.C. Ribeiro, G. Jacobs, R. Pendyala, B.H. Davis, D.C. Cronauer, A.J. Kropf, C.L. Marshall, *J. Phys. Chem. C* 115 (2011) 4783–4792.
- [9] E. de Smit, A.M. Beale, S. Nikitenko, B.M. Weckhuysen, *J. Catal.* 262 (2009) 244–256.
- [10] K. Xu, B. Sun, J. Lin, W. Wen, Y. Pei, S. Yan, M. Qiao, X. Zhang, B. Zong, *Nat. Commun.* 5 (2014) 5783.
- [11] Y. Liu, J.F. Chen, J. Bao, Y. Zhang, *ACS Catal.* 5 (2015) 3905–3909.
- [12] Q. Chang, C. Zhang, C. Liu, Y. Wei, A.V. Cheruvathur, A. Iulian Dugulan, J.W. Niemantsverdriet, X. Liu, Y. He, M. Qing, L. Zheng, Y. Yun, Y. Yang, Y.W. Li, *ACS Catal.* 8 (2018) 3304–3316.
- [13] P. Wang, W. Chen, F.K. Chiang, A.I. Dugulan, Y. Song, R. Pestman, K. Zhang, J. Yao, B. Feng, P. Miao, W. Xu, E.J.M. Hensen, *Sci. Adv.* 4 (2018) eaau2947.
- [14] E. de Smit, F. Cinquini, A.M. Beale, O.V. Safonova, W. van Beek, P. Sautet, B.M. Weckhuysen, *J. Am. Chem. Soc.* 132 (2010) 14928–14941.
- [15] E. de Smit, B.M. Weckhuysen, *Chem. Soc. Rev.* 37 (2008) 2758–2781.
- [16] G.B. Yu, B. Sun, Y. Pei, S. Xie, S. Yan, M. Qiao, K. Fan, X. Zhang, B. Zong, *J. Am. Chem. Soc.* 132 (2010) 935–937.
- [17] S.Z. Li, W.P. Ding, G.D. Meitzner, E. Iglesia, *J. Phys. Chem. B* 106 (2002) 85–91.
- [18] K. Zhao, H. Tang, B. Qiao, L. Li, J. Wang, *ACS Catal.* 5 (2015) 3528–3539.
- [19] W. Ning, T. Wang, H. Chen, X. Yang, Y. Jin, *PLoS One* 12 (2017) e0182955.
- [20] K.M. Kreitman, M. Baerns, J.B. Butt, *J. Catal.* 105 (1987) 319–334.
- [21] J. Venter, M. Kaminsky, G.L. Geoffroy, M.A. Vannice, *J. Catal.* 103 (1987) 450–465.
- [22] B. Qiao, A. Wang, J. Lin, L. Li, D. Su, T. Zhang, *Appl. Catal. B* 105 (2011) 103–110.
- [23] B. Qiao, Y. Deng, *Appl. Catal. B* 66 (2006) 241–248.
- [24] B. Qiao, L. Liu, J. Zhang, Y. Deng, *J. Catal.* 261 (2009) 241–244.
- [25] G.C. Maiti, R. Malessa, M. Baerns, *Appl. Catal.* 5 (1983) 151–170.
- [26] J.D. Xu, K.T. Zhu, X.F. Weng, W.Z. Weng, C.J. Huang, H.L. Wan, *Catal. Today* 215 (2013) 86–94.
- [27] G.C. Maiti, R. Malessa, U. Löchner, H. Papp, M. Baerns, *Appl. Catal.* 16 (1985) 215–225.
- [28] X. Mou, B. Zhang, Y. Li, L. Yao, X. Wei, D.S. Su, W. Shen, *Angew. Chem. Int. Ed.* 51 (2012) 2989–2993.
- [29] Z. Schniepp, S.C. Wimbush, M. Antonietti, C. Giordano, *Chem. Mater.* 22 (2010) 5340–5344.
- [30] B. Ravel, M. Newville, *J. Synchrotron Radiat.* 12 (2005) 537–541.
- [31] M.A. Legodi, D. de Waal, *Dyes Pigments* 74 (2007) 161–168.
- [32] F.J. Pérez-Alonso, T. Herranz, S. Rojas, M. Ojeda, M. López Granados, P. Terreros, J.L.G. Fierro, M. Graciani, J.R. Gancedo, *Green Chem.* 9 (2007) 663–670.
- [33] H. Suo, S. Wang, C. Zhang, J. Xu, B. Wu, Y. Yang, H. Xiang, Y.W. Li, *J. Catal.* 286 (2012) 111–123.
- [34] J. Zhang, T. Sun, J. Ding, H. Xiao, F. Kong, J. Chen, *RSC Adv.* 6 (2016) 60349–60354.
- [35] J.W. Long, M.S. Logan, C.P. Rhodes, E.E. Carpenter, R.M. Stroud, D.R. Rolison, *J. Am. Chem. Soc.* 126 (2004) 16879–16889.
- [36] T. Qiu, L. Wang, S. Lv, B. Sun, Y. Zhang, Z. Liu, W. Yang, J. Li, *Fuel* 203 (2017) 811–816.
- [37] C.F. Huo, Y.W. Li, J. Wang, H.J. Jiao, *Am. Chem. Soc.* 131 (2009) 14713–14721.
- [38] G.R. Johnson, S. Werner, A.T. Bell, *ACS Catal.* 5 (2015) 5888–5903.
- [39] B.H. Davis, *Ind. Eng. Chem. Res.* 46 (2007) 8938–8945.
- [40] J. Graciani, K. Mudiyanse, F. Xu, A.E. Baber, J. Evans, S.D. Senanayake, D.J. Stacchiola, P. Liu, J. Hrbek, J.F. Sanz, J.A. Rodriguez, *Science* 345 (2014) 546–550.
- [41] J.B. Park, J. Graciani, J. Evans, D. Stacchiola, S.D. Senanayake, L. Barrio, P. Liu, J.F. Sanz, J. Hrbek, J.A. Rodriguez, *J. Am. Chem. Soc.* 132 (2010) 356–363.
- [42] J.A. Rodriguez, P. Liu, J. Hrbek, J. Evans, M. Pérez, *Angew. Chem. Int. Ed.* 46 (2007) 1329–1332.
- [43] A. Campos, N. Lohitharn, A. Roy, E. Lotero, J.G. Goodwin Jr., J.J. Spivey, *Appl. Catal. A* 375 (2010) 12–16.
- [44] D. Koningsberger, B. Mojet, G. Van Dorssen, D. Ramaker, *Top. Catal.* 10 (2000) 143–155.
- [45] Y. Kou, B. Zhang, J. Niu, S. Li, H. Wang, T. Tanaka, S. Yoshida, *J. Catal.* 173 (1998) 399–408.
- [46] H. Cui, Y. Liu, W. Ren, *Adv. Powder Technol.* 24 (2013) 93–97.
- [47] S. Qin, C. Zhang, J. Xu, Y. Yang, H. Xiang, Y.W. Li, *Appl. Catal. A* 392 (2011) 118–126.
- [48] Y. Liu, W. Sheng, Z. Hou, Y. Zhang, *RSC Adv.* 8 (2018) 2123–2131.
- [49] S. Xie, Z. Shen, J. Deng, P. Guo, Q. Zhang, H. Zhang, C. Ma, Z. Jiang, J. Cheng, D. Deng, Y. Wang, *Nat. Commun.* 9 (2018) 1181.
- [50] R. Grissa, H. Martinez, S. Cotte, J. Galipaud, B. Pecquenard, F. Cras, *Appl. Surf. Sci.* 411 (2017) 449–456.
- [51] T. Yamashita, P. Hayes, *Appl. Surf. Sci.* 254 (2008) 2441–2449.
- [52] A.L.M. da Silva, J.P. den Breejen, L.V. Mattos, J.H. Bitter, K.P. de Jong, F.B. Noronha, *J. Catal.* 318 (2014) 67–74.
- [53] W. Chen, T.F. Kimpel, Y. Song, F.K. Chiang, B. Zijlstra, R. Pestman, P. Wang, E.J.M. Hensen, *ACS Catal.* 8 (2018) 1580–1590.
- [54] W. Chen, R. Pestman, F.K. Chiang, E.J.M. Hensen, *J. Catal.* 366 (2018) 107–114.
- [55] L.E. Toth, *Transition Metal Carbides and Nitrides*, Academic Press, New York, 1971.
- [56] J. Dong, Q. Fu, Z. Jiang, B. Mei, X. Bao, *J. Am. Chem. Soc.* 140 (2018) 13808–13816.



**Update**

**Applied Catalysis B: Environmental**

Volume 278, Issue , 5 December 2020, Page

DOI: <https://doi.org/10.1016/j.apcatb.2020.119287>



## Corrigendum

# Corrigendum to “Effects of initial crystal structure of $\text{Fe}_2\text{O}_3$ and Mn promoter on effective active phase for syngas to light olefin” [Appl. Catal. B: Environ. 261 (2020) 118219]




Yi Liu<sup>a</sup>, Fangxu Lu<sup>a</sup>, Yu Tang<sup>b</sup>, Minyang Liu<sup>a</sup>, Franklin Feng Tao<sup>b,\*</sup>, Yi Zhang<sup>a,\*</sup>

<sup>a</sup> State Key Laboratory of Organic-Inorganic Composites, Beijing University of Chemical Technology, 15 Beisanhuan East Road, Beijing 100029, PR China

<sup>b</sup> Department of Chemical and Petroleum Engineering, University of Kansas, Lawrence, KS 66045, USA

The authors regret to inform that the following error in the aforementioned article. The HRTEM image in Fig. 4b was incorrect. Fig. 4b should be corrected to



**Fig. 4.** HRTEM of  $\alpha\text{-Fe}_2\text{O}_3$  (a, c, e, g) and  $\gamma\text{-Fe}_2\text{O}_3$  (b, d, f, h) nanorods after carburized (a–f) and after FTS reaction (g, h). Carburized conditions: 340 °C, 0.1 MPa,  $\text{H}_2/\text{CO} = 1$ ,  $\text{W/F}(\text{CO} + \text{H}_2 + \text{Ar}) = 2.5 \text{ g}_{\text{cat}} \cdot \text{h} \cdot \text{mol}^{-1}$ . Reaction conditions: 320 °C, 1.0 MPa,  $\text{H}_2/\text{CO} = 1$ ,  $\text{W/F}(\text{CO} + \text{H}_2 + \text{Ar}) = 5 \text{ g}_{\text{cat}} \cdot \text{h} \cdot \text{mol}^{-1}$ .

Above correction do not change the overall results & discussion, and conclusion reported in the published article.

The authors would like to apologise for any inconvenience caused.

DOI of original article: <https://doi.org/10.1016/j.apcatb.2019.118219>

\* Corresponding authors.

E-mail addresses: [franklin.feng.tao@ku.edu](mailto:franklin.feng.tao@ku.edu) (F.F. Tao), [yizhang@mail.buct.edu.cn](mailto:yizhang@mail.buct.edu.cn) (Y. Zhang).

<https://doi.org/10.1016/j.apcatb.2020.119287>

Available online 09 July 2020

0926-3373/ © 2019 Elsevier B.V. All rights reserved.