

Thermal Field Products

Ping Zhou Consulting · European Distribution

Note:

Values are based on manufacturer specifications. Custom dimensions and tolerances on request. Contact Ping Zhou Consulting for quotations and delivery within Europe.

Hinweis: Werte basieren auf Herstellerangaben. Sondermaße und Toleranzen auf Anfrage. Für Angebote und Lieferungen in Europa wenden Sie sich an Ping Zhou Consulting

Integral Needle-Punched Solidified Felt (Graphit Felt)

Integrale nadelfixierte Festkohlefaser-Matte



Product Overview / Produktübersicht

Product / Produkt	Integral Needle-Punched Solidified Felt
Specification / Spezifikation	Standard size: 1500 mm × 1000 mm × 40 mm
Manufacturer / Hersteller	Made in China
EU Distributor / EU-Vertrieb	Ping Zhou Consulting, Germany
Application / Anwendung	Thermal field insulation for high-temperature industrial furnaces.
Anwendung (DE)	Wärmedämmung für Thermofelder in Hochtemperatur-Industrieöfen.

Technical Parameters / Technische Parameter

Parameter / Parameter	Unit / Einheit	Value / Wert
Density	g/cm ³	0.17-0.20
Carbon content	wt. %	> 99%
Ash content	ppm	≤300
Compressive strength	Mpa	≥2
Flexural strength	Mpa	≥1
Thermal conductivity (25 °C)	W/m·k	≤0.16
Processing temperature	°C	≥1800
Moisture absorption	%	< 1
Thickness	mm	5-200
Maximum service temperature (non-oxidizing atmosphere)	°C	≤3200
Thermal expansion coefficient	×10 ⁻⁶ /K	≤0.25 (0-1000°C) ≤0.4 (1000-2000°C)
Machining accuracy	mm	±2

*Processing temperature: Graphitization temperature >1800°C (in inert atmosphere/vacuum during manufacturing)

Carbon Cloth Laminated Carbon Plate (CFC Plate)

Kohlefaserstoff-laminierte Kohleplatte



Product Overview / Produktübersicht

Product / Produkt	Carbon Cloth Laminated Carbon Plate
Specification / Spezifikation	Standard size: 1000 mm × 1000 mm × 2 mm
Manufacturer / Hersteller	Made in China
EU Distributor / EU-Vertrieb	Ping Zhou Consulting, Germany
Application / Anwendung	Rigid carbon composite plate for thermal field and structural applications.
Anwendung (DE)	Starre Kohlenstoffverbundplatte für Thermofeld- und Strukturanwendungen.

Technical Parameters / Technische Parameter

Parameter / Parameter	Unit / Einheit	Value / Wert
Process	-	carbon cloth lamination
Density	g/cm ³	1.20-1.50
Carbon content	wt. %	≥99.5
Ash content	ppm	≤300
Compressive strength	Mpa	≥150
Flexural strength	Mpa	≥110
Thermal conductivity (25°C)	W/m·k	26 ± 3
Processing temperature*	°C	≥1800
Moisture absorption	%	< 1
Thickness	mm	1.0-50
Maximum service temperature (non-oxidizing atmosphere)	°C	≤3200
Thermal expansion coefficient	×10 ⁻⁶ /K	≤0.2 (0-1000°C) ≤0.3 (1000-2000°C)
Machining accuracy	mm	±1

*Processing temperature: Graphitization temperature >1800°C (in inert atmosphere/vacuum during manufacturing)

U-Shaped Carbon-Carbon Edge (CFC U-Profile)

U-förmige Kohlenstoff-Kohlenstoff-Kante



Product Overview / Produktübersicht

Product / Produkt	U-Shaped Carbon-Carbon Edge
Specification / Spezifikation	Standard size: 1000 mm × 1000 mm × 2 mm
Manufacturer / Hersteller	Made in China
EU Distributor / EU-Vertrieb	Ping Zhou Consulting, Germany
Application / Anwendung	Edge protection and thermal insulation component for furnace assemblies.
Anwendung (DE)	Kantenschutz- und Wärmedämmkomponente für Ofenbaugruppen.

Technical Parameters / Technische Parameter

Parameter / Parameter	Unit / Einheit	Value / Wert
Process	-	Carbon cloth lamination
Density	g/cm ³	1.20-1.40
Carbon content	wt. %	≥99.5
Ash content	ppm	≤300
Compressive strength	Mpa	≥120
Flexural strength	Mpa	≥100
Thermal conductivity (25°C)	W/m·K	≤30 ⊥ ≤5
Processing temperature*	°C	≥1800
Moisture absorption	%	< 1
Thickness	mm	1.0-2.0
Maximum service temperature (non-oxidizing atmosphere)	°C	≤3200
Thermal expansion coefficient	×10 ⁻⁶ /K	≤0.2 (0-1000°C) ≤0.3 (1000-2000°C)
Machining accuracy	mm	±1

*Processing temperature: Graphitization temperature >1800°C (in inert atmosphere/vacuum during manufacturing)