NOCTUO

PRODUCT CARD

Wood PLA Oak

1. GENERAL INFORMATION ABOUT THE PRODUCT

Wood PLA is a wood-like material, based on PLA with added wood fibers. It is very easy to print and can be used on most FDM 3D printers. It requires no experience or special primers. It emits a wood odor during printing.

Main Wood PLA features:

- easy to print,
- ready for use in almost any FDM 3D printer,
- wood smell during printing,
- unique, wood-like print structure,
- low temperature and chemical resistance.

2. TECHNICAL PARAMETERS

CHARACTERISTICS	TEST METHOD	TEST CONDITIONS	IU	VALUE
	ISO			
PHYSICAL				
Density	1183	-	g/cm^3	1.19
MECHANICAL				
Tensile strength	527	-	MPa	47
Breaking stress	527	-	MPa	34
Elongation at break	527	-	%	6
Modulus of elasticity	527	-	GPa	3.2
Charpy Impact Strength	179-1/1 eA	-	kJ/m^2	4,2
Charpy Impact Strength	179-1/1 eU	-	kJ/m^2	21

Tests have been done in 23°C, if it's not marked differently.

3. RECOMMENDATION OF PRINTING

PLA does not require drying before using. Satisfying results could be achieved by using standard settings for PLA in available slicers and printers.

Cooling during printing is recommended.

Recommended parameters of printing:

Hotend temperature	200 - 225 °C
Bed temperature	50 - 60 °C
Print speed	< 300 mm/s

4. SAFETY NOTES

Exhaust fan is recommended.
Air filters in printer is recommended.
PLA needs to be used only in well ventilated conditions.
Inhaling fumes generated during the printing must be avoided.

Generating fumes during the printing depends mainly on printing temperature. In case of visibly raising emission level, the printing needs to end. Check the hotend temperature and efficiency of the control system before using it next time.

In proper using conditions, the product doesn't endanger health.

It's forbidden to set fire or exceed decomposition temperature!

Decomposition of PLA is typically over 250 °C and it should be strictly avoided.
Main ingredient of decomposition is lactide.

Detailed safety information available in SDS.