

TECHNICAL DATA SHEET (TDS)

Product Name : Titanium Dioxide Rutile Grade ATR-312

Appearance : White Powder

Characters : Low impurity content, narrow particle size distribution of TiO_2 particles, even as well as compact coated membrane, high weather resistance, easy dispersion, high gloss and excellent scattering force.

MAIN TECHNICAL DATA:

PROPERTY	ATR-312
Process:	Rutile TiO_2 produced by sulfate process
TiO_2 content (%):	≥ 92.0
Rutile crystal content (%):	≥ 98.0
Relative tinting strength:	$\geq 110\%$
Matter soluble in water (%):	≤ 0.4
Water extracted PH:	6.5 ~ 8.5
Oil absorption (g/100g):	17 ~ 22
105°C loss (%):	≤ 0.5
Residue (45um):	$\leq 0.05\%$
Water extracted resistivity ($\Omega \cdot \text{M}$):	≥ 80
Inorganic Treatment:	Silica, Alumina
Organic Treatment	Yes

Disclaimer: The information contained herein is accurate and is based on the present state of our knowledge. Although reasonable care has been taken in the preparation of this document, we extend no warranties and make no representations as to the accuracy or completeness of the information contained herein, and assume no responsibility regarding the suitability of this information for the user's intended purposes or for the consequences of its use. Each individual should make a determination as to the suitability of the information for their particular purpose(s). All materials may present unknown hazards and should be used with caution. Although certain hazards are described herein, we cannot guarantee that these are the only hazards that exist.



TECHNICAL DATA SHEET

Product: TR-33, a general & multiple purpose white pigment, rutile grade, inorganically coated by Zirconium Oxide and Alumina compound, also specially treated by organic modifying, with good whiteness, good dispersion, hydrophylic and lipophylic.

Features: Good whiteness, excellent tint reducing power and opacity, good dispersion both in aqueous and oil systems, high durability, heat and light resistance.

Applications: Decorative paints (both interior and exterior), powder coatings, coil coatings, plastic, inks, general industrial coatings, paper, rubber and leather industries.

TECHNICAL SPECIFICATION:

PROPERTIES	PERFORMANCE
TiO ₂ content, %	94, min
Inorganic coating	Al ₂ O ₃ , ZrO ₂
Organic treatment	Present
CIE L*	97.5-99.9
Oil absorption, (g/100g pigment)	20, max
Residue on 45µm, %	0.03, max
Tint reducing power, TCS	1800, min
Dispersibility (Hegeman index)	5.00, min
Crystal size, µm	0.25
Specific resistance, Ω·m	80, min
pH	6.5-8.5
Durability	Moderate
Specific gravity, g/cm ³	4.0-4.2
Rutile content, %	95,min