

Number of casings tested at each aging temp:

(2) (3) (3) (3) (2)

Number of specimens tested at each aging temp:

(6) (12) (14) (13) (6)

Ti-6Al-4V, Cast

Cast compressor casing (See Figure 3.3.1.1 for casing (1/2 ins long) and specimen details. All casings from single heat. Casings solution treated 1760F, 1 hr, WQ; 1/2 in square specimen blanks aged 8 hrs (except 10 hrs at 800F), AC.




Figure 3.2.1.11 Effect of aging temperatures on tensile properties of three compressor casings cast from one heat (Ref. 4)