

Ti-6Al-4V, Cast
 Cast ring segment
 Annealed in full section: 1550F, 2 to 4 hrs in vacuum, AC.
 See Table 3.2.1.2 for ring segment and specimen (flat type) details.

Number of specimens tested at each test temperature:

Base	(A)			
Flange + Web	(B)			
(A)	5	38	6	6
(B)	6	49	5	5
	(-100F)	(RT)	(300F)	(600F)

Minimum of three rings total from two heats tested at each test temperature.

 Base

 Flange + Web

No directionality observed.




Figure 3.3.1.3 Effect of test temperatures on tensile properties of annealed cast ring segments from two heats (Ref. 5)