Autonomous Physical Characterization Report

Sample: 5nm Ag/Si Thin Film | Hardware: Ossila SMU (COM3)

Physical Parameter	Extracted Value
Baseline Resistance (2-Probe)	8.90e+04 Ω
SCLC Conduction Exponent (n)	1.00
Schottky/FN Barrier Height (Φb)	0.450 eV
Hysteresis Loop Area	0.00e+00 V·A
1/f Noise Spectral Density (Mean)	2.60e-10 A²/Hz

Scientific Characterization Curves:







