

Product Description

GFTP-600 LO Low Oil Gap Pad is a thermally conductive interface material engineered to deliver stable heat transfer between electronic components and heat sinks, while actively mitigating oil bleed to preserve interface integrity in contamination-sensitive environments.

Designed for high-reliability systems, GFTP-600 LO maintains consistent thermal impedance over time by minimizing silicone oil migration that can lead to pump-out, surface contamination, and performance degradation. This makes it well suited for dense electronic assemblies, power modules, and systems where long-term cleanliness and interface stability are critical.

The material combines a ceramic-filled silicone architecture with a controlled low-bleed formulation to achieve a balance of thermal performance, conformability, and mechanical compliance, enabling effective gap filling with low compression force while sustaining electrical insulation and durability under thermal cycling.

Key Features

- **Low oil bleed**
- Thermally conductive, electrically insulating
- Conformable for effective gap filling
- Low compression force for reduced stress
- Stable performance over wide temperatures
- Multiple thickness options for gap variation

Applications

- Heat sink attachment for electronic components
- Power electronics and power supply modules
- Telecommunications and networking systems
- Consumer and computing electronics
- Automotive electronic assemblies

Application Guidelines

- Avoid exposure to open flame and direct sunlight.
- Ensure application surfaces are clean.

Storage and Shelf Life

- Store at 8°C to 28°C in a dry environment (RH<70%).
- Shelf life is 12 months from the date of manufacture.

Packaging Information

- Available in thicknesses from 0.5 mm to 10.0 mm, with additional thicknesses available upon request
- Supplied in standard sheet formats and custom die-cut parts for specific application requirements
- Custom sizes and configurations supported to meet design and manufacturing needs

Property	Value	Test Method
Color	Gray	Visual
Hardness (Shore 00)	50	ASTM D2240
Thermal Conductivity (W/(m·K))	6.0	ASTM D5470
Thickness (mm)	0.5-10	--
Density (g/cm³)	3.3	ASTM D792
Breakdown Voltage (kV/mm)	>10	ASTM D149
Operating Temperature Range (°C)	-50 to 200	--
Volume Resistivity (Ω·cm)	10 ¹³	ASTM D257
Flammability Rating	V-0	UL94

The data provided are typical values derived from laboratory testing and are intended for reference only. They should not be used as specifications or as a basis for design without independent validation.