



Deep-Materials Special Gap Pad: Low density and Low dielectric



Use fundamental science to make practical improvements in TIM

Deep-Materials

TIM Product Brochure

Use *fundamental science* to make practical improvements in Thermal Materials


CPU/GPU TIMs



Grease

- Best in class performance
- Significantly reduce pump out

Highest performance traditional grease & Innovative Liquid Metal grease with low resistance



Liquid Metal

- Multi-phase Liquid metal – high viscosity
- Practical to use
- Highest performance

Brand new category of TIM with perf. of LM but ease of grease

Gap Fillers



Gels

- Highest conductivity
- Almost no oil seepage

Many kinds of unique gels – e.g. ultra low oil seepage gel, low dielectric constant gels



Gap Pads

- Almost eliminate oil seepage
- Reliable to very high temperatures

Ultra low oil seepage & ultra low outgassing silicone pads



GAP Fillers

- For Applications in lower power/thicker TIM applications
- Do not require high pressure or mechanical support
- Typically used in consumer electronics, SSDs, Radios
- Performance measured in thermal conductivity (W/mK)

Our offerings in this space

- Liquid Gap Fillers/Gels
 - Single part (Fully cured)/Two part (in situ cure)
- Gap pads

Special Gap Pad: Low density and Low dielectric

Applications:
Consumer Electronics, Automotive, Computing
SSDs, Memory Modules, Networking, Data Centers

	GFTP-200 LD	GFTP-300 LD	GFTP-300LP	Testing Method
Color	Grey	Yellow	Yellow	Visual
Thickness (mm)	0.5~5.0	0.5~5.0	0.5~5.0	—
Density (g/cc)	2.0	2.3	1.6	ASTM D792
Hardness (Shore 00)	30-50	40-70	20-70	ASTM D2240
Operation Temp (°C)	-50~150	-50~150	-50~150	—
Electrical Performance				
Dielectric Constant@1GHZ	5.5	7.3	3.8	ASTM D150
Volume Resistance (Ω.cm)	10 ¹⁴	10 ¹⁴	10 ¹⁴	ASTM D257
Breakdown Voltage (KV/mm)	>10	>10	>10	ASTM D149
Flammability rating	V-0	V-0	V-0	UL 94
Thermal Performance				
Thermal Conductivity (W/m-K)	2.0	3.0	3.0	ASTM D5470

Contact Us

Deep Materials Inc.

Address: 14654 Placida Ct, Saratoga, CA, USA

Manufacture: No.68 Lianfeng Road, Changshu, Suzhou City,
Jiangsu Province, China

Website: deep-materials.com

Email: sales@deep-materials.com

