

SBI

ใบรับวัสดุคุณภาพ  
(Incoming Material Acceptance)

Inspector

Checked

Approved

Receive Date : 12/01/69

Supplier (ผู้จำหน่าย) : TOYOTA

Grade of Material : S48C

Maker (ผู้ผลิต) : SHI

No.	Heat No.	Q'ty	Data Inspection							
			Specification	Tool	Tol.	1	2	3	4	
1	2414700	32	Ø 40 mm.	Vernier	±0.3	40.27	40.32	40.25	40.20	
			L 5800 mm.	ดิสก์เมตร	±50	5825	5830	5840	5820	
			Appearance	Visual		OK	OK	OK	OK	
			Judgement			O	O	O	O	
2	2414700	32	Ø 40 mm.	Vernier	±0.3	40.23	40.29	40.34	40.30	
			L 5800 mm.	ดิสก์เมตร	±50	5830	5826	5830	5820	
			Appearance	Visual		OK	OK	OK	OK	
			Judgement			O	O	O	O	
3			Ø mm.	Vernier	±0.3					
			L mm.	ดิสก์เมตร	±50					
			Appearance	Visual						
			Judgement							
4			Ø mm.	Vernier	±0.3					
			L mm.	ดิสก์เมตร	±50					
			Appearance	Visual						
			Judgement							
5			Ø mm.	Vernier	±0.3					
			L mm.	ดิสก์เมตร	±50					
			Appearance	Visual						
			Judgement							
6			Ø mm.	Vernier	±0.3					
			L mm.	ดิสก์เมตร	±50					
			Appearance	Visual						
			Judgement							

## Reference :

- ใบรายการตรวจสอบเหล็กเส้น ( PO or Packing List )
- ตรวจสอบ Spec ส่วนผสมเหล็ก ตามมาตรฐาน SBI-PC-S01
- รูปแบบการบรรจุ



## ตรวจสอบสภาพการบรรจุ ( Package )

## หัวข้อการตรวจสอบ

## ผลการตรวจสอบ

1. มัดเหล็กเส้น ไม่ขาดจากกัน

 OK NG

2. การจัดเรียงหัว-ท้ายเหล็กเส้น

 OK NG

semen กัน



3. มีการซึ่งบ่อมัดเหล็กเส้นทุนมัด

 OK NG

Comment : Appearance

Remark :

SYMBOL FOR JUDGE MENT

O

= OK

Δ

= SPECIAL ACCEPT

X

= NO GOOD



SHIJIAZHUANG IRON & STEEL CO., LTD



SG-MES-PZ-1001

NO 25075827

Customer's contract No. ZTH25612 Customer TOYOTA TSUSHO (THAILAND) CO., LTD. Shape of Product Round Bar Standard JSXY2039-2022 Steel grade S48C Certificate No. 2508250126														
Heat No.	2414700	Rolling plan No.	B112490689				Delivery condition	Hot rolled	Size(mm)	DIA. 40	Weight(MT)	16.932	Bundles	9
Chemical Composition (%)														
Item	C	Si	Mn	P	S	Cr	Ni	Cu	O	SP1				
Ladle Result	0.48	0.25	0.78	0.012	0.005	0.10	0.05	0.05	0.0005	0.15				
Scattered porosity	Center porosity	Ingot shape segregation	Yield strength	Tensile strength	Elongation	Reduction of area	Hardness	dA	d(B+C)	Decarburized layer	Austenite grain size	Inspection	Surface quality & Shape size	
Grade	Grade	Grade	ReL MPa	Rm MPa	A %	Z %	HBW	%	%	mm	Grade			
0.5	1.5	0	426	713	24.5	51	149	0.03	0.01	0.25	7.5	Qualified	Qualified	
0.5	1.5	0	415	703	24.0	50	150	0.02	0.02	0.22				
						147								
Note	SP1-Cr+Ni:		12 / 09 / 19		ผู้ตรวจสอบ..... ทักษิณานนท์ O.S.P.									
 Shijiazhuang Iron & Steel Co., Ltd. Steel grade S48C Heat No. 2414700 Size Ø40 mm MADE IN CHINA														
 Shijiazhuang Iron & Steel Co., Ltd. Signature														

Address: Hebei, Shijiazhuang, China 363 Heping donglu, Code:050031, Tel:(0311) 80713193

