| SBI | ใบรับวัตถุดิบ (Incoming Material Acception) | Inspector | Checked | Approved |
|---|---|---|---|---|
| | | | | |

**Receive Date :** 02/03/69 **Supplier (ผู้จำหน่าย):** Sam En

**Grade of Material :** S35C **Maker (ผู้ผลิต) :** SeAH

| No. | Heat No. | Q'ty | Data Inspection | | | | | | |
|---|---|---|---|---|---|---|---|---|---|
| | | | Specification | Tool | Tol. | 1 | 2 | 3 | 4 |
| 1 | B 89093 | 68 | Ø 36 mm. | Vernier | ±0.3 | 35.94 | 35.98 | 35.90 | 36.00 |
| | | | L 5,500 mm. | ตลับเมตร | ±50 | 5,530 | 5,520 | 5,525 | 5,530 |
| | Chamfer 2.70-4.20 | | Appearance | Visual | | ok | ok | ok | ok |
| | | | | Judgement | | Δ | Δ | Δ | Δ |
| 2 | B 89093 | 68 | Ø 36 mm. | Vernier | ±0.3 | 36.04 | 35.96 | 35.89 | 35.93 |
| | | | L 5,500 mm. | ตลับเมตร | ±50 | 5,526 | 5,530 | 5,520 | 5,525 |
| | Chamfer 2.50-4.50 | | Appearance | Visual | | ok | ok | ok | ok |
| | | | | Judgement | | Δ | Δ | Δ | Δ |
| 3 | | | Ø mm. | Vernier | ±0.3 | | | | |
| | | | L mm. | ตลับเมตร | ±50 | | | | |
| | | | Appearance | Visual | | | | | |
| | | | | Judgement | | | | | |
| 4 | | | Ø mm. | Vernier | ±0.3 | | | | |
| | | | L mm. | ตลับเมตร | ±50 | | | | |
| | | | Appearance | Visual | | | | | |
| | | | | Judgement | | | | | |
| 5 | | | Ø mm. | Vernier | ±0.3 | | | | |
| | | | L mm. | ตลับเมตร | ±50 | | | | |
| | | | Appearance | Visual | | | | | |
| | | | | Judgement | | | | | |
| 6 | | | Ø mm. | Vernier | ±0.3 | | | | |
| | | | L mm. | ตลับเมตร | ±50 | | | | |
| | | | Appearance | Visual | | | | | |
| | | | | Judgement | | | | | |

**Reference :**

1. ใบรายการตรวจรับเหล็กเส้น ( PO or Packing List)
2. ตรวจ Spec ส่วนผสมเหล็ก ตามมาตรฐาน SBI-PC-S01
3. รูปแบบการบรรจุ



**ตรวจสอบสภาพการบรรจุ ( Package)**

| หัวข้อการตรวจสอบ | ผลการตรวจสอบ | |
|---|---|---|
| 1. มัดเหล็กเส้นไม่ขาดจากกัน | ☑ OK | ☐ NG |
| 2. การจัดเรียงหัว-ท้ายเหล็กเส้นเสมอกัน | ☑ OK | ☐ NG |
| 3.มีการชี้บ่งที่มัดเหล็กเส้นทุกมัด | ☑ OK | ☐ NG |

SeAH S35C RB036.00 B89093 SeAH Bestee

**Comment :** Appearance

- No Crack
- No Burr
- No Bend
- No Oval

Remark :

SYMBOL FOR JUDGE MENT

O = OK

Δ = SPECIAL ACCEPT

X = NO GOOD



**ต้นฉบับ**

**SeAH Besteel**

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

# INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2025-11-13
Cert. No. : 202511-004713
Made in Korea
Melted and poured in the Republic of Korea



Steel Grade : S35C
Heat No. : B89093
Size : 36 mm
Commodity : Round Bar

Specification :
Melting Process : EAF-LF-VD(RH)-CC
Delivery Condition : As Rolled

Customer : HONDA THAILAND
Supplier : SeAH Besteel
Serial-No. :

| Inspection Items | | Chemical Composition (wt. %) | | | | | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | C | Si | Mn | P | S | Cu | Ni | Cr | Mo | Ni+Cr | | | | | | | | | | |
| | | ×100 | ×100 | ×100 | ×1000 | ×1000 | ×100 | ×100 | ×100 | ×100 | ×100 | | | | | | | | | | |
| Spec. | Min. | 32 | 15 | 60 | | 15 | | | | | | | | | | | | | | | |
| | Max. | 38 | 35 | 90 | 30 | 40 | 30 | 20 | 20 | | 35 | | | | | | | | | | |
| Ladle Result | | 36 | 23 | 70 | 20 | 18 | 17 | 7 | 15 | 1 | 22 | | | | | | | | | | |

| Inspection Items | | Nonmetallic Inclusion (ASTM E-45) | | | | | | | | | | | | | | | |
|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|---|
| | | A(T) | A(H) | B(T) | B(H) | C(T) | C(H) | D(T) | D(H) | | | | | | | | |
| Spec. | Min. | 0 | 0 | 0 | 0 | 0 | 0 | 0 | 0 | | | | | | | | |
| | Max. | 4 | 3 | 3 | 2 | 2 | 2 | 2 | 2 | | | | | | | | |
| Result | | 2.0 | .5 | .0 | .0 | .0 | .0 | 1.0 | .5 | | | | | | | | |

| Inspection Items | | Austenite Grain Size | | |
|---|---|---|---|---|
| Spec. | Min. | 6 | | |
| | Max. | | | |
| Result | | 7.0 | | |

| Inspection Items | | Decarburized Layer (mm) | | |
|---|---|---|---|---|
| | | DM-T | | |
| Spec. | Min. | 0 | | |
| | Max. | .35 | | |
| Result | | .27 | | |

| Inspection Items | | Macro Streak Flaw | | |
|---|---|---|---|---|
| Spec. | Min. | | | |
| | Max. | | | |
| Result | | GOOD | | |

| Inspection Items | | Macro Structure | | |
|---|---|---|---|---|
| | | SURFACE | RANDOM | CENTER |
| Spec. | Min. | | | |
| | Max. | 2 | 2 | 2 |
| Result | | 1.0 | 1.0 | 1.0 |

| Inspection Items | | Product Hardness (HB) | | |
|---|---|---|---|---|
| | | SURFACE | MID | CENTER |
| Spec. | Min. | | | |
| | Max. | 241 | 241 | 241 |
| Result | | 189 | 186 | 181 |

| Inspection Items | | Reduction Ratio | | |
|---|---|---|---|---|
| Spec. | Min. | 4 | | |
| | Max. | | | |
| Result | | 195.4 | | |

| Inspection Items | | Surface Inspection (mm) | | |
|---|---|---|---|---|
| Spec. | Min. | | | |
| | Max. | | | |
| Result | | GOOD | | |

| Inspection Items | | Ultrasonic Test | | |
|---|---|---|---|---|
| Spec. | Min. | | | |
| | Max. | | | |
| Result | | GOOD | | |

SeAH
S35C
RB036.00
B89093
SeAH Besteel

PASS
02 / 03 / 69
ผู้ตรวจสอบ.....
หัวหน้าแผนก.....

| Bundle | TOTAL | | | | | | |
|---|---|---|---|---|---|---|---|
| Quantity(pcs) | 622 | | | | | | |
| Weight(kg) | 27,378 | | | | | | |
| Length(mm) | 5,500 | | | | | | |

**We hereby certify that the material described herein has been made in accordance with the rules of the contract.**
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

Certified by S. J. Yoon.
*Manager of Quality Assurance Team.*

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423