SBI	ใบรับวัตถุดิบ (Incoming Material Acception)	Inspector	Checked	Approved

Receive Date : 02/03/69 **Supplier (ผู้จำหน่าย):** San En

Grade of Material : SCM 415 H **Maker (ผู้ผลิต) :** DAI

No.	Heat No.	Q'ty	Data Inspection						
			Specification	Tool	Tol.	1	2	3	4
1	5C13A	72	Ø 28 mm.	Vernier	±0.3	28.21	28.25	28.20	28.27
			L 5500 mm.	ตลับเมตร	±50	5525	5530	5520	5525
			Appearance	Visual		OK	OK	OK	OK
				Judgement		O	O	O	O
2			Ø mm.	Vernier	±0.3				
			L mm.	ตลับเมตร	±50				
			Appearance	Visual					
				Judgement					
3			Ø mm.	Vernier	±0.3				
			L mm.	ตลับเมตร	±50				
			Appearance	Visual					
				Judgement					
4			Ø mm.	Vernier	±0.3				
			L mm.	ตลับเมตร	±50				
			Appearance	Visual					
				Judgement					
5			Ø mm.	Vernier	±0.3				
			L mm.	ตลับเมตร	±50				
			Appearance	Visual					
				Judgement					
6			Ø mm.	Vernier	±0.3				
			L mm.	ตลับเมตร	±50				
			Appearance	Visual					
				Judgement					

Reference :

1. ใบรายการตรวจรับเหล็กเส้น (PO or Packing List)
2. ตรวจ Spec ส่วนผสมเหล็ก ตามมาตรฐาน SBI-PC-S01
3. รูปแบบการบรรจุ

ตรวจสอบสภาพการบรรจุ (Package)

หัวข้อการตรวจสอบ	ผลการตรวจสอบ	
1. มัดเหล็กเส้นไม่ขาดจากกัน	☑ OK	☐ NG
2. การจัดเรียงหัว-ท้ายเหล็กเส้นเสมอกัน	☑ OK	☐ NG
3.มีการชี้บ่งที่มัดเหล็กเส้นทุกมัด	☑ OK	☐ NG

Comment : Appearance

- No Crack
- No Burr
- No Bend
- No Oval

Remark :

SYMBOL FOR JUDGE MENT

O = OK

Δ = SPECIAL ACCEPT

X = NO GOOD

ต้นฉบับ

INSPECTION CERTIFICATE

It is hereby certified that the above results are true and correct in every detail.

Chita Plant.
Daido Steel Co. Ltd.

Chief of Quality Assurance Section
T. Usami

Messrs; HONDA TRADING CORPORATION. Date ; JUN., 11, 2025 Packing List No; 6-0310 (5EJ064)

Contract No; CAD0053725 (BB550559-00 01) Customer No; Condition; HOT ROLLED

	NO	Type of Steel	Heat No.	Size(MM)	Length(MM)	P'cs	Weight (KGS)	Body Hardness ( )
Quantity	A201- A205	SCM415H	5C63A	DIA 28	4,000- 5,500	301	8,128	
				TOTAL	5 BUNDLES	301	8,128	

Items / Heat No.	Chemical Composition C	SI	MN	P	S	CU	NI	CR	MO	AL	N						Decarburization	Grain Size	Hardenability ℃
Unit	% 100	% 100	% 100	% 1000	% 1000	% 100	% 100	% 100	% 100	% 1000	% 1000	%	%	%	%	%			
Specification	12 -18	15 -35	55 -90	MAX 30	10 -30	MAX 30	MAX 25	85 -125	10 -25	MIN 15	MIN 10								
5C63A	17	26	69	16	17	18	12	102	15	33	14								

MM / Heat No.	Hardenability (End Quenching Method.) 1.5	3	5	7	9	11	13	15	20	30	40	50
5C63A	43	42	35	29	26	24	23	22	19	14	11	9

Non Metallic Inclusion ASTM	AT	AH	BT	BH	CT	CH	DT	DH
5C63A	1.5	0.5	1.0	0.0	0.0	0.0	0.5	0.5

Items / Heat No. / Specification	Mechanical Properties (Type of Specimen) Yield Point Strength	Tensile Strength	Elongation	Reduction of Area	Hardness	Impact Value	Heat Treatment
Unit			%	%	HB		

Items / Heat No.	Macro structure	Streak Flaw	Micro structure	Upsetting Test	Ultrasonic Test	Size Tolerance (MM)
5C63A					GOOD	

PASS
02 / 03 / 69
ผู้ตรวจสอบ.....
หัวหน้าแผนก.....

Remarks