SBI	ใบรับวัตถุดิบ (Incoming Material Acception)	Inspector	Checked	Approved

Receive Date : 05/03/69 **Supplier (ผู้จำหน่าย):** San En

Grade of Material : S35C **Maker (ผู้ผลิต) :** SeAH

No.	Heat No.	Q'ty	Data Inspection						
			Specification	Tool	Tol.	1	2	3	4
1	B 89093	48	Ø 36 mm.	Vernier	±0.3	35.92	36.00	36.02	35.97
			L 5500 mm.	ตลับเมตร	±50	5530	5520	5525	5530
	Chamfer 2.70 - 4.10		Appearance	Visual		OK	OK	OK	OK
				Judgement		O	O	O	O
2	B 89093	48	Ø 36 mm.	Vernier	±0.3	36.01	35.93	35.96	35.92
			L 5500 mm.	ตลับเมตร	±50	5525	5530	5520	5530
	Chamfer 3.10 - 4.50		Appearance	Visual		OK	OK	OK	OK
				Judgement		O	O	O	O
3	B 89093	48	Ø 36 mm.	Vernier	±0.3	36.00	36.04	35.98	35.98
			L 5500 mm.	ตลับเมตร	±50	5520	5530	5525	5530
	Chamfer 2.60 - 4.00		Appearance	Visual		OK	OK	OK	OK
				Judgement		O	O	O	O
4	B 89093	48	Ø 36 mm.	Vernier	±0.3	36.06	35.96	35.89	35.94
			L 5500 mm.	ตลับเมตร	±50	5520	5525	5520	5520
	Chamfer 3.00 - 4.80		Appearance	Visual		OK	OK	OK	OK
				Judgement		O	O	O	O
5			Ø mm.	Vernier	±0.3				
			L mm.	ตลับเมตร	±50				
			Appearance	Visual					
				Judgement					
6			Ø mm.	Vernier	±0.3				
			L mm.	ตลับเมตร	±50				
			Appearance	Visual					
				Judgement					

Reference :

1. ใบรายการตรวจรับเหล็กเส้น (PO or Packing List)
2. ตรวจ Spec ส่วนผสมเหล็ก ตามมาตรฐาน SBI-PC-S01
3. รูปแบบการบรรจุ



ตรวจสอบสภาพการบรรจุ (Package)

หัวข้อการตรวจสอบ	ผลการตรวจสอบ	
1. มัดเหล็กเส้นไม่ขาดจากกัน	☑ OK	☐ NG
2. การจัดเรียงหัว-ท้ายเหล็กเส้นเสมอกัน	☑ OK	☐ NG
3.มีการชี้บ่งที่มัดเหล็กเส้นทุกมัด	☑ OK	☐ NG

SeAH S35C RB036.00 B89093 SeAH Bester

Comment : Appearance

- No Crack
- No Burr
- No Bend
- No Oval

Remark :

SYMBOL FOR JUDGE MENT

O = OK

Δ = SPECIAL ACCEPT

X = NO GOOD

ต้นฉบับ

SeAH Besteel

522, Oehang-ro, Gunsan-si, Jeollabuk-do, Republic of Korea (54007)

INSPECTION CERTIFICATE

ACCORDING TO EN10204:2004, Type 3.1

Date : 2025-11-13
Cert. No. : 202511-004713
Made in Korea
Melted and poured in the Republic of Korea

Steel Grade	: S35C	Specification	:	Customer	: HONDA THAILAND
Heat No.	: B89093	Melting Process	: EAF-LF-VD(RH)-CC		
Size	: 36 mm	Delivery Condition	: As Rolled	Supplier	: SeAH Besteel
Commodity	: Round Bar			Serial-No.	:

Chemical Composition (wt. %)

Inspection Items		C	Si	Mn	P	S	Cu	Ni	Cr	Mo	Ni+Cr
		×100	×100	×100	×1000	×1000	×100	×100	×100	×100	×100
Spec.	Min.	32	15	60		15					
	Max.	38	35	90	30	40	30	20	20		35
Ladle Result		36	23	70	20	18	17	7	15	1	22

Nonmetallic Inclusion (ASTM E-45)

Inspection Items		A(T)	A(H)	B(T)	B(H)	C(T)	C(H)	D(T)	D(H)
Spec.	Min.	0	0	0	0	0	0	0	0
	Max.	4	3	3	2	2	2	2	2
Result		2.0	.5	.0	0	.0	.0	1.0	.5

Austenite Grain Size

Inspection Items				
Spec.	Min.	6		
	Max.			
Result		7.0		

Decarburized Layer (mm)

Inspection Items		DM-T		
Spec.	Min.	0		
	Max.	.35		
Result		.27		

Macro Streak Flaw

Inspection Items				
Spec.	Min.			
	Max.			
Result		GOOD		

Macro Structure

Inspection Items		SURFACE	RANDOM	CENTER
Spec.	Min.			
	Max.	2	2	2
Result		1.0	1.0	1.0

Product Hardness (HB)

Inspection Items		SURFACE	MID	CENTER
Spec.	Min.			
	Max.	241	241	241
Result		189	186	181

Reduction Ratio

Inspection Items				
Spec.	Min.	4		
	Max.			
Result		195.4		

Surface Inspection (mm)

Inspection Items				
Spec.	Min.			
	Max.			
Result		GOOD		

Ultrasonic Test

Inspection Items				
Spec.	Min.			
	Max.			
Result		GOOD		

PASS
06/03/69
ผู้ตรวจสอบ.....
หัวหน้าแผนก.....

SeAH
S35C
RB036.00
B89093
SeAH Bestee

Bundle	TOTAL									
Quantity(pcs)	622									
Weight(kg)	27,378									
Length(mm)	5,500									

We hereby certify that the material described herein has been made in accordance with the rules of the contract.
Our quality system is certified in accordance with IATF 16949:2016 / ISO 9001:2015 by KSA

TEL : +82-(0)2-6970-2192(Sales) +82-(0)63-460-8573(QA) / 8285(QA) / 8516(Technology Service) FAX : +82-(0)63-460-8423

Certified by S. J. Yoon.

Manager of Quality Assurance Team.