

```
fck = float(input(" Enter the value of characteristic compressive strength:"))
```

```
# Experimental Determinations
```

```
Gca = float(input ("Enter the value of specific gravity of CA: ")) Gfa
```

```
= float(input("Enter the value of specific gravity of FA: "))
```

```
Gc = float(input("Enter the value of specific gravity of Cement: "))
```

```
Water_Density = float(input("Enter the value of Water Density: "))
```

```
AGG_Size = float(input(" Enter the nominal Size of Aggregate: "))
```

```
Nature_of_AGG = input("Nature of Aggregates:")
```

```
Slump = float(input("Enter the value of workability of concrete: "))
```

```
Admixture = input("Type of Admixture:")
```

```
Exposure_Condition = input("Exposure Condition:")
```

```
Concreting = input("Type of Concreting:")
```

```
Zone = int(input("Zone: ")) # Target Mean
```

```
Strength
```

```
sigma = {
```

```
10:3.5,
```

```
15:3.5,
```

```
20: 4,
```

```
25:4,
```

```
30: 5,
```

```
35: 5,
```

```
40: 5,
```

```
45: 5,
```

```
50: 5,
```

```
55: 5
```

```
}
```

```
ft = fck + sigma[fck]*1.65
```

```
print("Target Mean Strength: ", ft, "MPa")
```

```
# Maximum free Water Cement Ratio
```

```
# Reference IS 456: 2000 Table 5
```

```
if(Concreting=="Plain"):
```

```
    WC_ratio={
```

```
"Mild" : 0.6,
```

```
"Moderate" :0.6,
```

```
"Severe" :0.5,
```

```
"Very Severe" :0.45,
```

```
"Extreme":0.4
```

```
} else:
```

```
WC_ratio = {
```

```
"Mild": 0.55,
```

```
"Moderate":0.5,
```

```
"Severe" :0.45,
```

```
"Very Severe" :0.45,
```

```
"Extreme":0.4
```

```
}
```

```
print ("W/C Ratio:", WC_ratio[Exposure_Condition])
```

```
WC_ratio = WC_ratio [Exposure_Condition]
```

```
# Minimum Cement Content
```

```

if(Concreting == "plain"):
    Min_Cement_Content = {
        "Mild":220,
        "Moderate": 240,
        "Severe": 250,
        "Very Severe": 260,
        "Extreme": 280
    } else:
        Min_Cement_Content = {
            "Mild": 300,
            "Moderate" :300,
            "Severe": 320,
            "Very Severe" :340,
            "Extreme": 360
        }

    print ("Minum Cement Content:", Min_Cement_Content[Exposure_Condition], "kg/m^3")

# Water Content

Water_Content = {
    10:208,
    20:186,
    40:165
}
Water_Content = Water_Content[AGG_Size] if
(Slump == 75):
    Water_Content = Water_Content + Water_Content*0.03
elif (Slump == 100):
    Water_Content = Water_Content + Water_Content*0.06
elif (Slump == 125):
    Water_Content = Water_Content + Water_Content*0.09
elif (Slump == 150):
    Water_Content = Water_Content + Water_Content*0.12
elif (Slump == 175):
    Water_Content = Water_Content + Water_Content*0.15
elif (Slump == 200):
    Water_Content = Water_Content + Water_Content*0.18

if (Nature_of_AGG == "Sub-Angular"):
    Water_Content = Water_Content - 10 elif
(Nature_of_AGG == "Gravel"):
    Water_Content = Water_Content - 20 elif
(Nature_of_AGG == "Round"):
    Water_Content = Water_Content - 25

if (Admixture == "Plastisizer"):
    Water_Content = Water_Content-(0.1*Water_Content) elif
(Admixture=="Super-plastisizer"):
    Water_Content = Water_Content-(0.2*Water_Content)

print("Water Content: ", Water_Content, "kg/m^3")

# Cement Content

Cement_Content = Water_Content/WC_ratio
print("Cement_Content:", Cement_Content, "kg/m^3")

```

```

print("As Per IS 456:2000, Maximum allowed Cement
Content is 450 kg/m^3")

if (Cement_Content<450):
    Cement_Content = Cement_Content else:
    Cement_Content=450

    if Cement_Content< 450:
print("Safe")

# Volume Calculations

Vol_Cement = Cement_Content/(Gc*Water_Density)
print("Volume of Cemnet: ", Vol_Cement, "m^3")

Vol_Water = Water_Content/Water_Density print("Volume
of Water: ", Vol_Water, "m^3")

Vol_AGG= 1-Vol_Water-Vol_Cement print("Volume of Course Aggregates and Fine
Aggregates: ", Vol_AGG, "m^3")

Zone_ID={}
Zone_ID[1]= {10:0.44, 20:0.60, 40:0.69}

Zone_ID[2]={10:0.46, 20:0.62, 40:0.71}

Zone_ID[3]={10:0.48, 20:0.64, 40:0.73}

Zone_ID[4]={10:0.5, 20:0.66, 40:0.75} Fraction

= Zone_ID[Zone][AGG_Size]

if (WC_ratio==0.5) :
Fraction=Fraction elif
(WC_ratio==0.45):
    Fraction=Fraction+(0.01*Fraction) elif
(WC_ratio==0.4):
    Fraction=Fraction+(0.02*Fraction) elif
(WC_ratio==0.55):
    Fraction=Fraction-(0.01*Fraction) elif
(WC_ratio==0.60):
    Fraction=Fraction-(0.02*Fraction) print("Course
Aggregate fraction:", Fraction)

Vol_CA = Vol_AGG*Fraction print("Volume of Course
Aggregate:", Vol_CA,"m^3")

Vol_FA = Vol_AGG-Vol_CA print("Volume of Fine
Aggregate: ", Vol_FA,"m^3")

Mass_CA= Vol_CA*Gca* Water_Density print("Mass of Course
Aggregates: ", Mass_CA, "Kg/m^3")

Mass_FA = Vol_FA*Gfa*Water_Density
print("Mass of Fine Aggregates:", Mass_FA, "kg/m^3")

# Ratios

```

```
print("Weight Batching")
print(Cement_Content/Cement_Content,":", Mass_FA/Cement_Content,":", Mass_CA/Cement_Content)
➡ Enter the value of characteristic compressive strength:40
Enter the value of specific gravity of CA: 2.74
Enter the value of specific gravity of FA: 2.74
Enter the value of specific gravity of Cement: 3.15
Enter the value of Water Density: 1000
Enter the nominal Size of Aggregate: 20
Nature of Aggregates:Sub-Angular
Enter the value of workability of concrete: 100
Type of Admixture:Super-Plasticizer
Exposure Condition:Severe
Type of Concreting:Reinforced
Zone: 1
Target Mean Strength: 48.25 MPa
W/C Ratio: 0.45
Minum Cement Content: 320 kg/m^3
Water Content: 187.16 kg/m^3
Cement_Content: 415.9111111111111 kg/m^3
As Per IS 456:2000, Maximum allowed Cement Content is 450 kg/m^3
Volume of Cemnet: 0.1320352733686067 m^3
Volume of Water: 0.18716 m^3
Volume of Course Aggregates and Fine Aggregates: 0.6808047266313932 m^3
Course Aggregate fraction: 0.606
Volume of Course Aggregate: 0.4125676643386243 m^3
Volume of Fine Aggregate: 0.26823706229276895 m^3
Mass of Course Aggregates: 1130.4354002878308 Kg/m^3
Mass of Fine Aggregates: 734.969550682187 kg/m^3
Weight Batching
1.0 : 1.7671313197637537 : 2.7179735527330835 : 0.45
Volume Batching:
1.0 : 2.0315560792904463 : 3.1246776244924126 : 1.4174999999999998
```