

# DMH 120 C-HPU

Mechanical, Physical and Thermal Properties

thermoplastic polyurethane with resistance to hydrolysis

PROPERTIES	CONDITION	STANDARD	UNIT		UNIT	
Colour				red		red
hardness	23°C	ISO 868	Shore A	96 ± 2	Shore A	96 ± 2
hardness	23°C/3 sek.	ISO 868	Shore D	50 ± 3	Shore D	50 ± 3
hardness	23°C/15 sek.	ISO 868	Shore D	48 ± 3	Shore D	48 ± 3
modulus 100%	23°C	DIN 53 504	MPa	≥ 11	psi	≥ 1595
modulus 300 %	23°C	DIN 53 504	MPa	≥ 22	psi	≥ 3190
tensile strength	23°C	DIN 53 504	MPa	≥ 45	psi	≥ 6525
elongation at break	23°C	DIN 53 504	%	≥ 450	%	≥ 450
tear strength	23°C	DIN ISO 34-1	kN/m	≥ 80	lbf/inch	≥ 450
spec. gravity	23°C	ISO 1183	kg/m <sup>3</sup>	1110 ± 20	g/cm <sup>3</sup>	1,11± 0,02
abrasion		DIN 53 516	mm <sup>3</sup>	20	mm <sup>3</sup>	20
compression set	*	ISO 815	%	≤ 30	%	≤ 30
compression set	**	ISO 815	%	≤ 35	%	≤ 35
minimum service temperature			°C	-37	°F	-35
maximum service temperature			°C	110	°F	230

\* 24h 70°C 25% def. \*\* 24h 100°C 25% def. \*\*\* 24h 150°C 25% def.

## Chemical Properties

Copolymer, based on aromatic isocyanate and diols

Resistant to oil, water, ozone, microbes

Not resistant to conc. acids, conc. lyes, conc. alcohols and aromatic solvents

<b>Foodstuff approval</b>	in accordance with FDA CFR 21-177.2600
revision: 12-2022	

Detailed information concerning chemical resistance see DMH Chemical Resistance Guide

**DMH Dichtungs- und  
Maschinenhandel GmbH**

 Industriepark West 11  
 8772 Traboch  
 Austria  
 dmh.at

 p. +43 (0)3833/200 60-0  
 f. +43 (0)3833/200 60-500  
 e. office@dmh.at
