# CROSSPAULIN – EXPORT TECHNICAL INFORMATION REQUEST

| A. Product | |
|---|---|
| • Product name: | Cross-laminated multi-layer tarpaulin |
| • Brand: CROSSPAULIN - | A PRODUCT OF PANKAJ |
| • Construction: | AS AGREED BETWEEN THE PURCHASER & SUPPLIER |
| • Number of layers: | MINIMUM 2 LAYERS – MAXIMUM 4 LAYERS |
| • Polymer composition: | COMBINATION OF LDPE, LLDPE & PLASTOMER |
| • Virgin/recycled percentage: | 100% VIRGIN |
| • GSM: | 70,90,120,150,200,250 |
| • GSM tolerance: | ±5% |
| • Thickness: , | 0.10,0.12, |
| • Thickness tolerance: | |
| • Available colours: | BLUE, YELLOW, RED, OLIVE GREEN, BLACK & SILVER, BLACK,NATURAL, MILKY WHITE |
| • Maximum width: | 2750 mm |
| • Maximum roll length: | 1000MTR |

| B. Mechanical | |
|---|---|
| • Tensile strength MD: | 250 $Kg/cm^2$ |
| • Tensile strength TD: | 200 $Kg/cm^2$ |
| • Elongation MD: | 400% |
| • Elongation TD: | 300% |
| • Tear strength MD: | AS PER IS:14611:2024 (DEPENDS ON GSM) |
| • Tear strength TD: | AS PER IS:14611:2024 (DEPENDS ON GSM) |
| • Dart impact: | AS PER IS:14611:2024 (DEPENDS ON GSM) |
| • Puncture resistance: | PASS |
| • Test methods: | AS PER IS 14611:2024 |

| C. Weathering | |
|---|---|
| • UV stabilisation: | YES |
| • UV test standard: | IS 14611:2024 |
| • UV exposure hours: | 192 HOURS |
| • Tensile retention after UV: | MD – 65.2% , TD – 67.51% |
| • Elongation retention after UV: | MD – 66.03% , TD – 66.34% |
| • Accelerated ageing: | IS 7016 (Part 8) PASS |
| • Ageing temperature: | 70° C |
| • Ageing duration: | 168 HOURS |
| • Tensile retention after ageing: | MD - 232 $Kg/cm^2$ , TD - 202 $Kg/cm^2$ |
| • Tear retention after ageing: | MD –2415 gram, TD – 1875 gram |
| • Flex cycles: | 50000 CYCLES |
| • Flex test result: | PASSED |

**REGISTERED OFFICE**
**'STEPHEN HOUSE'**, Suite No. 57ABC, 4th Floor
56E, Hemanta Basu Sarani, Kolkata - 700001
Ph.:033-2262-3124/3125, 033-2242-9745, Fax : 033-2243-3091
E info@malsonspolymers.com W www.malsonspolymers.com

**WORKSHOP I :** Sankrail Industrial Park, Dhulagori,
P.S.: Sankrail, Howrah, Pin : 711302
**WORKSHOP II :** Barunda (Near Ghoraghata Ananda
Niketan School) Bagnan, Howrah - 711303

| D. Waterproofing | |
|---|---|
| • Water-proofness test standard: | IS 7016 (Part 7) PASS |
| • Hydrostatic pressure: | |
| • Test duration: | 1 HOUR |
| • Result: | PASS |

| E. Fabrication | |
|---|---|
| • Heat sealing: | YES |
| • Welding method: | HOT WEDGE WELDING |
| • Seam strength: | PASS |
| • Hemming: | FOLDED FILM 55 MM and TWO SEALING BANDS WITH DISTANCE 10 MM |
| • Eyelet type: | ULTRASONIC |
| • Eyelet size: | 35MM DIA |
| • Eyelet spacing: | 3FT |
| • Reinforcement: | YES |
| • Rope options: | YES |

| F. Standards | |
|---|---|
| • IS 14611:2024 compliance: | YES |
| • BIS licence: | YES |
| • Certificate number: | CM/L-5100278799 |
| • Independent laboratory: | YES |
| • Test report date: | INITIATION DATE – 06.11.2025 & COMPLETION DATE – 02.01.2026 |
| • ISO certification: | IN122639A |
| • Other international certifications: | NO |

| G. Chemical compliance | |
|---|---|
| • REACH: | NO |
| • SVHC: | NO |
| • RoHS: | NO |
| • Heavy metals: | NO |
| • PAH: | NO |
| • Food contact, if applicable: | YES |
| • Recyclability: | YES 100% |
| • Material declaration: | YES |

| H. Export | |
|---|---|
| • MOQ: | 24 TONS |
| • Standard lead time: | 30 DAYS |
| • Monthly production capacity: | 200 TONS |
| • Private labelling: | YES |
| • Custom printing: | YES |
| • Custom colours: | YES |
| • Custom sizes: | YES |
| • Packing options: | HEAVY DUTY BROWN PAPER, WOODEN BOX PACKING ETC. |
| • 20-ft container loading: | YES |
| • 40-ft HC loading: | YES |
| • HS/HSN classification used by manufacturer/exporter: | 39269099 |

| I. Commercial | |
|---|---|
| • EXW price: | **235/KG** |
| • FOB price: | **240/kg** |
| • Price per kg: | **235 Rs** |
| • Price per square metre: | **NA** |
| • Price per piece: | **NA** |
| • Sample availability: | **YES** |
| • Payment terms: | **Advance** |
| • Warranty: | |
| • Claim/replacement policy: | **Any manufacturing defect** |

**REGISTERED OFFICE**
**'STEPHEN HOUSE'**, Suite No. 57ABC, 4th Floor
56E, Hemanta Basu Sarani, Kolkata - 700001
Ph.:033-2262-3124/3125, 033-2242-9745, Fax : 033-2243-3091
E info@malsonspolymers.com W www.malsonspolymers.com

**WORKSHOP I :** Sankrail Industrial Park, Dhulagori,
P.S.: Sankrail, Howrah, Pin : 711302
**WORKSHOP II :** Barunda (Near Ghoraghata Ananda
Niketan School) Bagnan, Howrah - 711303