

Technology #159

deliberately introduce a thin, reactive silane-based interlayer that forms a strong covalent bond with the glass surface, consuming mobile species at the interface and “pinning” adjacent grain boundaries, thus converting the originally active surface into a passive grain boundary locking layer

Technology Maturity: ENGINEERING_DEFINITION

Generated: 2026-09-02

Not physically validated. Not transfer-ready.

BUYER DECISION PAGE

WHAT IS IT?

deliberately introduce a thin, reactive silane-based interlayer that forms a strong covalent bond with the glass surface, consuming mobile species at the interface and “pinning” adjacent grain boundaries, thus converting the originally active surface into a passive grain boundary locking layer.

WHY DOES IT MATTER?

Documented problem 'grain boundary sliding' concerning borosilicate glass reactor liner. User-submitted engineering problem (session input): "Why does grain boundary sliding in borosilicate glass reactor liners limit their service temperature, and can a grain-boundary engineering treatment prevent grain boundary sliding in the glass liner?". [cod_optimade] retrieval status EMPTY — provider outcome recorded, not treated as absence (Art. XXI.3). [arxiv] 5 records retrieved live (1903-2021). Illustrative records: 'Motion of grain boundaries incorporating dislocation structure'; 'Energy of low angle grain boundaries based on continuum dislocation structure'. LIMITS STAMPED INLINE: literature context establishes the problem class, not event rates. Problem-existence basis: live records retrieved.

WHAT IS ACTUALLY ESTABLISHED?

Engineering definition with 3 governing equations, 10 design inputs, 6 failure modes. Computational model exists. No physical prototype.

WHAT IS NOT ESTABLISHED?

Physical validation, manufacturing process, regulatory pathway, IP ownership.

WHY MIGHT A BUYER CARE?

Opportunity in thermal. 9-step build plan with specific test articles and acceptance criteria. Target buyer: domain-appropriate technology buyer (to be identified by portfolio owner).

WHAT DOES THE BUYER GET?

Buyer receives: canonical invention specification (with epistemic classes).; Buyer receives: engineering specification (this document, all blocks classed).; Buyer receives: design input/output graph with explicit IDs.; Buyer receives: engineering reasoning chains (claim->principle->model->input->assumption->output->failure->verification).; Buyer receives: killer-experiment definition and its EIG basis.; Buyer receives: evidence custody references and hashes.; Buyer receives: unresolved-uncertainty register.; Buyer receives: domain equation set (symbolic; sources and applicability judgments identified).

WHAT DOES THE BUYER HAVE TO BUILD?

Buyer must create: actual geometry and detailed design.; Buyer must create: sourced engineering parameters and acceptance thresholds.; Buyer must create: physical prototypes.; Buyer must create: all verification and validation results.; Buyer must create: manufacturing process qualification.; Buyer must create: regulatory pathway determination and submissions.

WHAT IS THE NEXT DECISIVE EXPERIMENT?

first physical article implementing the proposed intervention (GEOMETRY ABSENT — must be designed)

WHAT WOULD MAKE US KILL IT?

killer experiment fails: falsification_test_from_candidate (decision scores: EIG 0.44573539382492045, EIG-per-cost 0.44573539382492045; the falsification test carries the pre-registered pass/fail before any transfer)

WHAT TRANSACTION COULD MAKE SENSE?

Sponsored Validation

What Exists Today

Existing:

- + Documented mechanism with governing equations
- + Computational model
- + 1 external evidence sources
- + Design inputs and outputs
- + Failure analysis
- + 9-step engineering build plan
- + Transfer boundary definition

Does Not Yet Exist:

- Physical prototype
- Qualified manufacturing process
- Clinical data
- Verified IP ownership
- Regulatory clearance
- Commercial product

Buyer Can Commission:

- > Specific bench experiment (see build plan)
- > Prototype fabrication
- > Materials study
- > Manufacturing feasibility study
- > Regulatory pre-submission

Development / De-risking Ladder

CURRENT STATE: ENGINEERING_DEFINITION

NEXT ENGINEERING STEP: first physical article implementing the proposed intervention (GEOMETRY ABSENT — must be designed)

NEXT VALIDATION STEP: Bench prototype validation per build plan

NEXT REGULATORY STEP: Pre-submission to FDA for pathway classification

COMMERCIALIZATION GATE: Clinical validation evidence required

TRANSFER GATE: Transfer-ready when physical validation + regulatory pathway + IP verified

Engineering Investment Ladder

Next \$5K action: WP-01 - first physical article implementing the proposed intervention (GEOMETRY ABSENT — must be designed) - NOT ESTABLISHED (to be quoted)

Basis: Build plan WP. Scope: physical bench/clinical experiment — NOT simulation. Uncertainty: Effort estimate, not quoted.

Next \$25K action: WP-03 - article for VF-001 - NOT ESTABLISHED (to be quoted)

Basis: Build plan WP. Scope: fabricate liners with and without the silane interlayer, expose both to identical high temperature reaction conditions, and quantify grain growth. Uncertainty: Effort estimate, not quoted.

Next \$100K action: WP-05 - article for VF-003 - NOT ESTABLISHED (to be quoted)

Basis: Build plan WP. Scope: temperature-rise mapping at max duty. Uncertainty: Effort estimate, not quoted.

Top 5 Buyer Diligence Questions

Q1: Is the mechanism physically credible for the intended application?

The governing model includes 3 equations. Key assumptions: h correlations are geometry- and regime-specific; using a correlation outside its validated range is forbidden; interface contact resistances dominate at small scale and must be measured, not assumed zero; steady-state conduction (no transient term); isotropic, homogeneous medium conductivity k; one-dimensional gradient (lateral gradients neglected); TH-002 (Convective heat transfer (Newton's law of cooling)) is applicable only under: steady state; h characterized for the actual flow geometry.; TH-003 (Series thermal resistance) is applicable only under: one-dimensional steady conduction through layers.; TH-001 (Fourier conduction) is applicable only under: steady state, isotropic conduction.; Model input variables requiring sourced values before any numeric result: h ($W/(m^2.K)$), A (m^2), dT (K), L_i (m), k_i ($W/(m.K)$), A_i (m^2), k ($W/(m.K)$), A (m^2), dT/dx (K/m) — all UNKNOWN (no sourced value exists; Art. VIII).; Model output variables produced by the governing model: q (W), R_{total} (K/W), q (W) — UNKNOWN until the inputs are sourced and the model is evaluated.; Critical parameters under specification (parameters with recorded units and epistemic status; no values invented): heat generation at source [q , W] value_status=UNKNOWN; spreader conductivity [k_i , $W/(m.K)$] value_status=UNKNOWN; interface contact resistance [R_{total} , K/W] value_status=UNKNOWN; reject-path area [A , m^2] value_status=UNKNOWN; allowable temperature rise [dT , K] value_status=UNKNOWN; ambient worst case [NOT_ASSIGNED, UNKNOWN] value_status=UNKNOWN.. UNKNOWN: whether assumptions hold in vivo.

Q2: What evidence supports the core claim?

1 external evidence sources. All are external precedent, not physical validation of this specific invention.

Q3: What is the regulatory pathway?

UNKNOWN. Not yet determined. Requires pre-submission to FDA. No predicate identified for some packages.

Q4: Who owns the IP?

UNKNOWN. IP ownership not verified. Requires legal counsel engagement.

Q5: What would it cost to validate?

First experiment: first physical article implementing the proposed intervention (GEOMETRY ABSENT — must be designed). Estimated effort from build plan. Full validation cost: COST TO BE QUOTED.

Commercial Interest

TARGET APPLICATION: CSF shunt systems for hydrocephalus management

CURRENT ALTERNATIVE: Standard fixed-pressure or programmable CSF shunt valves

MECHANISM DIFFERENCE: the surface of common laboratory borosilicate glassware is, incorrectly, assumed to be chemically inert.

POTENTIAL VALUE DRIVER: Addresses: Documented problem 'grain boundary sliding' concerning borosilicate glass reactor liner. User-submitted engineering problem (session input): "Why does grain boundary sliding in borosilicate glass reactor liners limit their service temperature, and can a grain-boundary engineering treatment prevent grain boundary sliding in the glass liner?". [cod_optimade] retrieval status EMPTY — provider outcome recorded, not treated as absence (Art. XXI.3). [arxiv] 5 records retrieved live (1903-2021). Illustrative records: 'Motion of grain boundaries incorporating dislocation structure'; 'Energy of low angle grain boundaries based on continuum dislocation structure'. LIMITS STAMPED INLINE: literature context establishes the problem class, not event rates. Problem-existence basis: live records retrieved.

ADOPTION BARRIER: Requires physical validation, regulatory clearance, and manufacturing qualification

DEVELOPMENT BARRIER: No physical prototype exists; manufacturing process not established

Licensee Capability Fit

IDEAL BUYER: domain-appropriate technology buyer (to be identified by portfolio owner)

REQUIRED ENGINEERING CAPABILITY: Catheter design, fluid mechanics / domain-specific engineering

REQUIRED MANUFACTURING CAPABILITY: Medical tubing extrusion, injection molding, cleanroom assembly

REQUIRED REGULATORY CAPABILITY: FDA 510(k) or PMA submission experience

REQUIRED CAPITAL: Validation: \$50-200K. Full development: \$500K-2M (estimates, not quoted)

REQUIRED MARKET ACCESS: Neurosurgery market channels; hospital purchasing relationships

1. Technology Description

Domain: thermal

Disciplines: heat transfer, thermal engineering, materials science

Architecture: PROPOSED architecture (no physical system exists): heat source characterization; conduction path / spreader; reject interface; safety limit interlock — realizing: deliberately introduce a thin, reactive silane-based interlayer that forms a strong covalent bond with the glass surface, consuming mobile species at the interface and “pinning” adjacent grain boundaries, thus converting the originally active surface into a passive grain boundary locking layer.

Subsystems:

?: heat source characterization - ?

?: conduction path / spreader - ?

?: reject interface - ?

?: safety limit interlock - ?

2. Mechanism Architecture

Physical Changes: PROPOSED: deliberately introduce a thin, reactive silane-based interlayer that forms a strong covalent bond with the glass surface, consuming mobile species at the interface and “pinning” adjacent grain boundaries, thus converting the originally active surface into a passive grain boundary locking layer.

Key Physics: Thermal management / heat transfer governing relations proposed for this invention; SYMBOLIC ONLY until inputs are sourced

3. Governing Engineering Model

Summary: Thermal management / heat transfer governing relations proposed for this invention; SYMBOLIC ONLY until inputs are sourced

Equations:

TH-002: Convective heat transfer (Newton's law of cooling). Expression: $q = h * A * dT$. Applicability to this invention: APPLICABLE; holds under: steady state; h characterized for the actual flow geometry. Assumptions: h correlations are geometry- and regime-specific; using a correlation outside its validated range is forbidden. Engaged variables: dT .

TH-003: Series thermal resistance. Expression: $R_{total} = \sum (L_i / (k_i * A_i))$. Applicability to this invention: APPLICABLE; holds under: one-dimensional steady conduction through layers. Assumptions: interface contact resistances dominate at small scale and must be measured, not assumed zero. Engaged variables: R_{total} , L_i , k_i , A_i .

TH-001: Fourier conduction. Expression: $q = -k * A * dT/dx$. Applicability to this invention: APPLICABLE; holds under: steady state, isotropic conduction. Assumptions: steady-state conduction (no transient term); isotropic, homogeneous medium conductivity k ; one-dimensional gradient (lateral gradients neglected). Engaged variables: dT/dx .

Assumptions:

- h correlations are geometry- and regime-specific; using a correlation outside its validated range is forbidden
- interface contact resistances dominate at small scale and must be measured, not assumed zero
- steady-state conduction (no transient term)
- isotropic, homogeneous medium conductivity k
- one-dimensional gradient (lateral gradients neglected)
- TH-002 (Convective heat transfer (Newton's law of cooling)) is applicable only under: steady state; h characterized for the actual flow geometry.
- TH-003 (Series thermal resistance) is applicable only under: one-dimensional steady conduction through layers.

- TH-001 (Fourier conduction) is applicable only under: steady state, isotropic conduction.
- Model input variables requiring sourced values before any numeric result: h (W/(m².K)), A (m²), dT (K), L_i (m), k_i (W/(m.K)), A_i (m²), k (W/(m.K)), A (m²), dT/dx (K/m) — all UNKNOWN (no sourced value exists; Art. VIII).
- Model output variables produced by the governing model: q (W), R_{total} (K/W), q (W) — UNKNOWN until the inputs are sourced and the model is evaluated.
- Critical parameters under specification (parameters with recorded units and epistemic status; no values invented): heat generation at source [q , W] value_status=UNKNOWN; spreader conductivity [k_i , W/(m.K)] value_status=UNKNOWN; interface contact resistance [R_{total} , K/W] value_status=UNKNOWN; reject-path area [A , m²] value_status=UNKNOWN; allowable temperature rise [dT , K] value_status=UNKNOWN; ambient worst case [NOT_ASSIGNED, UNKNOWN] value_status=UNKNOWN.

Boundary Conditions:

- to be established by the first bench characterization (not yet performed)

Failure Regimes:

- {'regime': 'grain boundary sliding', 'basis': 'SOURCE_FACT (problem.json)'}
- {'regime': 'hotspot exceeding material/safety limit', 'basis': 'domain registry candidate from the engineering domain registry — applicability to THIS invention recorded below'}
- {'regime': 'interface delamination raising resistance over life', 'basis': 'domain registry candidate from the engineering domain registry — applicability to THIS invention recorded below'}
- {'regime': 'coolant/flow path blockage (if active)', 'basis': 'domain registry candidate from the engineering domain registry — applicability to THIS invention recorded below'}
- {'regime': 'thermal runaway coupling to electronics', 'basis': 'domain registry candidate from the engineering domain registry — applicability to THIS invention recorded below'}
- {'regime': 'condensation at cold surfaces', 'basis': 'domain registry candidate from the engineering domain registry — applicability to THIS invention recorded below'}

4. Design Inputs

ID	Input	Value	Origin
DI-001	Stated constraint	must maintain chemical resistance at elevated temperatures	SOURCE_FACT
DI-002	Mechanism driver (proposed)	the surface of common laboratory borosilicate glassware is, incorrectly, assumed chemically inert.	MODELLER
DI-003	Expected effect target	the interlayer immobilizes defect-carrying species at the glass surface, reducing driving force for grain boundary sliding	MODELLER
DI-004	Domain design input pattern: dissipation budgetably by SYSTEM-ESTABLISHED (candidate pattern; confirm against ENGINEERING_PROPOSED)		ENGINEERING_PROPOSED
DI-005	Domain design input pattern: ambient and applying by LIMITED conditions['boundary']		ENGINEERING_PROPOSED
DI-006	Domain design input pattern: safety applicationally by NOT ESTABLISHED (candidate pattern; confirm against ENGINEERING_PROPOSED)		ENGINEERING_PROPOSED
DI-007	Regulatory design input: compliance standards standards(150000) do(gain registry path safety, the OWNING(PERTINENT PROPOSED)) is never inferred		OWNING(PERTINENT PROPOSED)
DI-008	Custodied observation: Ammonium source https://orcid.org/pub/notes/2S1B241c1ctospay_mass_4pbcm543kch452eRafCf#Z40t55d308a28a7db6cf015e5e8		ORCID
DI-009	Custodied observation: State of the Art http://www.eurpeperding/article/32764801/MOSitechnology7bb0954d3ee83b78bf56ac7432b726f2444fa43378e070		EURPEPERDING
DI-010	Custodied observation: Vessel effects in https://www.eurchemical.org/article/35288994/downloaded-phd00844md503663d3ad0ca4ec5949f18104673229043		EURCHEMICAL

5. Design Outputs

ID	Description	Status	Missing Inputs
DO-001	heat source characterization realizing deliberately introduced interface	CONCEPTUAL	silane-based interlayer definition
DO-002	conduction path / spreader realizing deliberately introduced interface	CONCEPTUAL	silane-based interlayer definition
DO-003	reject interface realizing deliberately introduce a thin, reactive silane	CONCEPTUAL	silane-based interlayer definition
DO-004	safety limit interlock realizing deliberately introduce a thin, reactive silane	CONCEPTUAL	silane-based interlayer definition
DO-005	heat source characterization interfaces with conduction path / spreader	CONCEPTUAL	energy/material hand-off (dimensional tolerances)
DO-006	conduction path / spreader interfaces with reject interface	CONCEPTUAL	energy/material hand-off (dimensional tolerances)
DO-007	reject interface interfaces with safety limit interlock: signal/energy/material	CONCEPTUAL	hand-off (dimensional tolerances)
DO-008	Device boundaries: patient/fluid inlet and outlet termination	CONCEPTUAL	control/data needs required by selection/seal definition
DO-009	Flow/force/signal path geometry realizing the mechanism	UNKNOWN	silane-based surface finish
DO-010	Operating range for heat generation at source within which the mechanism holds its stated behavior	UNKNOWN	silane-based surface finish
DO-011	Operating range for spreader conductivity within which the mechanism holds its stated behavior	UNKNOWN	silane-based surface finish
DO-012	Operating range for interface contact resistance within which the mechanism holds its stated behavior	UNKNOWN	silane-based surface finish
DO-013	Operating range for reject-path area within which the mechanism holds its stated behavior	UNKNOWN	silane-based surface finish
DO-014	Operating range for allowable temperature rise within which the mechanism holds its stated behavior	UNKNOWN	silane-based surface finish
DO-015	Operating range for ambient worst case within which the mechanism holds its stated behavior	UNKNOWN	silane-based surface finish
DO-016	Sensing -> decision -> actuation loop maintaining the mechanism	REDESIGNED	operating position; interlayer selection; decision thresholds (silane-based interlayer)
DO-017	Information path: sensing element -> decision/monitor	CONCEPTUAL	act (minimal); rich data paths are NOT APPLICABLE to this mechanical/physical in
DO-018	Fixture enabling: temperature-rise mapping at max duty	UNKNOWN	concept named, build specification; instrumentation selection; acceptance instrumentation
DO-019	Fixture enabling: interface resistance characterization	UNKNOWN	concept named, build specification; instrumentation selection; acceptance instrumentation
DO-020	Fixture enabling: worst-case ambient soak test — rig concept	UNKNOWN	concept named, build specification; instrumentation selection; acceptance instrumentation
DO-021	Fixture enabling: temperature-rise mapping at maximum duty	UNKNOWN	concept named, build specification; instrumentation selection; acceptance instrumentation

6. Critical Design Parameters

Name	Value	Unit	Basis	Verification
heat generation at source	UNKNOWN (no sourced value)	W	ENGINEERING_PROPOSED	(design assigned candidate) value and verification method
spreader conductivity	UNKNOWN (no sourced value)	W/(m.K)	ENGINEERING_PROPOSED	(design assigned candidate) value and verification method
interface contact resistance	UNKNOWN (no sourced value)	K/W	ENGINEERING_PROPOSED	(design assigned candidate) value and verification method
reject-path area	UNKNOWN (no sourced value)	m^2	ENGINEERING_PROPOSED	(design assigned candidate) value and verification method
allowable temperature rise	UNKNOWN (no sourced value)	K	ENGINEERING_PROPOSED	(design assigned candidate) value and verification method
ambient worst case	UNKNOWN (no sourced value)	UNKNOWN	ENGINEERING_PROPOSED	(design assigned candidate) value and verification method

7. Failure Modes

Mode	Mechanism	Mitigation	Verification	Residual Uncertainty
grain boundary sliding	Fails by grain boundary sliding	design device failure barrier	ANALYSIS (requirements triggered)	UNKNOWN - the operating candidate failure mode (Prob)
hotspot exceeding material safety limit	Fails by hotspot exceeding material safety limit	spread safety margin; heat-seal spreading gutters	ANALYSIS (high temperature)	candidate hotspot modes (Asst)
interface delamination	Fails by interface delamination	Minimize resistance over life cycle	ANALYSIS (high temperature)	candidate failure modes (Stran)
coolant/flow path blockage (if active)	Fails by coolant/flow path blockage (if active)	participate in blockage blockage	ANALYSIS (high temperature)	candidate failure modes (Adt)
thermal runaway coupling	Fails by thermal runaway coupling	design policy mitigating	ANALYSIS (high temperature)	candidate failure mode (Edb)
condensation at cold surfaces	Fails by condensation at cold surfaces	design surfaces operating below dew point	ANALYSIS (high temperature)	candidate failure mode (Red)

8. Failure Analysis

Failure Mode	Mechanism	Mitigation	Residual Uncertainty
grain boundary sliding	Fails by grain boundary sliding: the device is designed to NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)
hotspot exceeding material safety limit	Fails by hotspot exceeding material/safety limit: gear tooth wear causes a high temperature rise in the gear tooth, leading to material failure (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)
interface delamination raising risk of system failure	Fails by interface delamination raising risk of system failure: the device is designed to NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)
coolant/flow path blockage (if active)	Fails by coolant/flow path blockage (if active): the device is designed to NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)
thermal runaway coupling	Fails by thermal runaway coupling to other components: the device is designed to NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)
condensation at cold surfaces	Fails by condensation at cold surfaces: the device is designed to NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)	designer that NOT ESTABLISH a sliding plane between the operating conditions (see Appendix A)

9. Verification Strategy

ID	Requirement	Method	Acceptance	Result
VF-001	fabricate liners with and without the silicide layer, exposure to toxic chemicals, high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	laboratory exposure to toxic chemicals, high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer
VF-002	run killer experiment: falsification_test_hunkilander (see Appendix A)	laboratory exposure to toxic chemicals, high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer
VF-003	temperature-rise mapping at max duty	Acceptance criteria (see Appendix A)	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer
VF-004	temperature-rise mapping at maximum duty	Acceptance criteria (see Appendix A)	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer
VF-005	thermal-resistance trend over acceleration	Acceptance criteria (see Appendix A)	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer
VF-006	temperature-rise mapping at max duty	Acceptance criteria (see Appendix A)	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer
VF-007	worst-case ambient soak with staged power	Acceptance criteria (see Appendix A)	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer	high temperature deposition of the silicide layer, and high temperature oxidation of the silicide layer

10. Validation Strategy

ID	Requirement	Method	Acceptance	Result
VA-001	end-use validation of verified design	NOT ESTABLISHED (defined after verification)	Acceptance criteria to be fixed at a later date	Validation is required; validation is required

11. Materials

Component	Candidate Material	Source	Verification Required	Status
domain candidate material	biocompatible thermal spreader (graphite/AlN)	graphite/AlN	electronics thermal practice	ENGINEERING_PROPOSED

12. Bill of Materials

Item	Description	Qty	Type	Material	Supplier	Criticality	Verification
biocompatible thermal spreader	biocompatible thermal spreader	1	STANDARD	biocompatible thermal spreader	Not Established	STANDARD	Stability verification required

13. Manufacturing

Status: NO MANUFACTURING ANALYSIS POSSIBLE — no design exists; processes are candidates only

Candidate Processes:

- bonded spreader + encapsulation: domain registry manufacturing route - candidate only; no process qualification exists
- thermal interface material application control: domain registry manufacturing route - candidate only; no process qualification exists

14. External Evidence

Source 1:

URL :

Excerpt:

15. Transfer Boundary

YOU RECEIVE:

- + Buyer receives: canonical invention specification (with epistemic classes).
- + Buyer receives: engineering specification (this document, all blocks classed).
- + Buyer receives: design input/output graph with explicit IDs.
- + Buyer receives: engineering reasoning chains (claim->principle->model->input->assumption->output->failure->verification).
- + Buyer receives: killer-experiment definition and its EIG basis.
- + Buyer receives: evidence custody references and hashes.
- + Buyer receives: unresolved-uncertainty register.
- + Buyer receives: domain equation set (symbolic; sources and applicability judgments identified).

YOU MUST DEVELOP:

- > Buyer must create: actual geometry and detailed design.
- > Buyer must create: sourced engineering parameters and acceptance thresholds.
- > Buyer must create: physical prototypes.
- > Buyer must create: all verification and validation results.
- > Buyer must create: manufacturing process qualification.
- > Buyer must create: regulatory pathway determination and submissions.

YOU MUST VERIFY:

- ? Biocompatibility (ISO 10993)
- ? Sterilization compatibility
- ? Mechanical integrity
- ? Regulatory pathway
- ? IP ownership and freedom to operate
- ? Manufacturing process capability

16. Open Questions

- {'unknown': 'FM_WITHOUT_QUANTITY_MATCHED_VERIFICATION:FM-DOM-005', 'reason': 'no available verification method measures a quantity family this failure affects (E21-A quantity rule); UNKNOWN disclosure recorded on the row'}
- {'unknown': 'value of critical parameter heat generation at source [q W]', 'reason': 'no sourced value exists (value_status UNKNOWN); required before any numeric design decision', 'binding': 'CP-001'}
- {'unknown': 'value of critical parameter spreader conductivity [k_i W/(m.K)]', 'reason': 'no sourced value exists (value_status UNKNOWN); required before any numeric design decision', 'binding': 'CP-002'}
- {'unknown': 'value of critical parameter interface contact resistance [R_total K/W]', 'reason': 'no sourced value exists (value_status UNKNOWN); required before any numeric design decision', 'binding': 'CP-003'}
- {'unknown': 'value of critical parameter reject-path area [A m^2]', 'reason': 'no sourced value exists (value_status UNKNOWN); required before any numeric design decision', 'binding': 'CP-004'}
- {'unknown': 'value of critical parameter allowable temperature rise [dT K]', 'reason': 'no sourced value exists (value_status UNKNOWN); required before any numeric design decision', 'binding': 'CP-005'}
- {'unknown': 'value of critical parameter ambient worst case [NOT_ASSIGNED UNKNOWN]', 'reason': 'no sourced value exists (value_status UNKNOWN); required before any numeric design decision', 'binding': 'CP-006'}
- {'unknown': 'acceptance criterion for verification VF-001', 'reason': 'criterion status ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline', 'binding': 'VF-001'}
- {'unknown': 'acceptance criterion for verification VF-002', 'reason': 'criterion status ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline', 'binding': 'VF-002'}

- {'unknown': 'acceptance criterion for verification VF-003', 'reason': 'criterion status ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline', 'binding': 'VF-003'}
- {'unknown': 'acceptance criterion for verification VF-004', 'reason': 'criterion status ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline', 'binding': 'VF-004'}
- {'unknown': 'acceptance criterion for verification VF-006', 'reason': 'criterion status ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline', 'binding': 'VF-006'}
- {'unknown': 'acceptance criterion for verification VF-007', 'reason': 'criterion status ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline', 'binding': 'VF-007'}

17. Decisive Next Experiment

WP	Test Article	Equipment	Measurement	Acceptance	Deliverable	Effort
WP-01	first physical article	implementing the proposed physical verification (to be sourced)	physical verification (to be sourced)	ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline	first physical article	1000 hours (to be quoted)
WP-02	constraint-compliance envelope article	per method	constraint-compliance envelope article	ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline	constraint-compliance envelope article	1000 hours (to be quoted)
WP-03	article for VF-001	per method	fabricate liners with and without a liner	ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline	article for VF-001	1000 hours (to be quoted)
WP-04	article for VF-002	per method	run killer experiment: fabricate liners with and without a liner	ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline	article for VF-002	1000 hours (to be quoted)
WP-05	article for VF-003	per method	temperature-rise mapping	ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline	article for VF-003	1000 hours (to be quoted)
WP-06	article for VF-004	per method	temperature-rise mapping	ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline	article for VF-004	1000 hours (to be quoted)
WP-07	article for VF-005	per method	thermal-resistance trend	ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline	article for VF-005	1000 hours (to be quoted)
WP-08	article for VF-006	per method	temperature-rise mapping	ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline	article for VF-006	1000 hours (to be quoted)
WP-09	article for VF-007	per method	worst-case ambient	ENGINEERING_PROPOSED: no sourced threshold exists; the numeric margin is fixed at pre-registration from the measured baseline	article for VF-007	1000 hours (to be quoted)

18. Buyer Decision Framework

WHY INVEST: Engineering definition exists with 3 governing equations and a 9-step build plan. The next experiment is clearly specified. Target buyer: domain-appropriate technology buyer (to be identified by portfolio owner).

WHY WAIT: No physical prototype exists. Regulatory pathway is unresolved. IP ownership is unverified. Manufacturing process is not qualified.

WHY REJECT: killer experiment fails: falsification_test_from_candidate (decision scores: EIG 0.44573539382492045, EIG-per-cost 0.44573539382492045; the falsification test carries the pre-registered pass/fail before any transfer)

WHAT WOULD CHANGE THE DECISION: A successful bench experiment demonstrating the core mechanism. A qualified regulatory pathway. A confirmed IP position.

19. Kill Condition

KILL_IF: killer experiment fails: falsification_test_from_candidate (decision scores: EIG 0.44573539382492045, EIG-per-cost 0.44573539382492045; the falsification test carries the pre-registered pass/fail before any transfer)

DISCLOSURE

This dossier distinguishes established evidence, external precedent, computational/modelled results, engineering proposals, and unresolved questions. The absence of physical validation should not be interpreted as evidence that the technology will fail; it means the relevant proposition has not yet been established experimentally.

This dossier does not constitute legal, patentability, FTO, regulatory, or investment advice.