

Test Order/Report No.: BVIPL: RECYCLED COARSE AGGREGATE/43451A/416/9/2024 Date of Issue : 24-09-2024
JOB ID No. : 2024/Sept/43451A-(UIN-19012721) Date of Receipt : 30-09-2024

Page 1 of 1

Issued to: Indo Envio Integrated Solutions (P) Limited
C&D Plant Shastri Park,
Delhi-100053

TEST REPORT ON RECYCLED FINE AGGREGATE – 3-10MM

Source of Sample : C&D Waste Processing Plant, Shastri Park, New Delhi
No. of Samples : 03 (Three)
Condition of Sample : Satisfactory
Sample Drawn by : BV Representative in presence of IEISPL
Sample Identification : SHP/3/9 R1.3
Grade/Type : Not Furnished
Brand : Not Furnished
Period of Test : 24.09.2024 to 30.09.2024

Physical Test-(Building Material)

S. No.	Test Conducted	Results			Requirement as per IS:383-2016 for single size RA of nominal size 10mm	Test Method
		SHP 3/9 R1.3.1	SHP 3/9 R1.3.2	SHP 3/9 R1.3.3		
1.	Sieve Analysis, % passing, IS : Sieve Size					
a.	12.5 mm	100	100	100	100	IS:2386 (Part-1) 1963
b.	10.0 mm	100	100	100	85-100	
c.	4.75 mm	80.4	78.6	33.2	0-20	
d.	2.36 mm	38.4	35.8	40.2	0-5	
2.	Aggregate Crushing Value, %	34.8	34.3	35.6	30% max. of wearing surfaces	IS:2386 (Part-4) 1963
3.	Aggregate Abrasion Value, %	38.2	37.9	39.4	30% max. of wearing surfaces	
4.	Specific Gravity	2.36	2.34	2.40	2.1-3.2	IS:2386 (Part-3) 1963
5.	Water Absorption, % by wt	5.4	4.8	4.6	10.0 Max	IS:2386 (Part-1) 1963
6.	Combined Flakiness & Elongation, %	38.8	38.0	38.7	40.0 Max	IS:2386 (Part-1) 1963
7.	Soundness (after 5 cycles), %					IS:2386 (Part-5) 1963
a.	With Sodium Sulphate (Na ₂ SO ₄)	3.9	3.8	3.8	12.0 Max	
8.	Deleterious Material, %					
a.	Material finer than 75 micron, %	0.7	0.7	0.8	1.00 Max	IS:2386 (Part-1) 1963
b.	Coal & Lignite % by Wt.	0.3	0.4	0.2	1.00 Max	IS:2386 (Part-2) 1963
c.	Clay Lumps, % by Wt.	0.8	0.8	0.7	1.00 Max	
d.	Total Deleterious Material	1.10	1.20	0.90	2.00 Max	IS:2386 (Part-3) 1963
9.	Bulk Density, kg/m ³	1380	1425	1400	-	IS:2386 (Part-2) 1963
10.	Moisture Content, % by wt.	3.2	3.6	3.9	-	IS:2386 (Part-2) 1963
11.	Organic Impurities	Passes the test			-	IS:2386 (Part-2) 1963

- Note :**
1. The result relates only to the sample tested.
 2. Report shall not be reproduced, except in full, without the written approval of the lab.
 3. The report shall be read in line with the disclaimer given
 4. Any corrections invalidate this report

For BUREAU VERITAS (INDIA) PRIVATE LIMITED
Construction Service Laboratory


Authorised Signator
(Mechanical)

