

PRODICONSEIL

9 PROMENEE JEANNE HACHETTE
94 200 IVRY SUR SEINE
FRANCE



N°154

www.prodi.com

FICHE TECHNIQUE

1. QUALITE KRAFT SEMI EXTENSIBLE

Caractéristiques :

- Grammage de 70 – 120 g /m²
- kraft naturel 2faces Mat
- Résistances mécaniques élevées
- Apte au contact alimentaire
- Kraft Non apprêté

Avantages :

- Recommandé pour la fabrication de sacs de moyenne et grande contenance
- Présente un traitement de résistance à l'état humide élevé
- Utilisation est recommandée pour l'ensachage de produits

Tehnelical Data Sheet					PM - 4	
NH Sx – Semi Extensible Sack Kraft Paper						
Properties	Units	Test method		Typical values		
Basis weight	g/m²	ISO 536		70 ±3%	80 ±3%	90 ±3%
Tensile Strength	kN/m	ISO 1924-3	MD	5,2	6,0	6,8
			CD	4,1	4,6	5,2
Stretch	%	ISO 1924-3	MD	6,5±0,5	6,5±0,5	6,5±0,5
			CD	7,5±0,5	7,5±0,5	7,5±0,5
TEA	J/m2	ISO 1924-3	MD	200	230	260
			CD	200	230	260
TEA Index	J/g	ISO 1924-3	MD	2,9	2,9	2,9
			CD	2,9	2,9	2,9
Tear Index	mNm²/g	ISO 1974	MD	10	10	10,5
			CD	11	11	11,5
Cobb ₆₀	g/m²	ISO 535		32	32	32
Gurley	s	ISO 5636/5		15±5	15±5	15±5
Moisture	%	ISO 287		6,0±1	6,0±1	6,0±1
Test conditions : 50 ± 2% RH; 23 ± 1°C (ISO 187) Valid from 01.01.2014. onwards						

The table above shows typical values

Comments :

Above Technical Specifications are for guide lines. For any specific requirement please contact us for suggestions.
Different TEA and stretch is possible within certain limits if so required by the customer .

Rev/Date 01.01.2014.	PREPARED BY	COORDINATED BY	APPROVED BY
	HEAD OF QUALITY CONTROL DEPARTMENT	PRODUCTION MANAGER	EXECUTIVE DIRECTOR

CERTIFICATION F.C.