

1 Board structure

		% of total board	+/- in % of total	
	Multiple pigment coating			
	Printed PIW + Bleached chemical pulp + Unprinted PIW	Virgin fibre	25	10
	Printed PIW + Mechanical pulp + PCW + Unprinted PIW	PIW	45	10
		PCW	15	5
		Pigment coating	15	5
	Bleached chemical pulp + Unprinted PIW	Total	100	
	Functional barrier			
	Pigmentation			

2 Technical specifications

Grammage	Caliper	Stiffness				
		L&W 5° md	L&W 5° cd	L&W	Taber 15° md	Taber 15° cd
		mNm	mNm	$\sqrt[3]{(md \times cd)}$	mNm	mNm
g/m ²	µm					
280	395	24.5	11.1	16.5	13.0	5.8
300	435	32.0	14.6	21.6	15.7	7.2
320	465	39.3	17.9	26.5	19.3	8.8
350	510	49.7	22.6	33.5	24.4	11.1
375	550	60.4	25.2	39.0	29.6	12.4
400	585	70.5	29.4	45.5	36.0	15.0
425	625	84.4	35.2	54.5	41.4	17.3

Property	Value	Tolerances	Test standard
Brightness top (% Elrepho)	83	- 2	ISO 2470-2
Grammage (g/m ²)		+/- 2%	EN ISO 536
Caliper (µm)		+/- 5%, > 350 g/m ² +/- 3%	EN 20534
Stiffness (mNm)		- 15% ¹	DIN 53121
Testing climate	23°C	+/- 1°C	EN ISO 186
	50%	+/- 2% rh	