

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



FICHE TECHNIQUE DU CARTON GRIS / GRIS BOUFFANT GK
BOOKBINDING BOARD BULKY GK TECHNICAL SHEET

Grammage Weight	Epaisseur Caliper	Micron Bulk	Rigidité / Stiffness				
			L+W 5°		$\frac{L+W}{(mdxcd)}$	Taber 15°	
			md	cd		md	cd
g/m ²	µm	cm ³ /g	mNm	mNm		mNm	mNm
890	1400	1.57	543.1	196.0	317.8		
940	1500	1.60	585.2	203.9	345.4		
990	1600	1.62	660.4	231.1	390.7		
1040	1700	1.63	760.8	265.7	449.6		
1090	1800	1.65	884.2	310.2	523.7		
1140	1900	1.67	979.9	350.2	585.8		
1200	2000	1.67	1113.0	399.1	666.5		
1250	2100	1.68	1197.6	445.2	730.2		
1300	2200	1.69	1282.3	491.4	793.8		
1360	2300	1.69	1389.5	531.6	859.5		
1410	2400	1.70	1536.2	597.2	957.8		
1480	2500	1.69	1629.0	639.2	1020.4		
1510	2600	1.72	163.7	676.0	1050.9		
1560	2700	1.73	1735.3	734.3	1128.8		
1580	2800	1.77	1774.3	774.8	1172.5		
1590	2900	1.82	1837.5	824.0	1172.5		
1600	3000	1.88	1850.0	880.0	1275.9		

Brillance / Brightness	N/A
Méthode d'essai / Testing method	Tolérances / Tolerances
Echantillonnage / Sampling: EN ISO 186	Temperature d'essai/ Testing climate: 23 + / - 1° C 50 + / - 2% rF/hr
Grammage / Weight: EN ISO536	- 2% / + 2%
Raideur / Stiffness: DIN 53121	- 15%
Epaisseur / Caliper: EN 20534	+ / - 5%
Micron / Bulk:	+ / - 5%