

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°F087

FICHE TECHNIQUE DU CARTON TRIPLEX BLANC DOS CREME GT2
WHITE BACK LIGHT TRIPLEX BOARD GT2 TECHNICAL SHEET

Grammage Weight	Epaisseur Caliper	Micron Bulk	Rigidité / Stiffness				
			L+W 5°		$L + W$ $(md \times cd)$	Taber 15°	
			md	cd		md	cd
g/m ²	μm	cm ³ /g	mNm	mNm		mNm	mNm
250	310	1.24	15.8	5.3	9.2	9.0	3.0
300	380	1.27	28.2	9.7	16.5	16.0	5.5
350	440	1.26	40.2	14.2	23.9	22.9	8.1
400	500	1.25	57.3	20.5	34.3	30.9	11.0
450	570	1.27	80.9	29.5	48.9	43.7	15.9
500	640	1.28	103.0	38.3	62.8	55.6	20.7
600	770	1.28	169.1	64.0	104.0	86.2	32.6

Brillance / Brightness	81 - 1 / + 1% Elrepho (DS)
Méthode d'essai / Testing method	Tolérances / Tolerances
Echantillonnage / Sampling: EN ISO 186	Temperature d'essai/ Testing climate: 23 + / - 1° C 50 + / - 2% rF/hr
Grammage / Weight: EN ISO536	- 2% / + 2%
Raideur / Stiffness: DIN 53121	- 15%
Epaisseur / Caliper: EN 20534	+ / - 5%
Micron / Bulk:	+ / - 5%