

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°F087

FICHE TECHNIQUE DU CARTON GRIS / GRIS DEMI-GLOSS GK
GREYBOARD MEDIUM GLOSSED GK TECHNICAL SHEET

Grammage Weight	Epaisseur Caliper	Micron Bulk	Rigidité / Stiffness				
			L+W 5°		$\frac{L+W}{(mdxcd)}$	Taber 15°	
			md	cd		md	cd
g/m ²	µm	cm ³ /g	mNm	mNm		mNm	mNm
300	420	1.40	24.6	7.5	13.6	13.8	4.2
350	480	1.37	37.2	11.4	20.6	20.8	6.4
400	540	1.35	54.9	17.3	30.8	30.7	9.7
450	620	1.38	72.8	24.0	41.8	40.8	13.4
500	690	1.38	96.6	32.6	56.1	54.1	18.2
550	760	1.38	130.0	45.7	77.1	72.8	23.3
600	830	1.38	153.7	54.5	91.5	86.1	30.5
700	1010	1.44	221.4	77.2	130.7		
800	1190	1.49	332.6	113.1	194.0		
900	1330	1.48	451.0	154.9	264.3		
1000	1480	1.48	575.6	197.2	336.9		
1100	1620	1.47	763.8	263.0	448.2		
1200	1760	1.47	907.2	314.4	534.1		

Brillance / Brightness	N/A
Méthode d'essai / Testing method	Tolérances / Tolerances
Echantillonnage / Sampling: EN ISO 186	Temperature d'essai / Testing climate: 23 + / - 1° C 50 + / - 2% rF/hr
Grammage / Weight: EN ISO536 Raideur / Stiffness: DIN 53121 Epaisseur / Caliper: EN 20534 Micron / Bulk:	- 2% / + 2% - 15% + / - 5% + / - 5%