

9 promenade Jeanne Hachette  
94200 Ivry sur Seine - FRANCE  
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°F087

**FICHE TECHNIQUE DU CARTON LINER**  
**LINER BOARD TECHNICAL SHEET**

| Grammage<br>Weight | Epaisseur<br>Caliper | Micron<br>Bulk     | Rigidité / Stiffness |     |                             |           |     |
|--------------------|----------------------|--------------------|----------------------|-----|-----------------------------|-----------|-----|
|                    |                      |                    | L+W 5°               |     | $L + W$<br>$(md \times cd)$ | Taber 15° |     |
|                    |                      |                    | md                   | cd  |                             | md        | cd  |
| g/m <sup>2</sup>   | μm                   | cm <sup>3</sup> /g | mNm                  | mNm |                             | mNm       | mNm |
| 180                | 200                  | 1.11               | 4.0                  | 1.9 | 2.8                         | 2.3       | 1.1 |
| 210                | 240                  | 1.14               | 6.1                  | 2.9 | 4.2                         | 3.4       | 1.6 |
| 230                | 260                  | 1.13               | 8.0                  | 3.8 | 5.5                         | 4.6       | 2.2 |
| 250                | 280                  | 1.12               | 10.5                 | 5.0 | 7.3                         | 5.7       | 2.7 |

|                                                                                                                   |                                                                             |
|-------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------------------|
| Brillance / Brightness                                                                                            | 83 - 1 / + 1% Elrepho (DS)                                                  |
| Méthode d'essai / Testing method                                                                                  | Tolérances / Tolerances                                                     |
| Echantillonnage / Sampling: EN ISO 186                                                                            | Temperature d'essai/ Testing climate:<br>23 + / - 1° C    50 + / - 2% rF/hr |
| Grammage / Weight: EN ISO536<br>Raideur / Stiffness: DIN 53121<br>Epaisseur / Caliper: EN 20534<br>Micron / Bulk: | - 2% / + 2%<br>- 15%<br>+ / - 5%<br>+ / - 5%                                |