

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



FICHE TECHNIQUE DU PAPIER

JOURNAL BLANC 72

WHITE NEWSPRINT PAPER 72

TECHNICAL SHEET

N°122

CATEGORIE CATEGORY	Papier offset en continu sans sécheur <i>Coldset web offset papers</i>	GRADE	Machine finished speciality (MFS)
UTILISATION FINALE END USE	Publicité, Encarts de presses, Journaux, Envois direct, Magazines <i>Advertising material, Newspaper inserts, Newspapers, Direct mailing, Magazines</i>	FINISH	Matt
FIBRE FURNISH	Pâte mécanique, Recyclage <i>Mechanical pulp, Recycled fibre</i>	METHODE D'IMPRESSION PRINTING METHOD	Papier offset en continu sans sécheur, Flexo, Typographie <i>Coldset web offset papers, Flexo, Letterpress</i>
FORMAT SIZE	Bobines <i>Reels</i>	DIAMETRE (cm) DIAMETER	90.0 - 150.0
LAIZE (cm) WIDTH	22.5 – 380.0	MANDRIN (mm) CORE	76.0 - 150.0
EMBALLAGE WRAPPING	Strong kraft paper, Strong moisture proof polythylene laminated kraft paper	CERTIFICATS ET LABELS CERTIFICATES AND LABELS	EMAS, EN 16001, EU Ecolabel, FSC Chain-of-Custody, FSC Recycled, ISO 14001, ISO 50001, ISO 9001, OHSAS 18001, PEFC Chain-of-Custody

VALEURS TECHNIQUES TECHNICAL TARGETS VALUES

GRAMMAGE DISPO (ISO 536) BASIS WEIGHT (g/m2)	45.0	48.8	52.0	55.0
MICRON (ISO 534) BULK (cm3/g)	1.35	1.35	1.35	1.35
BLANCHEUR D65 (ISO 2470 - 2) BRIGHTNESS D65 (%)	72.0	72.0	72.0	72.0
OPACITE (ISO 2471) OPACITY (%)	92.0	93.0	94.0	95.0
RUGOSITE BENDTSEN (ISO 8791-2) ROUGHNESS BENDTSEN (ml/min)	130.0 - 210.0	130.0 - 210.0	130.0 - 210.0	130.0 - 210.0
L-VALUE C/2°	89.0	89.0	89.0	89.0
a-VALUE C/2°	(-)0.1 / 0.2	(-)0.1 / 0.2	(-)0.1 / 0.2	(-)0.1 / 0.2
b-VALUE C/2°	(-)4.0 / (-) 1.4	(-)4.0 / (-) 1.4	(-)4.0 / (-) 1.4	(-)4.0 / (-) 1.4