

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



FICHE TECHNIQUE DU PAPIER

LWC DEMI-MATT

SEMI MATT LWC TECHNICAL SHEET

N°122

PAPIER LWC DEMI-MATT
SEMI MATT LWC PAPER

CATEGORIE CATEGORY	Papiers Heliogravure Rotogravure Papers	GRADE	LIGHTWEIGHT COATED (LWC)
UTILISATION FINALE END USE	Publicité, Catalogues, Envois direct, Magazines Advertising material, Catalogues, Direct mailing, Magazines	FINISH	Satin Satin
FIBRE FURNISH	Pâte chimique, Pâte mécanique, DIP Chemical pulp, Mechanical pulp, DIP	METHODE D'IMPRESSIO N PRINTING METHOD	Héliogravure Rotogravure
FORMAT SIZE	Bobines Reels	DIAMETRE (cm) DIAMETER	100.0 - 135.0
LAIZE (cm) WIDTH	50.0 – 432.0	MANDRIN (mm) CORE	76.0 - 150.0
CERTIFICATS ET LABELS CERTIFICATES AND LABELS	EMAS, EN 16001, EU Ecolabel, FSC Chain-of-Custody, FSC Recycled, ISO 14001, ISO 9001, OHSAS 18001, PEFC Chain-of-Custody		

<i>VALEURS TECHNIQUES</i> <i>TECHNICAL TARGETS VALUES</i>
--

GRAMMAGE DISPO (ISO 536) BASIS WEIGHT (g/m2)	57.0	65.0	75.0
MICRON (ISO 534) BULK (cm3/g)	1.00	1.00	1.00
BLANCHEUR D65 (ISO 2470 - 2) BRIGHTNESS D65 (%)	84.0	84.0	84.0
OPACITE (ISO 2471) OPACITY (%)	93.0	96.0	95.0
LISSAGE PPS (ISO 8791-4) SMOOTHNESS PPS (µm)	1.1	1.1	1.1
L-VALUE C/2°	93.0	93.0	93.0
a-VALUE C/2°	0.6	0.6	0.6
b-VALUE C/2°	(-) 3.5	(-) 3.5	(-) 3.5
SATINE (ISO 8254-1) GLOSS HUNTER (%)	31.0	31.0	31.0