

9 promenade Jeanne Hachette
 94200 Ivry sur Seine - FRANCE
 Tel : 33 1 46720369 - Fax : 33 1 4959 8731



FICHE TECHNIQUE DU PAPIER

MWC BRILLANT

GLOSSY MWC TECHNICAL SHEET

N°122

PAPIER MWC BRILLANT
GLOSSY MWC PAPER

CATEGORIE CATEGORY	Impression sur rotative offset Heatset web offset papers	GRADE	Medium weight coated (MWC)
UTILISATION FINALE END USE	Publicité, Envois direct, Magazines, Livres, Brochures, Catalogues, Magazines haute qualité Advertising material, Direct mailing, Magazines, Books, Brochures Catalogues, High- quality magazines	FINISH	Brillant Glossy
FIBRE FURNISH	Pâte chimique, Pâte mécanique, Couleur de couche Chemical pulp, Mechanical pulp, Coating colour	METHODE D'IMPRESSI ON PRINTING METHOD	Impression sur rotative offset Heatset web offset papers
FORMAT SIZE	Bobines Reels	DIAMETRE (cm) DIAMETER	80.0 – 150.0

LAIZE (cm) WIDTH	36.0 – 432.0	MANDRIN (mm) CORE	76.0 – 150.0
EMBALLAGE WRAPPING	Strong kraft paper, Strong moisture proof polythylene laminated kraft paper	CERTIFICA TS ET LABELS CERTIFICA TES AND LABELS	Bfr Food Certificate, EMAS, EN 16001, EU Ecolabel, FSC Chain-of-Custody, FSC Recycled, ISO 14001, ISO 9001, OHSAS 18001, PEFC Chain-of- Custody

VALEURS TECHNIQUES
TECHNICAL TARGETS
VALUES

GRAMMAGE DISPO (ISO 536) BASIS WEIGHT (g/m2)	60.0	65.0	70.0	75.0	80.0	90.0	100.0
MICRON (ISO 534) BULK (cm3/g)	0.80	0.80	0.80	0.80	0.80	0.80	0.80
BLANCHEUR D65 (ISO 2470 - 2) BRIGHTNESS D65 (%)	89.0	91.0	93.0	94.0	95.0	96.0	96.0
BLANCHEUR CIE (%) CIE WHITENESS	106.0	110.0	115.0	117.0	120.0	122.0	122.0
OPACITE (ISO 2471) OPACITY (%)	90.0	92.0	93.0	94.0	95.0	96.0	96.0
LISSAGE PPS (ISO 8791-4) SMOOTHNESS PPS (µm)	1.0	1.0	1.0	1.0	0.9	0.9	0.9
L-VALUE C/2°	93.0	93.0	93.0	94.0	94.0	94.0	94.0

Feuille1

a-VALUE C/2°	0.9	1.0	1.2	1.2	1.2	1.4	1.4
b-VALUE C/2°	(-)6.0	(-)6.0	(-)7.0	(-)7.5	(-)7.5	(-)8.0	(-)8.0
SATINE (ISO 8254-1) GLOSS HUNTER (%)	62.0	65.0	65.0	68.0	70.0	70.0	70.0