

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731

REF 160

FICHE TECHNIQUE DU CARTON DUPLEX BLANC DOS BLANC GC1
WHITE BACK COATED DUPLEX BOARD GC1 TECHNICAL SHEET

Property / Unit	Tolerance									Standards
Grammage, g/m ²	±4%	360	385	410	435	460	485	510	560	ISO 536
Thickness, µm	±5%	580	640	690	740	800	855	910	1000	ISO 534
Molsture, %	±1.5	8.5	9.0	9.0	9.0	9.0	9.5	9.5	9.5	ISO 287
Bending moment Taber 15° MD, mNm	-15%	39.9	46.8	55.7	65.3	74.9	85.8	97.6	123.8	ISO 2493
Bending moment Taber 15° CD, mNm	-15%	18.1	21.3	25.3	29.7	34.1	39.0	44.4	56.3	

Properties not related to grammage			
Property / Unit	Tolerance	Values	Standards
ISO Brightness C/2°, %, top	±1.5	85	ISO 2470-1
ISO Brightness C/2°, %, reverse	±1.5	80	ISO 2470-1
Colour CIELAB L * C/2°, top		93.5	ISO 5631-1
Colour CIELAB a * C/2°, top		0.7	ISO 5631-1
Colour CIELAB b * C/2°, top		0.5	ISO 5631-1
Surface Smoothness, PPS 10, µm	±0.3	1.0	ISO 8791-4
Smoothness Bendtsen, top, ml/min		40	ISO 7891-2
Gloss 75°, %	>40	40	ISO 8254-1
Scott Bond, J/m ²	>110	110	TAPPI 569