

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731

REF 160

FICHE TECHNIQUE DU CARTON DUPLEX BLANC DOS CREME GC2
CREAM BACK COATED DUPLEX BOARD GC2 TECHNICAL SHEET

Property / Unit	Tolerance												Standards
Grammage, g/m ²	±4%	275	300	325	350	375	400	425	450	475	500	550	ISO 536
Thickness, µm	±5%	460	510	560	610	670	720	770	830	885	940	1030	ISO 534
Moisture, %	±1.5	8.5	8.5	8.5	8.5	9.0	9.0	9.0	9.0	9.5	9.5	9.5	ISO 287
Bending moment Taber 15° MD, mNm	-15%	20.0	26.3	32.5	39.5	46.4	55.4	65.1	74.8	86.5	97.6	123.9	ISO 2493
Bending moment Taber 15° CD, mNm	-15%	8.8	12.1	14.9	17.9	21.1	25.2	29.5	33.9	39.1	44.1	55.9	

Properties not related to grammage

Property / Unit	Tolerance	Values	Standards
ISO Brightness C/2°, %, top	±1.5	85	ISO 2470-1
Colour CIELAB L * C/2°, top		93.5	ISO 5631-1
Colour CIELAB a * C/2°, top		0.7	ISO 5631-1
Colour CIELAB b * C/2°, top		0.5	ISO 5631-1
Surface Smoothness, PPS 10, µm	±0.3	1.0	ISO 8791-4
Gloss 75°, top %	>40	40	ISO 8254-1
Scott Bond, J/m ²	>110	110	TAPPI 569