

STANDARD TECHNICAL CONDITIONS

Extensible sack kraft paper

TD-CZOO-12-03-13-P

Technical specification

PARAMETER			UNIT	PARAMERER VALUE			TEST METHOD
Basis weight			g/m^2	70	80	90	PN-ISO 536
Tolerance			g/m^2	$\pm 2,5$	$\pm 2,5$	$\pm 3,0$	
Tensile strength index	MD	typical min	Nm/g	72 62	72 62	72 62	PN-EN ISO 1924-3
	CD	typical min		53 43	53 43	53 43	
Tensile strength	MD	typical min	kN/m	5,0 4,3	5,7 4,9	6,4 5,5	
	CD	typical min		3,7 3,0	4,2 3,4	4,7 3,9	
Strain at break	MD	typical min	%	7,4 6,5	7,4 6,5	7,4 6,5	
	CD	typical min		7,4 6,5	7,4 6,5	7,4 6,5	
Tensile Energy Absorption (TEA) index	MD	typical min	J/g	3,1 2,6	3,1 2,6	3,1 2,6	
	CD	typical min		2,9 2,4	2,8 2,3	2,8 2,3	
Tensile Energy Absorption (TEA)	MD	typical min	J/m^2	224 182	248 208	279 234	
	CD	typical min		203 168	224 184	252 207	
Air permeability, Gurley		max	s	18			PN-92/P-50176/05 (idt. ISO 5636-5)
Water absorption, Cobb ₆₀		max	g/m^2	32			PN-ISO 535
Moisture			%	7,5 $\pm$ 1,5			PN-ISO 287

Measure conditions: relative moisture $50 \pm 2\%$; temperature $23 \pm 1^\circ\text{C}$ (PN-EN 20187)
 Minimal values are guaranteed.