



Technical specification

Certified according to ISO 9001 / ISO 14001

Test climate 23°C, 50 % relative humidity, DIN EN 20 187
All rights to improve quality due to technical modifications reserved

Form number: AA-PQM-029-01/A 09/2015

Revision: H 01/2016 ersetzt G 05/10

Property	Unit	Standard	Target value										Tolerance
Grammage	g/m²	DIN ISO 536	160.0	220.0	240.0	270.0	300.0	330.0	350.0	380.0	400.0	± 5.0%	
Thickness	µm	DIN EN 20534	181.0	255.0	281.0	323.0	365.0	405.0	435.0	470.0	495.0	± 5.0%	
Bending force (15°/50 mm) MD	mN	ISO 5628 2493	35.0	110.0	160.0	220.0	300.0	400.0	460.0	520.0	600.0	± 15.0%	
Bending force (15°/50 mm) CD	mN	ISO 5628 2493	15.0	55.0	80.0	115.0	160.0	205.0	230.0	250.0	280.0	± 15.0%	
Bending moment (15°) MD	mNm	Taber T489- om-92	1.7	5.3	7.7	10.5	14.5	19.3	22.2	25.6	29.0	± 15.0%	
Bending moment (15°) CD	mNm	Taber T489- om-92	0.7	2.6	3.9	5.6	7.7	9.9	11.4	13.0	15.5	± 15.0%	
Bending stiffness (5°/50 mm) MD	mNm	DIN 53121	3.0	9.7	13.0	18.0	27.0	37.0	43.0	52.0	61.0	Reference value	
Bending stiffness (5°/50 mm) CD	mNm	DIN 53121	1.5	4.7	6.5	9.2	14.0	19.0	23.0	26.0	30.0	Reference value	
Whiteness (R457) coated side	%	ISO 2470	101.5									± 1.5	
Whiteness (CIE) coated side	%	ISO 11475	132.0									Reference value	
L-value coated side	%	ISO 5631	95.50									± 1.00	
a-Value coated side	-	ISO 5631	2.00									± 0.30	
b-Value coated side	-	ISO 5631	-9.00									± 1.00	
Whiteness (R457) uncoated side	%	ISO 2470	98.0									± 1.5	
b-value uncoated side	-	ISO 5631	-8.00									± 1.00	
Surface roughness coated side	µm	ISO 8791/4	1.8									± 0.6	
Moisture content abs.	%	DIN EN 20 287	5.5									± 1.0	