

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



FICHE TECHNIQUE KRAFTLINER BLANC DOS BRUN TECHNICAL SHEET FOR WHITE TOP LINER BOARD

REF 262

White Top Linerboard

Nominal Basis Weight		<i>lbs./msf.</i>	26	27	29	31	33		42	
			127	132	142	151	161	186	205	337
Conditioned Basis Weight	<i>Min</i>	<i>lbs./msf.</i>	24.5	25.6	27.4	29.4	31.3	36.1		
	<i>Max</i>	<i>lbs./msf.</i>			30.5	32.9	35.9			
	<i>Min</i>	<i>g/m²</i>	119.6	125.0	133.8	143.5	152.8		194.8	319.8
	<i>Max</i>		141.6	138.6	148.9	160.6	175.3	204.6	224.1	353.9
Moisture	<i>Min</i>	<i>percent</i>		4.5	4.5	4.5	4.5	4.5		
	<i>Max</i>						7.5	7.5	7.5	
Roll Caliper Variation	<i>Min</i>	<i>inches</i>	+/-0.0015	+/-0.0015	+/-0.0015	+/-0.001	+/-0.001			
	<i>Max</i>	<i>inches</i>	+/-0.0015							
Mullen	<i>Min</i>	<i>psi</i>					72.0	84.0	95.0	128.0
		<i>kPa</i>		392.7	434.1	461.6	496.1			
Brightness	<i>Min</i>	<i>% reflectance ISO</i>							70.5	
	<i>Max.</i>		74.5	74.5	74.5	74.5	74.5	74.5	74.5	74.5
Scuff	<i>Min</i>	<i>(by position)</i>	15.0	15.0	15.0	15.0	15.0			
Porosity			15.0	15.0	15.0	15.0	15.0	15.0	15.0	15.0
Slip Angle	<i>Min</i>		18.0	18.0	18.0	18.0	18.0			18.0
Cobb, Top (30 minute)	<i>Max.</i>		155.0	155.0	155.0	155.0	155.0	155.0	155.0	155.0
Smoothness	<i>Max</i>	<i>Emveco</i>		90.0	90.0		80.0		80.0	85.0
Color A				0.3	0.3	0.3	0.3			
Color B	<i>Min</i>									
	<i>Max</i>			1.5	1.5	1.5	1.5			
Moisture 2 Sigma	<i>Max</i>	<i>CD</i>	1.4	2.5	2	2	7			
	<i>Max</i>	<i>MD</i>					2.5			2.5
Mottle	<i>Min</i>		45.0	45.0	45.0	45.0	45.0	45.0	45.0	
	<i>Max</i>					95.0				