

1 Board structure

	Multiple pigment coating	% of total board	+/- in % of total	
	Printed PIW + PCW + Unprinted PIW	Virgin fibre	15	5
	PIW	PIW	20	10
	Mechanical pulp + PCW	PCW	55	10
		Pigment coating	10	5
	BCTMP + Bleached chemical pulp + Unprinted PIW	Total	100	
	Pigmentation			

2 Technical specifications

Grammage	Caliper	Stiffness				
		L&W 5° md	L&W 5° cd	L&W	Taber 15° md	Taber 15° cd
		mNm	mNm	$\sqrt[3]{(\text{md} \times \text{cd})}$	mNm	mNm
230	305	10.1	4.6	6.8	5.4	2.5
250	340	15.4	7.0	10.4	7.5	3.4
280	380	20.9	9.5	14.1	10.8	4.9
300	410	25.0	11.4	16.9	13.2	6.0
320	435	31.8	13.3	20.6	16.2	6.8
350	490	43.0	17.2	27.2	20.6	7.8
380	540	54.6	21.9	34.6	25.3	10.1
400	565	61.8	24.8	39.1	28.2	11.3
420	590	70.6	28.3	44.7	32.5	13.0
450	625	78.7	31.5	49.8	37.9	15.2

Property	Value	Tolerances	Test standard
Brightness top (% Elrepho)	82	- 1	ISO 2470-2
Brightness reverse (% Elrepho)	68	+/- 2	ISO 2470-2
Grammage (g/m ²)		+/- 2%	EN ISO 536
Caliper (µm)		+/- 5%, > 350 g/m ² +/- 3%	EN 20534
Stiffness (mNm)		- 15% ¹	DIN 53121
Testing climate	23°C	+/- 1°C	EN ISO 186
	50%	+/- 2% rh	