

1 Board structure

	Multiple pigment coating	% of total board	+/- in % of total	
	Printed PIW + PCW	Virgin fibre	10	5
	Mechanical pulp + PCW	PIW	20	10
		PCW	60	10
		Pigment coating	10	5
	BCTMP + Bleached chemical pulp + Unprinted PIW	Total	100	
	Pigmentation			

2 Technical specifications

Grammage	Caliper	Stiffness				
		L&W 5° md	L&W 5° cd	L&W	Taber 15° md	Taber 15° cd
		mNm	mNm	$\sqrt{(md \times cd)}$	mNm	mNm
230	300	8.6	3.9	5.8	5.0	2.3
250	320	12.0	5.4	8.0	6.4	2.9
280	365	17.1	7.8	11.5	8.8	4.0
300	390	22.1	10.1	14.9	11.0	5.0
320	420	28.5	11.4	18.0	14.2	5.7
350	450	36.3	14.5	22.9	18.1	7.3
380	500	44.3	17.8	28.1	22.5	9.0
400	530	52.6	21.1	33.3	25.0	10.0
420	560	59.9	24.0	37.9	27.9	11.2
450	600	72.9	29.2	46.1	33.6	13.5

Property	Value	Tolerances	Test standard
Brightness top (% Elrepho)	78	- 1	ISO 2470-2
Grammage (g/m ²)		+/- 2%	EN ISO 536
Caliper (µm)		+/- 5%, > 350 g/m ² +/- 3%	EN 20534
Stiffness (mNm)		- 15% ¹	DIN 53121
Testing climate	23°C	+/- 1°C	EN ISO 186
	50%	+/- 2% rh	