

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°F087

FICHE TECHNIQUE DU CARTON GRIS / GRIS ARGENT GK
SILVER GREY BOARD GK TECHNICAL SHEET

Grammage Weight	Epaisseur Caliper	Micron Bulk	Rigidité / Stiffness				
			L+W 5°		$\sqrt{\frac{L+W}{md \times cd}}$	Taber 15°	
			md	cd		md	cd
g/m ²	µm	cm ³ /g	mNm	mNm		mNm	mNm
250	360	1,44	15.0	6.0	9.5	8.3	3.3
300	410	1,37	21.5	9.0	13.9	12.2	5.3
350	490	1.40	34.0	14.0	21.8	18.6	8.3
400	560	1.40	49.0	20.5	31.7	27.2	11.9
450	640	1.42	69.0	30.0	45.5	36.3	15.8
500	720	1.44	91.5	40.5	60.9	49.5	21.1
550	790	1.44	125.0	54.0	82.2	64.7	27.4
600	860	1.43	157.0	67.5	102.9	82.6	34.7

Brillance / Brightness	N/A
Méthod d'essai / Testing method	Tolérances / Tolerances
Echantillonnage / Sampling: EN ISO 186	Temperature d'essai/ Testing climate: 23 + / - 1° C 50 + / - 2% rF/hr
Grammage / Weight: EN ISO536 Rigidité / Stiffness: DIN 53121 Epaisseur / Caliper: EN 20534 Micron / Bulk:	- 2% / + 2% - 15% + / - 5% + / - 5%