

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°F087

FICHE TECHNIQUE DU CARTON BLANC DOS CREME GC2
WHITE LIGHT BACK BOARD GC2 TECHNICAL SHEET

Grammage Weight	Epaisseur Caliper	Micron Bulk	Rigidité / Stiffness				
			L+W 5°		$L + W$ $(md \times cd)$	Taber 15°	
			md	cd		md	cd
g/m ²	μm	cm ³ /g	mNm	mNm		mNm	mNm
215	330	1.53	14.2	7.2	10.1	7.7	4.0
230	360	1.57	17.5	9.0	12.5	9.6	4.8
250	410	1.64	22.0	11.5	15.9	12.3	6.2
275	460	1.67	28.5	15.0	20.7	16.3	8.2
300	510	1.70	37.0	20.0	27.2	21.1	10.7
325	560	1.72	46.0	25.0	33.9	26.7	13.6
350	610	1.74	57.0	31.0	42.0	33.2	16.9
375	665	1.77	69.5	38.5	51.7	40.7	20.8
400	725	1.81	84.0	46.5	62.5	49.2	25.2
425	785	1.85	100.5	55.0	74.3	58.7	30.1
450	845	1.88	119.0	64.0	87.3	69.2	35.5
475	905	1.91	139.5	73.5	101.3	80.7	41.4
500	965	1.93	162.0	83.5	116.3	93.2	47.8

Brillance / Brightness	84 - 1 / + 1% Elrepho (DS)
Méthode d'essai / Testing method	Tolérances / Tolerances
Echantillonnage / Sampling: EN ISO 186	Temperature d'essai / Testing climate: 23 + / - 1° C 50 + / - 2% rF/hr
Grammage / Weight: EN ISO536	- 2% / + 2%
Rigidité / Stiffness: DIN 53121	- 15%
Epaisseur / Caliper: EN 20534	+ / - 5%
Micron / Bulk:	+ / - 5%