

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°F087

FICHE TECHNIQUE DU CARTON GRIS / GRIS BRILLIANT 1 FACE GK
GREYBOARD ONE SIDE GLOSSED GK TECHNICAL SHEET

Grammage Weight	Epaisseur Caliper	Micron Bulk	Rigidité / Stiffness				
			L+W 5°		$\frac{L+W}{(md \times cd)}$	Taber 15°	
			md	cd		md	cd
g/m ²	µm	cm ³ /g	mNm	mNm		mNm	mNm
250	340	1.36	17.0	4.2	8.4	9.5	2.4
300	410	1.37	30.5	8.1	15.7	17.5	4.5
350	460	1.31	38.5	11.0	20.6	21.6	6.2
400	510	1.28	50.3	15.7	28.1	28.2	8.8
450	580	1.29	66.6	22.0	38.3	37.3	12.3
500	640	1.28	87.7	30.6	51.8	49.1	17.1
550	700	1.27	111.2	39.3	66.1	62.2	2.0
600	780	1.30	146.7	52.4	87.7	82.1	29.3
700	920	1.31	220.8	79.7	132.7		
800	1080	1.35	290.2	104.5	174.1		
900	1200	1.33	414.5	146.0	246.0		
1000	1340	1.34	505.2	180.4	301.9		
1100	1480	1.35	663.3	241.8	400.5		

Brillance / Brightness	N/A
Méthode d'essai / Testing method	Tolérances / Tolerances
Echantillonnage / Sampling: EN ISO 186	Temperature d'essai / Testing climate: 23 + / - 1° C 50 + / - 2% rF/hr
Grammage / Weight: EN ISO536 Raideur / Stiffness: DIN 53121 Epaisseur / Caliper: EN 20534 Micron / Bulk:	- 2% / + 2% - 15% + / - 5% + / - 5%