

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°F087

FICHE TECHNIQUE DU CARTON TRIPLEX BLANC DOS KRAFT GT4
WHITE KRAFT BACK TRIPLEX BOARD GT4 TECHNICAL SHEET

Grammage Weight	Epaisseur Caliper	Micron Bulk	Rigidité / Stiffness				
			L+W 5°		$\frac{L+W}{(md \times cd)}$	Taber 15°	
			md	cd		md	cd
g/m ²	μm	cm ³	mNm	mNm		mNm	mNm
250	330	1.3	19.6	19.6	12.2	10.9	4.2
280	380	1.36	27.0	27.0	17.1	15.0	6.0
300	410	1.37	32.0	32.0	19.8	16.8	6.5
350	470	1.34	46.6	46.6	29.0	24.5	9.5
400	545	1.36	71.8	71.8	44.4	36.8	14.1
450	605	1.34	101.0	101.0	61.1	51.5	19.0
500	670	1.34	130.0	130.0	78.2	65.0	23.5
550	760	1.38	130.0	50.0	80.6	64.0	24.5
600	83	1.38	160.0	62.0	99.6	78.0	29.0
650	900	1.38	200.0	72.0	120.0	98.0	34.0

Brillance / Brightness	79 - 1 / + 1% Elrepho (DS)
Méthod d'essai / Testing method	Tolérances / Tolerances
Echantillonnage / Sampling: EN ISO 186	Temperature d'essai/ Testing climate: 23 + / - 1° C 50 + / - 2% rF/hr
Grammage / Weight: EN ISO536	- 2% / + 2%
Rigidité / Stiffness: DIN 53121	- 15%
Epaisseur / Caliper: EN 20534	+ / - 5%
Micron / Bulk:	+ / - 5%