

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°F087

FICHE TECHNIQUE DU CARTON BLANC DOS BLANC GC1
WHITE BACK BOARD GC1 TECHNICAL SHEET

Grammage Weight	Epaisseur Caliper	Micron Bulk	Rigidité / Stiffness				
			L+W 5°		$\frac{L+W}{(md \times cd)}$	Taber 15°	
			md	cd		md	cd
g/m ²	μm	cm ³ /g	mNm	mNm		mNm	mNm
215	310	1.44	14.2	7.2	10.1	7.7	4.0
230	360	1.57	17.5	9.0	12.5	9.3	4.7
250	400	1.60	22.0	11.5	15.9	12.0	6.1
275	450	1.64	28.5	15.0	20.7	15.9	8.1
300	500	1.67	37.0	19.5	26.9	20.6	10.5
325	550	1.69	46.0	24.0	33.2	26.1	13.4
350	600	1.71	57.0	30.0	41.4	32.5	16.7
375	650	1.73	69.5	37.0	50.7	39.9	20.6
400	710	1.78	84.0	44.5	61.1	48.4	25.0
425	770	1.81	100.5	53.0	73.0	57.9	29.9
450	830	1.84	119.0	62.0	85.9	68.4	35.3
475	890	1.87	139.5	71.5	99.9	79.9	41.2
500	950	1.90	162.0	81.5	114.9	92.4	47.6

Brillance / Brightness	84 - 1 / + 1% Elrepho (DS)
Méthode d'essai / Testing method	Tolérances / Tolerances
Echantillonnage / Sampling: EN ISO 186	Temperature d'essai / Testing climate: 23 + / - 1° C 50 + / - 2% rF/hr
Grammage / Weight: EN ISO536 Raideur / Stiffness: DIN 53121 Epaisseur / Caliper: EN 20534 Micron / Bulk:	- 2% / + 2% - 15% + / - 5% + / - 5%