

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



FICHE TECHNIQUE DU PAPIER

JOURNAL SAUMON

SALMON NEWSPRINT PAPER

TECHNICAL SHEET

N°122

PAPIER JOURNAL SAUMON
SALMON NEWSPRINT PAPER

CATEGORIE CATEGORY	Offset en continu sans sécheur, Impression sur rotative offset Coldset web offset papers, Heatset web offset papers	GRADE	Journal Newsprint
UTILISATION FINALE END USE	Publicité, Encarts de presses, Journaux Advertising material, Newspaper inserts, Newspapers	FINISH	Matt
FIBRE FURNISH	Recyclage Recycled fibre	METHODE D'IMPRESSIO N PRINTING METHOD	Offset en continu sans sécheur, Flexo, Heatset web offset, Typographie Coldset web offset, Flexo, Heatset web offset, Letterpress
FORMAT SIZE	Bobines Reels	DIAMETRE (cm) DIAMETER	90.0 - 150.0
LAIZE (cm) WIDTH	33.0 – 210.0	MANDRIN (mm) CORE	76.0
EMBALLAGE WRAPPING	Strong kraft paper, Strong moisture proof polyethylene laminated kraft paper	CERTIFICATS ET LABELS CERTIFICATE S AND LABELS	EMAS, EU Ecolabel, FSC Chain-of-Custody, FSC Recycled, ISO 14001, ISO 9001, OHSAS 18001, PEFC Chain-of-Custody

VALEURS TECHNIQUES
TECHNICAL TARGETS VALUES

GRAMMAGE DISPO (ISO 536) BASIS WEIGHT (g/m²)	40.0	42.0	45.0	48.8	52.0
MICRON (ISO 534) BULK (cm³/g)	1.35	1.35	1.35	1.35	1.35
OPACITE (ISO 2471) OPACITY (%)	93.5	94.5	95.0	95.0	97.0
RUGOSITE BENDTSEN (ISO 8791-2) ROUGHNESS BENDTSEN (ml/min)	210.0	210.0	210.0	210.0	210.0
EPAISSEURS (ISO 534) THICKNESS (μm)	55.0	57.0	60.0	65.0	68.0
L-VALUE C/2°	80.9	80.9	80.9	80.9	80.9
a-VALUE C/2°	6.4	6.4	6.4	6.4	6.4
b-VALUE C/2°	19.0	19.0	19.0	19.0	19.0