

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE
Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°122

FICHE TECHNIQUE DU PAPIER

LWC BRILLANT PRODI 2

GLOSSY LWC PRODI 2

TECHNICAL SHEET

PAPIER LWC BRILLANT
GLOSSY LWC PAPER

CATEGORIE CATEGORY	Papiers héliogravure Rotogravure Papers	GRADE	Lightweight coated (LWC)
UTILISATION FINALE END USE	Publicité, Catalogues, Envois direct, Magazines Advertising material, Catalogues, Direct mailing, Magazines	FINISH	Brillant Glossy
FIBRE FURNISH	Pâte chimique, Pâte mécanique, Couleur de couche Chemical pulp, Mechanical pulp, Coating colour	METHODE D'IMPRESSIO N PRINTING METHOD	Héliogravure Rotogravure
FORMAT SIZE	Bobines Reels	DIAMETRE (cm) DIAMETER	80.0 - 150.0
LAIZE (cm) WIDTH	36.0 - 432.0	MANDRIN (mm) CORE	76.0 - 150.0

EMBALLAGE WRAPPING	Strong kraft paper, Strong moisture proof polythylene laminated kraft paper	CERTIFICATS ET LABELS CERTIFICATE S AND LABELS	EMAS, EN 16001, EU Ecolabel, FSC Chain-of-Custody, FSC Recycled, ISO 14001, ISO 9001, OHSAS 18001, PEFC Chain-of-Custody
-------------------------------	---	---	--

**VALEURS TECHNIQUES
TECHNICAL TARGETS
VALUES**

GRAMMAGE DISPO (ISO 536) BASIS WEIGHT (g/m2)	48.0	51.0	54.0	57.0	60.0	65.0	70.0	75.0	80.0	85.0
MICRON (ISO 534) BULK (cm3/g)	0.90	0.90	0.90	0.90	0.90	0.90	0.80	0.80	0.80	0.80
BLANCHEUR D65 (ISO 2470 - 2) BRIGHTNESS D65 (%)	78.0	79.0	79.0	81.0	82.0	86.0	86.0	86.0	86.0	87.0
OPACITE (ISO 2471) OPACITY (%)	89.0	90.0	90.0	90.0	91.0	92.0	93.0	94.0	95.0	95.0
LISSAGE PPS (ISO 8791-4) SMOOTHNESS PPS (µm)	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.8	0.9
L-VALUE C/2°	91.0	91.0	91.0	91.0	91.0	92.0	92.0	92.0	92.0	93.0
a-VALUE C/2°	0.0	0.0	0.0	0.3	0.3	0.3	0.3	0.3	0.3	0.6
b-VALUE C/2°	(-) 0.5	(-) 0.5	(-) 0.5	(-) 3.2	(-) 3.2	(-) 3.8	(-) 3.8	(-) 4.0	(-) 4.5	(-) 4.5
SATINE (ISO 8254-1) GLOSS HUNTER (%)	50.0	55.0	60.0	63.0	65.0	66.0	66.0	66.0	66.0	60.0