

9 promenade Jeanne Hachette
 94200 Ivry sur Seine - FRANCE
 Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°122

FICHE TECHNIQUE DU PAPIER **LWC BRILLANT PRODI 4** **GLOSSY LWC PRODI 4** **TECHNICAL SHEET**

PAPIER LWC BRILLANT
GLOSSY LWC PAPER

CATEGORIE CATEGORY	Impression sur rotative offset <i>Heatset web offset papers</i>	GRADE	Lightweight coated (LWC)
UTILISATION FINALE END USE	Publicité, Catalogues, Envois direct, Magazines, <i>Advertising material,</i> Catalogues, Direct mailing, Magazines	FINISH	Brillant <i>Glossy</i>
FIBRE FURNISH	Pâte chimique, Pâte mécanique, Couleur de couche, Charges <i>Chemical pulp,</i> <i>Mechanical pulp,</i> Coating colour, Fillers	METHODE D'IMPRESSI ON PRINTING METHOD	Impression sur rotative offset <i>Heatset web offset papers</i>

FORMAT SIZE	Bobines Reels	DIAMETRE (cm) DIAMETER	85.0 – 150.0
LAIZE (cm) WIDTH	35.0 – 400.0	MANDRIN (mm) CORE	76.0 – 150.0
EMBALLAGE WRAPPING	Strong kraft paper, Strong moisture proof polythylene laminated kraft paper	CERTIFICAT S ET LABELS CERTIFICAT ES AND LABELS	EMAS, EN 16001, EU Ecolabel, FSC Chain-of- Custody, FSC Recycled, ISO 14001, ISO 50001, ISO 9001, OHSAS 18001, PEFC Chain-of- Custody

*VALEURS TECHNIQUES
TECHNICAL TARGETS
VALUES*

GRAMMA GE DISPO (ISO 536) BASIS WEIGHT (g/m2)	35.0	36.0	39.0	42.0	45.0	48.0	51.0	54.0	57.0	60.0	65.0	70.0	80.0
MICRON (ISO 534) BULK (cm3/g)	1.00	1.00	1.00	1.00	0.90	0.90	0.90	0.90	0.80	0.80	0.80	0.80	0.80
BLANCHE UR D65 (ISO 2470 - 2) BRIGHTN ESS D65 (%)	66.0	67.0	68.0	69.0	70.0	70.0	71.0	72.0	73.0	74.0	75.0	78.0	78.0
OPACITE (ISO 2471) OPACITY (%)	85.0	86.0	86.0	87.0	89.0	89.0	90.0	91.0	92.0	92.0	93.0	94.0	95.0

LISSAGE PPS (ISO 8791-4) SMOOTH NESS PPS (µm)	1.7	1.7	1.7	1.6	1.5	1.5	1.4	1.3	1.2	1.2	1.2	1.2	1.2	
L-VALUE C/2°	88.0	88.0	88.0	88.0	88.0	89.0	89.0	89.0	90.0	90.0	90.0	91.0	91.0	
a-VALUE C/2°	(-)0.8	(-)0.8	(-)0.8	(-)0.8	(-)0.8	(-)0.8	(-)0.8	(-)0.8	(-)0.8	(-)0.8	(-)0.8	(-)0.7	(-)0.6	0.0
b-VALUE C/2°	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5	1.2	1.0	1.0
SATINE (ISO 8254- 1) GLOSS HUNTER (%)	37.0	37.0	39.0	42.0	45.0	46.0	50.0	52.0	56.0	60.0	60.0	60.0	60.0	60.0