

9 promenade Jeanne Hachette
94200 Ivry sur Seine - FRANCE

Tel : 33 1 46720369 - Fax : 33 1 4959 8731



N°122

FICHE TECHNIQUE DU PAPIER LWC MATT MATT LWC TECHNICAL SHEET

PAPIER LWC MATT
MATT LWC PAPER

CATEGORIE CATEGORY	Impression sur rotative offset Heatset web offset papers	GRADE	Lightweight coated (LWC)
UTILISATION FINALE END USE	Publicité, Envois direct, Magazines, Advertising material, Direct mailing, Magazines	FINISH	Brillant Gloss
FIBRE FURNISH	Pâte chimique, Pâte mécanique, Couleur de couche, Charges Chemical pulp, Mechanical pulp, Coating colour, Fillers	METHODE D'IMPRESSION PRINTING METHOD	Impression sur rotative offset Heatset web offset papers
FORMAT SIZE	Bobines Reels	DIAMETRE (cm) DIAMETER	100.0 – 150.0
LAIZE (cm) WIDTH	35.0 – 400.0	MANDRIN (mm) CORE	76.0 – 150.0

EMBALLAGE WRAPPING	Strong kraft paper, Strong moisture proof polyethylene laminated kraft paper	CERTIFICATS ET LABELS CERTIFICATES AND LABELS	Bfr Food Certificate, EMAS, EN 16001, EU Ecolabel, FSC Chain-of- Custody, FSC Recycled, ISO 14001, ISO 50001, ISO 9001, OHSAS 18001, PEFC Chain-of- Custody
-------------------------------	--	--	---

VALEURS TECHNIQUES
TECHNICAL TARGETS VALUES

GRAMMAGE DISPO (ISO 536) BASIS WEIGHT (g/m2)	51.0	54.0	57.0	60.0	65.0	70.0	80.0	90.0
MICRON (ISO 534) BULK (cm3/g)	1.00	1.00	1.00	1.00	1.00	1.00	1.00	1.00
BLANCHEUR D65 (ISO 2470 - 2) BRIGHTNESS D65 (%)	79.0	79.0	79.0	80.0	80.0	80.0	83.0	83.0
OPACITE (ISO 2471) OPACITY (%)	92.0	94.0	94.0	95.0	95.0	96.0	95.0	96.0
LISSAGE PPS (ISO 8791-4) SMOOTHNESS PPS (µm)	2.5	2.5	2.5	2.5	2.5	2.5	2.5	2.5
L-VALUE C/2°	90.0	90.0	90.0	90.0	90.0	90.0	92.0	92.0
a-VALUE C/2°	0.3	0.3	0.3	0.3	0.3	0.3	0.3	0.3
b-VALUE C/2°	(-)2.2	(-)2.2	(-)2.2	(-)2.2	(-)2.2	(-)2.2	(-)2.2	(-)2.2
SATINE (ISO 8254-1) GLOSS HUNTER (%)	18.0	18.0	18.0	18.0	18.0	18.0	28.0	29.0