



www.prodi.com

FICHE TECHNIQUE CARTON PIGMENTE

Popular standard grade, proper printing performance, outstanding runability.

Substance (gsm)			450	500	550	600	650	700	750	800
PROPERTY	UNIT	TEST METHOD								
Thickness	mm	ISO 534	0,61	0,68	0,74	0,81	0,89	0,97	1,04	1,11
Density	g/ccm	ISO 534	0,74	0,74	0,74	0,74	0,73	0,72	0,72	0,72
Plybond	N	DIN 54516	125	125	125	120	120	110	100	100
Settress:										
2 point, 5°MD	mNm	ISO 5628/ DIN 53121	73	103	121	151	181	211	241	269
2 point, 5°CD	mNm	ISO 5628/ DIN 53121	30	36	45	59	73	83	103	113
Moisture	%	EN 20287	8,0	8,0	8,0	8,0	8,5	8,5	8,5	8,5

Substance (gsm)				450	500	550	600	650	700	750	800
PROPERTY	UNIT	TEST METHOD									
Substance	gsm	EN ISO 536	min max	428 473	475 525	523 577	570 630	618 683	665 735	713 788	760 840
Thickness	mm	ISO 534	min max	0,58 0,64	0,64 0,71	0,71 0,78	0,77 0,85	0,84 0,92	0,90 0,99	0,96 1,07	1,03 1,14
Plybond	N	DIN 54516	min	115	115	115	110	110	100	95	95
Bursting strength	kPa	EN ISO 2759	min	720	740	760	780	800	820	840	860
Stiffness	%	ISO 5628/ DIN 53121	min	- 15							
Moisture		EN 20287	+/-	1							
Cobb 60" top/ back	gsm	ISO 535	max	40/40							
Dennison top/ back		TAPPI T 459	min	8/9							