

Fiche technique



Brillant

Couché Moderne Brillant

Données Techniques :

Grammage g/m ² ISO 536	Bulk cm ³ /g ISO 534:1995	Whiteness CIE D 65/10 % ISO 11475	Brightness D65/10 % ISO 2470-2	Opacity D65/10 % ISO 2471	Gloss TAPPI 75 % T480 om-92 ISO/DIS 8245-1	Surface roughness PPS 1.0 ISO 8791-4
90	0.79	122	99	90.5	66	1.0
100	0.79	122	99	92.5	66	1.0
115	0.77	122	99	94.0	70	0.7
130	0.77	122	99	95.0	70	0.7
135	0.77	122	99	95.5	70	0.7
150	0.77	122	99	97.0	70	0.7
170	0.77	122	99	98.0	70	0.7
200	0.77	122	99	99.0	70	0.7
220	0.80	122	99	98.5	70	0.8
250	0.80	122	99	98.5	70	0.8
300	0.80	122	99	99.0	70	0.9
350	0.85	122	99	99.0	70	1.2
400	0.80	122	99	99.0	70	0.8

Certifications usine et produit :

Le papier est composé de plus de 10% de fibres mécanique .

O , usine certifiée : ISO 9001, ISO 14001, OHSAS18001, PEFC CoC, FSC Coc, Permanent paper ISO 9706, EN 71/3 2003 Safety of toys, migration of certain elements, 94/62/EC Heavy metal certificate. Fulfils the Nordics Swan criteria.

U , usine certifiée : ISO 9001, ISO 14001, OHSAS 18001, PEFC CoC, FSC CoC, Permanent paper ISO 9706, EN 71/3 2003 Safety of toys, migration of certain elements, 94/62/ EC Heavy metal certificate.

Gestion durable des forêts :

Produit certifié **sur stock** : PEFC 10-31-1211 (min 70 %)

